

FRAUNHOFER INSTITUTE FOR CERAMIC TECHNOLOGIES AND SYSTEMS IKTS



2011 2012



Fraunhofer Institute for Ceramic Technologies and Systems IKTS

Dresden branch of the institute Winterbergstrasse 28, 01277 Dresden, Germany Phone +49 351 2553-7700 Fax +49 351 2553-7600

Hermsdorf branch of the institute Michael-Faraday-Strasse 1, 07629 Hermsdorf, Germany Phone +49 36601 9301-0 Fax +49 36601 9301-3921

info@ikts.fraunhofer.de www.ikts.fraunhofer.de

FOREWORD



Dear friends of IKTS,

This year, Fraunhofer IKTS celebrates its 20th anniversary! This is a good occasion to look back and celebrate the institute's success story. The story of Fraunhofer IKTS begins with 80 staff members coming from the Institute for Ceramic Technologies and Materials Science (IKTM), the Central Institute for Solid State and Materials Research (ZFW) of the Academy of Sciences and the Sächsische Ingenieurkeramik GmbH Meißen (SIK). We can say with much pride and without any exaggeration that after the merger with the Hermsdorfer Institut für Technische Keramik e.V. (HITK) Fraunhofer IKTS has become one of the world's most prestigious institutes in the field of applied ceramic research. Our sincere thanks for this development go to the team of Fraunhofer IKTS in Dresden and Hermsdorf with its more than 400 scientists, engineers and technicians as well as to our partners.

Let us now move on to the past financial year that we have ended again with a positive result. With an operating budget in Dresden and Hermsdorf of about 33 million euros our total profit rate was again above 80 % (approx. 37 % industry revenues). Therefore, we were able to largely invest in equipment and construction measures (total budget about 41 million euros). Through these investments, we were able to extend our research in the field of structural and functional ceramics, as well as to create more office space by installing a new floor at or pilot plant facility in Dresden. This year, we

will complete further construction measures in Dresden and Hermsdorf resulting in a further improvement of our working conditions. Examples for investments include: the addition of an induction heating option to our SPS (spark plasma sintering) plant, the creation of test stands for the development of DeNox systems, a production line for SiC based tape cast flat filters, and process technologies for the pilot plant production of lithium ion batteries. Due to the latter investment, we were able to establish the conditions for the LiFab project which was funded by the Saxon State Ministry for Science and the Arts (SMWK/SAB). Together with our partners ThyssenKrupp System Engineering GmbH and KMS Technology Center GmbH, we are establishing a pilot line in Pleißa for the development of plants and processes used for the production of lithium ion batteries. Despite Germany's (and the Chemnitz region's) traditional strength in the field of mechanical engineering, there are still shortcomings in the field of plant engineering that we would like to resolve with this project. This is, once again, a good example of how we implement our strategy of closing the gap between laboratory development and production: "from lab to fab".

Which leads us to the topic of "building bridges". I was very pleased that the "Bridge Building Award" of the American Ceramic Society was awarded to me and the institute. I think this motto fits our work perfectly. Our strategy is downright





destined to build bridges: we are building bridges "from lab to fab", i.e. we are able to push our developments from the lab to the pilot plant scale; we are building bridges along the entire value chain "from materials to systems"; we are building bridges between structural and functional ceramics to realize synergies between these fields; we are building "technology transfer bridges" to transfer our R&D results into the industrial sector (at both national and international level); and last but not least we are building bridges between the world

of ceramics and users for whom ceramics and their advantageous applications are still a whole new territory.

In this annual report, you will find various examples for building such bridges. Please enjoy reading it. As always, we would like to invite you to make use of our competencies. We would be pleased to continue building bridges together with you.

The Fraunhofer IKTS as "one-stop shop" for ceramics

Material

Component

Module

System/Product

Ceramic expertise

System expertise

We bring worlds together

Yours,

Alexander Michaelis

A. Mi chael

Bärbel Voigtsberger

March 2012

TABLE OF CONTENTS

2	F
,	FORDMORD

4 Table of contents

Fraunhofer IKTS profile

- 6 Brief portrait
- 8 Organizational chart
- 10 Fraunhofer IKTS in figures
- 12 Board of trustees
- 13 The Fraunhofer-Gesellschaft

Research activities at Fraunhofer IKTS



- 16 Increase of the stability of opaque and transparent armor ceramics
- 18 Transparent tetragonal zirconium oxide
- 20 Ceramic matrix composites for high-temperature applications
- 22 Cost-effective production processes for ceramic filtration stacks
- 24 Plasma-assisted chemical vapor deposition of functional thin films
- 26 Research field: Processes and Components
- 28 Structuring of ceramic green tapes by embossing
- 30 Freeze foaming Cellular structures for versatile applications
- 32 Graded multilayer structures for refractories
- 34 Aging-resistant ZrO₂ ceramics made of commercial powders
- 36 Transparent MgAl₂O₄ ceramics by automated uniaxial pressing
- 38 Research field: Environmental Engineering and Bioenergy
- 40 CNT films for membrane separation and catalysis
- 42 Hydrothermally stable zeolite membranes for H₂ separation
- 44 Design and preparation of membrane components for oxygen production
- 46 Concentration of alcohols using hydrophobic membranes
- 48 Bioenergy Application Center Pöhl

50	Research field: Sintering and Characterization
52	Superhard SiC-diamond ceramics
54	Wafer cutting, abrasive flow machining – Abrasive particles in suspensions
56	Research field: Energy Systems – Materials and Components
58	CFY stacks: Technology for robust systems
60	Scaleable electrode manufacturing technology for supercaps
62	Research field: Energy Systems – Modules and Systems
64	Surface modification of electrodes for biosensor applications
66	Electrochemical and spectroscopic characterizaton of battery materials
68	Development and automated operation of a biogas SOFC system
70	Investigation of the dynamic behavior of catalytic reformers
72	Research field: Energy Systems – Industrialization Energy Systems
74	Characterization of materials and processes for lithium battery production
76	Research field: Smart Microsystems – Smart Materials and Systems
78	Backside passivation of crystalline silicon solar cells by ALD
80	Preparation and characterization of acoustic transducers based on KNN
82	·
82	Ultrasonic transducer arrays for particle manipulation
84	Research field: Smart Microsystems – Hybrid Microsystems
86	Customer and technology specific pastes and inks for PV applications
88	Wireless interrogable temperature sensors based on ceramic substrates
	Detromation
	Retrospective

90

94 96

101

Events and exhibitions

Names, dates, events

134 Events and trade fairs 2012

135 How to reach us

132 Art at Fraunhofer IKTS 2010–2011

Participation in trade fairs and exhibitions

Cooperation in groups, alliances and networks

5

BRIEF PORTRAIT

The work of the Fraunhofer Institute for Ceramic Technologies and Systems IKTS covers all aspects of technical ceramics from preliminary basic research to application. More than 140 well-equipped laboratories and pilot-scale facilities on nearly 20,000 square meters of usable floor space at the two locations Dresden and Hermsdorf are available for this. At Fraunhofer IKTS, high-performance ceramics know-how forms the basis of development work spanning the entire value chain up to prototype manufacture. With threefold expertise – in materials know-how, production technologies, and system/product integration – chemists, physicists, and materials scientists are supported by experienced research engineers and technicians in activities focused equally on structural and functional ceramics technology platforms.

Project partners are found among both manufacturers and users of ceramics. With extensive expertise and numerous contacts, Fraunhofer IKTS serves as a "one-stop shop" for all ceramics-related problems. Our mission is to bring together different technology worlds to give our customers access to the entire range of innovative solutions provided by ceramics. Fraunhofer IKTS possesses a number of unique capabilities:

Complete production lines from material to prototype

All standard processes for mix preparation, shaping, heat treatment, and finishing of structural and functional ceramics are available. A key area of expertise in functional ceramics is paste and film technology. We manufacture functional ceramic prototypes using the hybrid and multilayer ceramics lines in our inhouse clean rooms.

Multiscale development

Developments can be scaled up from laboratory to pilot scale. In our technological production chains, we can manufacture the quantities required for market introduction. Thus, we can minimize retention cost risks and time to market.

Synergies between structural and functional ceramics

By combining different technology platforms, we enable innovative ceramic products with extended functions and considerable added value to be manufactured.



Network formers

We are currently collaborating in projects with more than 450 national and international partners. Fraunhofer IKTS is also active in numerous networks and alliances, within the Fraunhofer-Gesellschaft, for example, in the Fraunhofer Group for Materials and Components – MATERIALS.

In addition, the role of spokesperson for the Fraunhofer AdvanCer Alliance, made up of seven institutes specialized in ceramics, is held by Fraunhofer IKTS. We facilitate network formation to drive product development and obtain the necessary external expertise.

This pioneering work is made possible by a wealth of experience, extensive knowledge, and constant focus on the interests of our partners.

Sustainable quality assurance management in both institute branches

For us, quality is one of the most important factors to stand out from the competition. For this reason, we merged the management systems of both institute branches in 2011. Due to the resulting synergy effects and cost savings we are now able to expand our management system to the fields of work safety and environmental protection.

Fraunhofer IKTS has already introduced and successfully established this environmental management system in Hermsdorf. As the main focus of our research lies in the field of energy and environmental technologies we are going to implement a sustainable environmental management system in Dresden by the end of this year, which will be in accordance with DIN EN ISO 14001. This system will guarantee that our processes will comply to work safety and environmental standards as well as legal conditions and regulations while maintaining our competitiveness.

ORGANIZATIONAL CHART FRAUNHOFER IKTS



Institute Director
Prof. Dr. habil. Alexander Michaelis
Phone +49 351 2553-7512
alexander.michaelis@
ikts.fraunhofer.de



Deputy Institute Director
Dr. Bärbel Voigtsberger
Phone +49 36601 9301-3902
baerbel.voigtsberger@
ikts.fraunhofer.de



Deputy Institute Director/
Head of Administration
Dr. Michael Zins
Phone +49 351 2553-7522
michael.zins@ikts.fraunhofer.de

Materials

Oxide Ceramics
Hardmetals and Cermets
Dr. habil. Andreas Krell

Nitride Ceramics, Carbide and Filter Ceramics, Precursor-Derived

Dr. Hagen Klemm

Ceramics,

Sintering and Characterization
Dr. habil. Mathias Herrmann

Environmental Engineering and Bioenergy

Dr. Ingolf Voigt

Energy Systems

Materials and Components

Dr. Mihails Kusnezoff

Modules and Systems

Dr. Matthias Jahn

Industrialization Energy Systems

Dr. Christian Wunderlich

Processes and Components

Dr. Michael Stelter

TU Dresden, Institute for Materials Science

Inorganic-Nonmetallic Materials

Prof. Dr. habil. Alexander Michaelis

Instrumented Powder Compaction, Combinatorial Microelectrochemistry

Friedrich Schiller University of Jena

Smart Microsystems

Smart Materials and Systems

Dr. Andreas Schönecker

Hybrid Microsystems

Dr. Uwe Partsch



Materials
Oxide Ceramics
Dr. habil. Andreas Krell
Phone +49 351 2553-7538
andreas.krell@ikts.fraunhofer.de



Energy Systems

Materials and Components

Dr. Mihails Kusnezoff

Phone +49 351 2553-7707

mihails.kusnezoff@ikts.fraunhofer.de



Materials
Nonoxide Ceramics
Dr. Hagen Klemm
Phone +49 351 2553-7553
hagen.klemm@ikts.fraunhofer.de



Energy Systems
Modules and Systems
Dr. Matthias Jahn
Phone +49 351 2553-7535
matthias.jahn@ikts.fraunhofer.de



Processes and Components
Dr. Michael Stelter
Phone +49 351 2553-7648
michael.stelter@
ikts.fraunhofer.de



Energy Systems
Industrialization Energy Systems
Dr. Christian Wunderlich
Phone +49 351 2553-7232
christian.wunderlich@
ikts.fraunhofer.de



Sintering and Characterization
Dr. habil. Mathias Herrmann
Phone +49 351 2553-7527
mathias.herrmann@
ikts.fraunhofer.de



Smart Microsystems
Smart Materials and Systems
Dr. Andreas Schönecker
Phone +49 351 2553-7508
andreas.schoenecker@
ikts.fraunhofer.de



and Bioenergy
Dr. Ingolf Voigt
Phone +49 36601 9301-2618
ingolf.voigt@ikts.fraunhofer.de

Environmental Engineering



Smart Microsystems
Hybrid Microsystems
Dr. Uwe Partsch
Phone +49 351 2553-7696
uwe.partsch@ikts.fraunhofer.de


FRAUNHOFER IKTS IN FIGURES

Operating budget and revenues

Due to the early publication date of this year's annual report, the operating budget and revenues for 2011 are presented before the financial statement. Any adjustments will be reflected in the following year. As in 2010, the diagrams show the financial results of both the Dresden and Hermsdorf institute branches. The operating budget of Fraunhofer IKTS has increased to 32.3 million euros: 22.6 million euros fall to the Dresden branch, and 9.7 million euros to the Hermsdorf branch. Here, we achieved synergies by splitting the work between both branches. By doing so, we proved once again that the added value which we aimed for by merging the both institutes was generated. Furthermore, 2.9 million euros were invested in equipment and additional 5.7 million euros in construction measures and the related basic equipment. In this connection, further growth is expected in 2012. In total, we earned 26.5 million euros in external funds. Fortunately, the industry revenues (11.8 million euros) of 45 % could be maintained as in the year before. The Hermsdorf branch contributed to this success with revenues of 3.8 million euros. With an increase of 0.6 million euros, Dresden was significantly above last year's results.

Expansion of the research basis

In 2011, Fraunhofer IKTS once again benefited from the large investments of the last years which were made within the framework of the Development Center for Energy Efficiency Systems. Especially for the large number of joint projects, these investments are the infrastructural basis for research in the field of fuel cells, photovoltaics, electricity generation from biomass, thermoelectric generators (TEG) and energy storage technologies (lithium ion batteries). We make use of the option to collaborate with strategic partners from industry and research in external laboratories and research facilities with our own equipment and staff. Through this cooperation, the




close relationship between industry and applied research can be further strengthened. Thus, the fast and exact drafting of cooperation and user agreements becomes a strategic tool. Aside from collaborations in the energy and environmental sector, the collaborations in the field of shaping and production technologies were intensified. One example is the strategic partnership with the Department of Ceramic, Glass and Construction Materials of the TU Bergakademie Freiberg (Prof. Aneziris). Within this project refractories are developed by applying new structural ceramic materials and adjusted manufacturing methods. Another example includes the cooperation with the Friedrich Schiller University Jena in which a concept of a joint Center of Energy and Environmental Chemistry (CEEC) was developed and two research groups were established. By pooling the material scientific as well as system and processing-relevant competencies, basic and applied research is significantly pushed, and thus a basis for innovation in Thuringia and especially the Jena-Saale-Holzland region is created.

Within the Fraunhofer-Gesellschaft we are closely linked. Fraunhofer's research programs significantly facilitate the generation of own IP rights and thus, the long-term opportunity to acquire new industry projects. Due to the integration of the Hermsdorf institute branch, we have further technologies and materials at hand.

Personnel development

Last year was marked by a considerable increase of staff. We created 10 new jobs for scientists and 24 jobs for graduates and technicians. In total, we have 431 full-time positions with 381 employees in Dresden and 140 employees in Hermsdorf. The cooperation with the chair of IfWW, Institute for Material Science at TU Dresden, remains an essential part of our personnel recruitment. Currently, 50 doctoral theses are being supervised.



In 2011, 13 apprentices were trained. By training apprentices at the IKTS, the quality of our laboratory work will be further improved, and knowledge transfer between the working groups is being supported. Regular exchange between the institute branches and departments is an increasingly important factor.

BOARD OF TRUSTEES

The president of the Fraunhofer-Gesellschaft has appointed the following people to the board of trustees at Fraunhofer IKTS:

Dr. G. Gille

Chairman of board of trustees

H.C. Starck GmbH & Co. KG, Goslar

Manager of Central Department Research and Development

Dr.-Ing. S. Blankenburg

CEO of Hermes Schleifkörper GmbH, Dresden

Dr. J. Damasky

Board member of Webasto AG, Stockdorf

A. Heller

Administrative head of the Saale-Holzland region

Prof. Dr.-Ing. J. Huber

Board member of CeramTec AG, Plochingen

Prof. Dr. C. Kaps

Bauhaus University Weimar, Chair of building chemistry

A. Krey

CEO of Landesentwicklungsgesellschaft Thüringen mbH (LEG), Erfurt

Dr. R. Lenk

CeramTec AG, Plochingen

Head of Central Development Department

Dr. C. Lesniak

ESK Ceramics GmbH & Co. KG, Kempten Vice president Technology and Innovation

Dr. F. Lindner

Robert Bosch GmbH, Gerlingen

Department head of Corporate Research and Development

Advanced Functional and Sintered Materials

Dr. H.-H. Matthias

Managing director of Tridelta GmbH, Hermsdorf

Dr. R. Metzler

Managing director of Rauschert GmbH, Judenbach-Heinersdorf

Dipl.-Ing. P. G. Nothnagel

Managing director of Wirtschaftsförderung Sachsen GmbH,

Dresden

Dipl.-Ing. M. Philipps

Endress+Hauser GmbH & Co. KG, Maulburg Head of business sector Sensor Technology

Dr.-Ing. W. Rossner

Siemens AG, München

Head of Central Department Technology, Ceramics

Dr. K. R. Sprung

CEO of German Federation of Industrial Research Associations

Prof. Dr. P. Woditsch

Sunicon GmbH, Freiberg

MR C. Zimmer-Conrad

Saxon Ministry of Science and the Fine Arts

Head of Technology Policy and Technology Funding Department


THE FRAUNHOFER-GESELLSCHAFT

Research of practical utility lies at the heart of all activities pursued by the Fraunhofer-Gesellschaft. Founded in 1949, the research organization undertakes applied research that drives economic development and serves the wider benefit of society. Its services are solicited by customers and contractual partners in industry, the service sector and public administration.

At present, the Fraunhofer-Gesellschaft maintains more than 80 research units in Germany, including 60 Fraunhofer Institutes. The majority of the more than 20,000 staff are qualified scientists and engineers, who work with an annual research budget of €1.8 billion. Of this sum, more than €1.5 billion is generated through contract research. More than 70 percent of the Fraunhofer-Gesellschaft's contract research revenue is derived from contracts with industry and from publicly financed research projects. Almost 30 percent is contributed by the German federal and Länder governments in the form of base funding, enabling the institutes to work ahead on solutions to problems that will not become acutely relevant to industry and society until five or ten years from now.

Affiliated international research centers and representative offices provide contact with the regions of greatest importance to present and future scientific progress and economic development.

With its clearly defined mission of application-oriented research and its focus on key technologies of relevance to the future, the Fraunhofer-Gesellschaft plays a prominent role in the German and European innovation process. Applied research has a knock-on effect that extends beyond the direct benefits perceived by the customer: Through their research and development work, the Fraunhofer Institutes help to reinforce the competitive strength of the economy in their local region, and throughout Germany and Europe. They do so by promoting innovation, strengthening the technological base, improving the acceptance of new technologies, and helping to train the urgently needed future generation of scientists and engineers.



As an employer, the Fraunhofer-Gesellschaft offers its staff the opportunity to develop the professional and personal skills that will allow them to take up positions of responsibility within their institute, at universities, in industry and in society. Students who choose to work on projects at the Fraunhofer Institutes have excellent prospects of starting and developing a career in industry by virtue of the practical training and experience they have acquired.

The Fraunhofer-Gesellschaft is a recognized non-profit organization that takes its name from Joseph von Fraunhofer (1787–1826), the illustrious Munich researcher, inventor and entrepreneur.

RESEARCH FIELD MATERIALS

Department heads: Dr. habil. Andreas Krell Dr. Hagen Klemm

Profile

The core competency of the "Materials" research field lies in the development of new or modified ceramic materials and ceramic-metal composites (hardmetals and cermets) with the use and generation of state-of-the-art technologies.

Our offering ranges from targeted synthesis of raw materials from ceramic precursors or renewable raw materials and application-oriented materials development to technological trials and manufacture of prototype parts and systems, including characterization and testing. Material-specific and technological aspects for industrial applications and safety-/health-related aspects are considered.

One focus of materials qualification is the development of low-defect and low-cost processes. Our wide range of capabilities encompasses powder processing technologies for simply structured ceramic materials as well as fiber processing and coating technologies for composite materials and functional coatings for solar applications.

The successful development of new application fields through targeted combination of structural and functional properties in ceramics and ceramic-metal composites is reflected, for example, in the development of high-temperature materials, electrically conducting ceramics, thermoelectric materials, forming tools, transparent components, functional ceramic coatings, and filters.

Services offered

- Integrated materials and process development for novel high-performance ceramics and hardmetals
- Development and supply of raw materials, trial parts, and complex components
- Expert opinions on production and application problems
- Materials testing (mechanical, tribological, electrical, and corrosive properties at room and high temperatures)
- Damage and failure analysis of components and tools
- Evaluation of safety and health risks from use of fine powders and materials
- Characterization of wetting behavior of coatings and surface tension of liquids
- Characterization of corrosion behavior under realistic application conditions (hot gas corrosion)





Department headOxide Ceramics, Hardmetals and
Cermets

Oxide Ceramics
Dr. habil. Andreas Krell
Phone +49 351 2553-7538
andreas.krell@ikts.fraunhofer.de



Department head
Nitride Ceramics, Carbide and
Filter Ceramics, Precursor-Derived
Ceramics

Nitride Ceramics
Dr. Hagen Klemm
Phone +49 351 2553-7553
hagen.klemm@ikts.fraunhofer.de




Hardmetals and Cermets
Dr. Volkmar Richter
Phone +49 351 2553-7614
volkmar.richter@
ikts.fraunhofer.de



Carbide and Filter Ceramics Dipl.-Krist. Jörg Adler Phone +49 351 2553-7515 joerg.adler@ikts.fraunhofer.de



Precursor-Derived Ceramics
Dr. Isabel Kinski
Phone +49 351 2553-7560
isabel.kinski@ikts.fraunhofer.de



INCREASE OF THE STABILITY OF OPAQUE AND TRANSPARENT ARMOR CERAMICS

Dr. Andreas Krell, Dipl.-Ing. Thomas Hutzler, Dr. Jens Klimke

Numerous previous studies investigated influences of materials selection, microstructures and basic mechanical data on the ballistic strength of ceramics under different threats or with different backing. Frequently, results seemed to reveal some apparent influences e.g. of hardness, Young's modulus or compressive strength which, however, disappeared completely at changed configurations. Understanding that

- the ballistic strength of armor ceramics is governed by the efficiency of projectile erosion and that
- the missing influence of strength indicates a strong role of the inertia (i.a. of the size) of ceramic debris,


Fraunhofer IKTS had proposed the hypothesis of a hierarchic ranking of major influences as known for the wear of ceramics: it was assumed that e.g. a high hardness will give rise to strong projectile erosion if ceramic fragmentation proceeds with a sufficiently large size of the debris. This positive influ-


ence of the hardness should, however, disappear when a narrow network of cracks forms small ceramic fragments.

The present study checked this hypothesis comparing

- the ballistic performance (in depth of penetration and perforation tests) of combinations of different backing materials with about ten highly dense but differently fine or coarse grained alumina and spinel ceramics and single crystals
- with comparative measurements of the Young's modulus, the bending strength and $K_{\rm ic}$, and of statically ($4\cdot10^{-3}$ /s) and dynamically measured (10^{3} /s) compressive strengths of these ballistically tested ceramics. The evaluation also included static and dynamic hardness data and the Hugoniot Elastic Limit (HEL) of such ceramics.

The major result is a confirmation of the idea of a hierarchic ranking of basic influences in three levels. Top priority is the mode of ceramic fragmentation. Thus, on ballistic impact the close spacing of cracks of failing sapphire (known from the crack network on Vickers tests - figure 1a/b) gives rise to small debris and less erosion of the projectile by sapphire (figure 2b) compared with polycrystalline Al₂O₃ (figure 2a). Another major influence on ceramic fragmentation and, thus, on projectile erosion comes from the dynamic stiffness of backings: the figure on the left shows a tremendously stronger projectile erosion by Al₂O₃ in front of glass than with Al backing – despite of a similar Young's modulus of Al and glass. Obviously, fragmentation will govern both the dwell and the subsequent penetration phase of the ceramic/projectile interaction: it influences the duration and extent of dwell, and on penetration it governs the force of inertia and, thus, the degree of projectile erosion.






Second priority is the elastic stiffness of the ceramic body on immediate impact (during dwell). This is the reason why at same hardness but with a higher Young's modulus the ballistic strength of coarse Al_2O_3 ceramics may exceed (depending on backing and threat) that of the best (most fine-grained) spinel ceramics.

Only when matching the before mentioned conditions a high hardness (e.g. by grain sizes < 1 μ m; see diagram below) will improve the ballistic strength significantly (diagram on the right). Compared with the three described influencing parameters, all strength parameters (in bending or in compression, by static or highly dynamic measurements) and K_{lc} turned out meaningless (see red frame in the diagram on the right).


Services offered

- Armor ceramics with defined properties for specific tests
- Ballistic evaluation in cooperation with Fraunhofer EMI

Increase of hardness of oxide ceramics by fine grained (sub-µm) microstructures with high sintering density; comparison of different hardness numbers



With stiff (steel) backing strong influence of high hardness (achieved by small grain size) on the ballistic stability of Al₂O₃ ceramics – without any impact of ceramic strength




Grain size, technology:


- 0.4 μm, gelcasting, HIP
- 0.6 μm, gelcasting, HIF
- ▲ 0.5 μm, pressed
- 0.6 μm, gelcasting0.7 μm, pressed
- 0.9 µm, pressed
- * 10 μm, gelcasting
- 0.3 μm, pressed × 17 μm, AD995

Acknowledgments

The presented work was subject of a joint project issued by WTD91 of the German Army (Bundeswehr) and realized together with the Fraunhofer Ernst-Mach Institute (EMI; ballistic investigations) between 2007 and 2011.

- **1** Different fragmentation under identical load.
- 2 Different wear impact on the penetrator (high-speed photography at t = 8 µs by E. Strassburger, EMI) resulting from different fragmentation.





TRANSPARENT TETRAGONAL ZIRCONIUM OXIDE


Dr. Jens Klimke, Dr. Andreas Krell


Recently, there has been considerable interest in transparent ceramics because of their unique combination of optical and mechanical properties, particularly with regard to window, laser, lamp envelope, and ballistic armor applications. However, most of the materials investigated so far have a cubic crystal structure and only few transparent non-cubic ceramics are known. The outstanding mechanical properties make the tetragonal ZrO₂ modification an interesting candidate for transparent ceramics. In addition to potential applications as high-strength windows, there is a demand for transparent and translucent tetragonal ZrO2 ceramics for dentures. The high refractive index of all ZrO₂ polymorphs increases the scattering losses caused by residual porosity far beyond the usually known level of other transparent ceramics. In contrast to the cubic modification, however, transmission of tetragonal porefree ZrO₂ ceramics is furthermore restricted by optical birefringence at each grain of the microstructure.

The present investigation has estimated the conditions to obtain transparent tetragonal $\rm ZrO_2$ ceramics (partially stabilized by yttria) by comparing the experimental results for sintered nanopowder with scattering calculations. The Mie calculations show that, for example, a porosity of only 0.01 % reduces the transparency by 58 % at a pore size of 300 nm (diagram on the right). The validation of these calculations required extreme experimental efforts in order to provide highly dense tetragonal $\rm ZrO_2$ polycrystals with grain sizes < 150 nm. A $\rm ZrO_2$ nanopowder stabilized with 3 mol % yttria, which had been synthesized in cooperation with the Brno University of Technology by a special sol-gel method (figure 1) and which was cold isostatically pressed at 1000 MPa, was used. To achieve

full densification the pressed pellets were pre-sintered in air followed by hot isostatic pressing (HIP) at 1100°C and 200 MPa, and annealing in air at 800°C. The final densification was determined by measuring the real in-line transmission (RIT) and by SEM analysis of the microstructures. Figure 2 shows a microstructure with a mean grain size of 95 nm and with some residual porosity whereas figure 3 presents a dense sintered microstructure with a mean grain size of 118 nm. Figure 4 shows the view through a polished disk of this material.

The total forward transmission measured with a CARY4000 spectrometer with integrating sphere was 54 to 57 % in the









visible range despite some residual porosity. The maximum inline transmission of 77 % in the IR range between 4 and 5 μ m is in good agreement with the calculated transmission for a mean birefringence of 0.035 (diagram below).

Assuming that a transmission of at least 50 % is necessary in the visible range of light for a similarly clear look through the ceramic material as through glass windows, this transmittance demands a grain size < 40 nm if the ceramic material is 1 mm thick. However, at 50 % transmission scattering can still induce a whitish or yellowish appearance, and the transparency further decreases at larger thickness. Thus, a better quality with a transmission > 70 % should be preferred but requires grain sizes < 20 nm according to the calculation presented in the diagram on the right. The calculation also demonstrates that the influence of grain size is significantly reduced in the IR range.





The high transmission in the midwave IR makes the dense sintered, nanoscale, tetragonal $\rm ZrO_2$ attractive as a potential material for durable IR windows with improved mechanical properties.

- **1** TEM micrograph of ZrO_2 (3 mol % Y_2O_3) powder.
- 2 SEM micrograph with mean grain size of 95 nm.
- 3 SEM micrograph with mean grain size of 118 nm.
- 4 Look through a disk of 0.5 mm thickness.





CERAMIC MATRIX COMPOSITES FOR HIGH-TEMPERATURE APPLICATIONS

Dipl.-Ing. Katrin Schönfeld, Dr. Hagen Klemm

Motivation


Ceramic matrix composites (CMC) play an ever increasing role in technology due to their excellent material properties. Particularly under high temperatures (> 800°C), ceramic materials have a high potential to replace metal materials and to facilitate processes at much higher temperatures. This is of increasing importance considering energy and environmental aspects as natural resources are limited. By embedding ceramic fibers into a ceramic matrix, the otherwise brittle behavior of monolithic ceramics (catastrophic failure due to brittle fracture) has changed in a way that the cracks formed under mechanical stress are deflected and branched. Thus, a damage-tolerant behavior is given which is interesting at cyclic loading of components.


Process development

At Fraunhofer IKTS, a manufacturing technology for ceramic matrix composites was developed which is based on placing ceramic fiber bundles onto rotationally symmetric cores. With the help of a CAD program, the geometry, fiber orientation as well as winding structure can be varied. A high-temperature stable SiC fiber (UBE SA 3) was used as basic material for the development of non-oxide CMC. During the winding process, the fiber bundle was impregnated with a ceramic slurry (SiC, $\operatorname{Si}_3\operatorname{N}_4$) forming the basis for the later matrix structure. The blanks manufactured by this method were infiltrated with a preceramic SiCN precursor and pyrolized (PIP) several times, and then sintered.

Results

By specifically varying the basic materials, fiber coating, fiber orientation pattern as well as sintering conditions, SiC fiber reinforced $\mathrm{Si_3N_4/SiC}$ composites of different properties were manufactured. In a circular ring test, these materials showed a damage-tolerant behavior and a strength of > 200 MPa. Oxidation and corrosion tests (hot gas with high flow velocity) in the temperature range between 1200 and 1450°C were in the focus of the high-temperature characterization of these materials. The formation of a nearly dense layer on the surface of the composite material was fundamental for the high oxidation and corrosion stability. Whereas a $\mathrm{SiO_2}$ protective layer which was in situ formed prevents the passing of oxygen and thus the oxidation inside the material during oxidation processes, the materials suffering hot gas corrosion had to be coated








with an environmental barrier coating (EBC). EBC coatings on the basis of silicates of the Rare Earths showed promising results. It is the subject of future studies to design the surface microstructure of CMC materials with oxidation and corrosionresistant functions.

Services offered

- Materials development for ceramic matrix composites
- Manufacture of components made of ceramic composites
- Mechanical materials testing
- High-temperature characterization in oxidizing and corrosive media
- Development of environmental barrier coatings (EBC) on CMC




The presented works were financed by the EU within the framework of the Dresden Innovation Center Energy Efficiency (DIZE^{eff}).



- 1 Fiber winding process.
- 2 Components made of SiC₄/Si₃N₄.
- **3** *Micrograph of a ceramic matrix composite.*
- 4 Reinforced SSiC tube.





COST-EFFECTIVE PRODUCTION PROCESSES FOR CERAMIC FILTRATION STACKS

Dipl.-Ing. Heike Heymer, Dr. Hans-Jürgen Richter, Dipl.-Ing. Olaf Scheithauer, Dr. Burkhardt Fassauer, Dipl.-Krist. Jörg Adler

Low-cost polymer membranes are commercially used for membrane filtration. Ceramic membranes, however, show better properties in terms of chemical stability, defined pore width and long-term stability. It was the aim to develop cost-effective, industrial-scale material and technology concepts for ceramic microfiltration membranes.


Within a project funded by the Free State of Saxony, Fraunhofer IKTS developed a concept for the manufacturing of cost-effective ceramic membranes for liquid filtration. Furthermore, all technological requirements were fulfilled to manufacture these membranes in industrial scale. In addition to material selection and technology development, testing methods for the filter elements were designed as well.

The concept provides a three-layer structure (diagram on the right). Glass-bound SiC was selected enabling the cofiring of the different porous layers. The total porosity of the material amounts to 45 %. The support strength reaches a level of 50 MPa. The used glass is chemically stable in the pH range between 1.5 and 9. In some cases, the cleaning procedure necessary for microfiltration membranes has to be adjusted to this glass. In this field, Fraunhofer IKTS has extensive experience on the basis of corrosion tests with conventional membrane cleaning agents.

A tape casting process on the basis of aqueous suspensions was developed for the manufacture of two-layer tapes (support and intermediate layer) made of glass-bound SiC (boron silicate bond). By wave-like structuring of the green tape and subsequent joining of the wavy and plane tape, flat mem-

branes are produced. These membranes are sintered in a continuous kiln within 2.5 hours using a sintering regime that is specifically adjusted to the glass binder. Then, the filtration layer is applied by dip coating, where ten filter elements can be machine-dipped simultaneously. After another sintering step of the same kind, the multichannel elements are tested for defects by bubble point measurements. It is generally possible to consolidate all three layers during one single sintering step. This method is currently investigated. The assembly of a filter stack, consisting of 31 multichannel elements for example, was realized by embedding the single elements into polyurethane resin.

The medium to be filtrated passes the interstices between the multichannel elements in the stack. The filtrate drains off through the channels. On account of the specific membrane geometry, the laminar flow behavior is disturbed and the con-








centration polarization over the membrane surface is mainly prevented so that even at low flow velocities high filtration flows can be reached. By reducing the necessary flow velocity and thus the necessary energy costs, the concept developed at Fraunhofer IKTS is a good alternative to the state-of-the-art shell-and-tube membranes made of alumina.

Due to their high chemical and abrasion stability, the developed SiC membranes can widely be used and are suitable, for example, for the filtration of biogeneous systems such as fermentation residues or sewage sludge. These media are a great challenge for filtration systems on account of the contained microorganisms and the resulting biofouling as well as the high content of fine materials. With the new system very good results have already been obtained in laboratory tests in which nutrients were retained from residual sludge during the dewatering process. At present, the membrane stacks are tested on an industrial-scale biogas plant.

Services offered


- Development of materials and technologies for costeffective ceramic membranes
- Development and manufacturing of filter modules
- Process and application tests
- Upscaling and commercialization



- 1 Three-layer structure of a filter.
- 2 Folding machine (structuring of green tape).
- 3 Continuous kiln.
- 4 Test stand at an industrialscale biogas plant.







PLASMA-ASSISTED CHEMICAL VAPOR DEPOSITION OF FUNCTIONAL THIN FILMS

Dipl.-Ing. Stefan Uhlig, Dr. Katja Wätzig, Dr. Isabel Kinski

Plasma-assisted chemical vapor deposition (PECVD) is used for industrial solar cell production based on thin functional layers. PECVD differs from conventional CVD energy transfer (thermal) as it works via the activation of the gaseous or liquid precursors using an rf excitation (e.g. 13.56 MHz). As the thin film layers are formed at low temperatures (< 450°C) due to plasma activation, PECVD is more favorable than thermal CVD (up to > 1000°C). Thus, the materials can be customized to the properties as well as precipitated on temperature-sensitive substrates. The thin-film solar cells are based on sequentially deposited thin absorbing layers (e.g. amorphous, microcrystalline silicon or SiC_x), contact layers (e.g., transparent conductive oxides – TCO) and reflection interlayers (e.g. SiO_x, SiN_y).

Using the AK 800 of Roth & Rau AG, Fraunhofer IKTS is able to process substrate sizes of up to 50 x 50 cm² on a pilot scale, and to scale-up the technologies and materials developed and optimized at the institute. With the AK 800 system, absorbing and reflection interlayers as well as the TCO can be deposited, so that all necessary layers for thin-film solar cells can be generated in a multilayer package.


The deposition system has two reaction chambers connected by a load lock. In the chambers a pressure of 0.1 to 10 mbar and deposition temperatures of up to 450°C can be realized. The parallel plate configuration with variable plate spacing and plasma power of up to 2500 W are suited for various deposition processes and their unique process requirements. The following examples of thin silicon absorbing layers and transparent conductive zinc oxide layers emphasize the variety of the PECVD process.


Microcrystalline and amorphous silicon

Silicon-based absorbing layers are deposited using gases (e.g. monosilane) or liquid precursors (e.g. higher silanes). By varying the process parameters the degree of crystallinity can be adjusted. Amorphous and microcrystalline silicon films (a-Si and µc-Si) have different band gaps and can be used in combination with each other, for example, in the tandem thin-film solar cell to absorb a wider range (400 to 1100 nm) of the solar spectrum, and thus contribute significantly to improve the efficiency.

Transparent conductive zinc oxide

Optoelectronic components and systems (OLEDs, thin-film solar cell) demand a transparent and conductive material to connect the optical functional layers electrically. Additionally, the conductive materials must guarantee a broad light transmission. Zinc oxide has a direct band transition of 3.4 eV and thus is an outstanding candidate for high light transmission. Adding doping elements of Group 13, zinc oxide can be changed into an n-type semiconductor. In close cooperation with the chairs of Semiconductor Physics and Inorganic Non-Metallic Materials at the Technical University of Dresden, zinc oxide layers were developed that have been deposited onto glass substrates by PECVD. The collaborative project was funded by the Dresden Innovation Center Energy Efficiency DIZEeff. Using different doping agents the mechanisms for n-type or p-type conduction in zinc oxide can be analyzed. Furthermore, the influence of process parameters on the layer growth can be investigated.







In the doped zinc oxide films (ZnO:B) a transparency of > 80 % in the visible light spectrum and high charge carrier concentrations $> 10^{20} \text{ cm}^{-3}$ were observed.

Services offered

- Deposition of functional thin films
- Evaluation of PECVD process parameters
- Process transfer to pilot scale
- Synthesis of metal-organic compounds
- Evaluation of PECVD precursors





boron content of the zinc oxide thin films

- 1 Two chamber PECVD tool.
- 2 a-Si thin-film on glass.
- 3 TCO thin film (ZnO).
- 4 Single-junction PV cell (FIB cut).



RESEARCH FIELD PROCESSES AND COMPONENTS

Department head: Dr. Michael Stelter

Profile

The research field "Processes and Components" encompasses manufacturing processes for ceramic components and assemblies. Prototype solutions are generated on laboratory and pilot scale, small batches are produced and, if required, scaled up to pilot technologies. The value chain ranges from modification of commercial powders and raw materials to shaping, sintering, machining (green and sintered bodies), and to joining and integration technologies. The equipment enables scale-up of all individual technological processes to industrial standards, readily transferrable to the customer's site.

Design of ceramic and metallic materials as well as composite materials and their precursor products form the heart of our powder technology. Silicate and polymer ceramics are additional core areas of materials expertise. Our component design group employs a broad range of plastic and thermoplastic shaping and casting technologies as well as powder pressing. Component surfaces are treated using plasma spray processes.

The technology chains are completed with a capable and innovative green machining and finishing center. Our high standard of quality is supported by a first-class QM system and numerous certifications and expert audits.

Overall, the research unit offers outstanding possibilities for component manufacturing, system integration, and advanced materials. Prototypes and small batches can be delivered quickly, reliably, and cost effectively. We offer a flexible handling and rapid response in order to help our customers to reduce the time to market

Services offered

- Development of ceramic processes, components and systems on a pilot scale
- Contract research and joint projects
- Services related to manufacturing processes
- Technology transfer
- Design of scientific equipment
- Feasibility studies
- Consulting and training courses

In conjunction with other research fields at Fraunhofer IKTS, namely materials development and simulation, we offer competent advice and excellent R&D to our partners. We can draw on the expertise of other institutes in the Fraunhofer AdvanCer Alliance to extend our scope.

www.advancer.fraunhofer.de





Department head
Dr. Michael Stelter
Phone +49 351 2553-7648
michael.stelter@ikts.fraunhofer.de



Powder Technology
Dr. Manfred Fries
Phone +49 351 2553-7810
manfred.fries@ikts.fraunhofer.de



Thermal Spraying
Dipl.-Ing. (FH) Bernd Gronde
Phone +49 36601 9301-4758
bernd.gronde@ikts.fraunhofer.de



Shaping
Dr. Tassilo Moritz
Phone +49 351 2553-7747
tassilo.moritz@ikts.fraunhofer.de



Pilot Manufacturing High-Purity Ceramics Dipl.-Chem. Frank Kastner Phone +49 36601 9301-4300 frank.kastner@ikts.fraunhofer.de



Component Development Dipl.-Ing. Jens Stockmann Phone +49 351 2553-7561 jens.stockmann@ ikts.fraunhofer.de




Oxide and Polymer-Ceramic Components Dipl.-Ing. Henry Ludwig Phone +49 36601 9301-4968 henry.ludwig@ikts.fraunhofer.de




Finishing
Mst. Matthias Nake
Phone +49 351 2553-7586
matthias.nake@ikts.fraunhofer.de



Process Technology and Silicate Ceramics Dipl.-Chem. Gundula Fischer Phone +49 36601 9301-1850 gundula.fischer@ikts.fraunhofer.de






STRUCTURING OF CERAMIC GREEN TAPES BY EMBOSSING

Dip.-Ing. (FH) Anja Kucera, Dr. Tassilo Moritz


For several decades, ceramic substrates have been used to manufacture functional components in multilayer technology. The integration of channel structures allows future applications in biotechnology, sensor technology as well as micro-reaction technology. Accurate, reproducible and high throughput production technologies are essential for the cost-effective production of such structured multilayer substrates.

Within the framework of the EU Large Project MULTILAYER (FP7-NMP-2007-214222), the Fraunhofer IKTS developed alumina and zirconia green tapes for subsequent structuring.



These substrates will be used as multi-channel elements, and integrated into a micro reactor. Three dimensional structures with various aspect ratios can be generated by embossing. In the future, the roll-to-roll process shall allow an upscaling to high throughput production. In contrast to hot embossing, which is widely used in plastics industry, the ceramic green tapes are embossed at room temperature. This allows for a significant reduction of cycling time for machining.

The key aspect within the project was the development of green tapes made of water-based systems which are suited for cold embossing. Environmental aspects as well as the mechanical behavior of the binder system determine the selection of the single components. For this purpose, various tape compositions were developed. Then, their flowability during processing and elastic-plastic behavior were characterized. Amongst others, tensile testing and micro indentation tests were used for analyzing the mechanical behavior of the green tapes. As result, an optimal composition was chosen which can be used as binder system for upscaling. For optimal process control, embossing tests were carried out at a modified tensile-compression machine. The embossing tool was made of brass. The channel height and the molding geometry were modified to compensate the elastic amount of binder during embossing. Different process parameters like maximum press capacity, dwell time or impression velocity were varied during embossing to analyze their influence on the embossing result. The resulting channel structure can be seen in figure 2. Using confocal white light microscopy, the dimensions of the structure can be measured and shown.




By laminating a structured and unstructured green tape, a compound of both can be realized. For this purpose, studies on cold chemical lamination are carried out. Conventional techniques, for example hot isostatic and uniaxial lamination, are also considered. It is the main aim of lamination to obtain an excellent contact between the layers while keeping the integrated structures. The resulting channel elements allow for the transport of fluids, and simultaneously serve as mechanical interface.

Acknowledgments

The European Commission is gratefully acknowledged for funding the MULTILAYER project (FP7-NMP-2007-214222). We thank all cooperating partners of the project consortium for contributing to the results.


Services offered

- Development of aqueous and organic as well as UV curable tape casting slips
- Development of green tapes as well as tape processing by embossing, deep drawing, corrugating, wrapping and laminating



- **1** Embossing tool made of steel.
- **2** REM image of a cross section through a channel in alumina green tape.
- 3 REM image of channel top view in alumina green tape.





FREEZE FOAMING – CELLULAR STRUCTURES FOR VERSATILE APPLICATIONS

M. Sc. (Chem.) Matthias Ahlhelm, Dr. Tassilo Moritz


In addition to the typical properties of ceramics such as wear resistance or brittleness, porous cellular ceramics are characterized by a broad variety of possible applications. Potential applications range from biomedicine (membrane bioreactors, bone scaffolds), through biomimetics (honeycomb filters) to mechanical and plant engineering (reactors, burners, insulators and refractories).


The freeze-foaming process presented here has the potential to cover at least two of these fields. Freeze-foaming is foaming of an aqueous ceramic or metallic suspension with subsequent freeze-drying to a porous, cellular structure. For this purpose, the ambient pressure is reduced in a freeze-drying device through which water vapor and residual air inflates the suspension (diagram on the right, curve sections I, II). As evaporation in aqueous suspensions causes a drop of temperature, the foaming suspension suddenly freezes at the intersection of the liquid-vapor-solid equilibrium line (triple point). By heating the panels underneath, the now stable protofoam is freeze-dried due to sublimation of the frozen water (curve section IV).


A porous, biocompatible ceramic foam was manufactured using different hydroxyapatite powders (Merck KGaA and SIGMA-ALDRICH Cooperation). It could be proved that this foam is suited for cell cultivation and even differentiation (figure 2). If toughness values similar to those of a real bone were achieved, the ceramic foam might be used as implant. The freeze-foaming technique also provides the possibility to manufacture a specific, outer shape of a porous foam by using, for example, synthetic rubber as counterpart. Figure 1 shows such a hydroxyapatite foam replica in shape of a human


thumb bone. The pore structure fulfilling the requirements to cultivate cells can be characterized by non-destructive X-ray computed tomography (PROCON X-Ray, max. 150 kV) and image analyzing software (Porescan, Image J) as well as mercury porosimetry.


In further studies, the freeze-foaming technique was successfully used to up-scale the manufactured foams to bigger geometries. Using a mullite powder (NABALTEC, KO/KOc) a freeze foamed structure (235 x 114 x 70 mm³) was achieved which might be used as light-weight insulating brick in refractory industry (figure 3). As shown in the lower diagram, the first tested samples (H01-H09) have already met the necessary requirements of refractories. The determined thermal conductivity is similar to state-of-the-art products.












So far, freeze foamed cellular structures have been manufactured in laboratory scale. However, through a specific adjustment of the process parameter and the experimental equipment, the manufactured quantity can be increased. In addition to the presented starting material, other ceramic powders (like SiC, ZrO₂, Al₂O₃, hybrids) and also powder metals (e.g. steel) can be transferred to porous semifinished parts.

Services offered

- Freeze foaming
- Freeze drying
- Development of suspensions

- **1** Hydroxyapatite foam replica in shape of a human thumb bone.
- 2 Vital staining of cultivated human mesenchymal stem cells in the hydroxyapatite foam, proved using fluorescein diacetate, in cooperation with Fraunhofer IBMT.
- **3** Light-weight insulating brick by freeze foaming.
- **4** Freeze-foamed microstructure, ion-polished (hydroxyapatite).





GRADED MULTILAYER STRUCTURES FOR REFRACTORIES

Dipl.-Ing. Uwe Scheithauer, Dipl.-Ing. Kristin Haderk

Within the framework of the DFG priority program 1418 "Refractories – Initiative to Reduce Emissions", new manufacturing and characterization methods are developed for refractories of the next generation. These components are free of carbon resulting in increased oxidation stability and reduced thermal conductivity. So, insulation properties can be improved and energy can be saved. However, carbon-containing refractories are characterized by very good thermal shock behavior.


To reach a thermal shock behavior of the carbon-free refractories which is comparable with the behavior of carbon-based refractories, the ceramic multilayer technology is further developed at Fraunhofer IKTS. Ceramic green tapes are cast and laminated to large-size products. It is the aim to improve the thermal shock properties by specifically placing pores and creating a graded pore structure. For this purpose, green tapes are made of water-based slurries with different amounts of pore forming agents. These tapes are cut, stacked and laminated using a new lamination technology which guarantees a defect-free joining of the single tapes and the co-sintering to one product with a defined graded microstructure. By adapting a paper winding technology, it is possible to manufacture axially symmetrical samples as well as components with a rectangular cross-section which also have a graded microstructure in radial direction

Cellulose fibers or graphite platelets were used as pore forming agents, which are burned-out before sintering and leave pores of defined size and orientation. During tape casting shear forces have an effect on the slurry components between doctor blade and carrier tape. Thus, the fibers (one-dimen-

sional) and graphite platelets (two-dimensional) are arranged in casting direction and leave pores in the same direction after burn-out and sintering. A crack, which is induced by thermal shock and propagates vertically to the tape layer, is absorbed and its propagation is slowed down to increase the lifetime of the product.

By means of suitable characterization methods, the samples of different compositions are analyzed in terms of temperaturedependent conductivity (specific heat capacity, coefficient of expansion, density and conductibility of temperature) and mechanical strength as well as residual strength after thermal shock by 4-point bending. These characteristic values allow scientists at TU Bergakademie Freiberg to simulate thermal shock behavior of multilayers with different graded microstructures to identify optimal gradients. Then, these multilayer structures are realized and characterized at Fraunhofer IKTS. For this purpose, new thermal shock testing equipment is developed, which allows heating up the samples on one side to simulate the occurring stress of the real application. So far, the samples have been heated inside a furnace homogeneously and quenched in cold water. Further cooperation in this field was initiated.

The crack propagation energy, which describes how much energy is needed to propagate an initiated crack, is another important parameter to characterize the thermal shock behavior of components. Scientists at Forschungszentrum Jülich used the wedge splitting test to show that kind and amount of pore forming agents as well as their orientation have a great effect on crack propagation inside the sintered lami-






nates. Further studies with specifically graded structures are planned.

The combination of different ceramic shaping technologies and the processing of ceramic green tapes by forming allow the production of sandwich structures nearly without any limitations concerning the possible design geometries. The lamination of formed green tapes with planar green tapes, for example, might be used to produce structures with high volume and low density as well as low heat capacity. A design with defined porosity and porosity gradients is possible as well as the use and combination of different materials adapted to the different requirements like chemical or thermal resistance, mechanical strength or economic aspects. These structures might be used, e.g. as kiln furniture, furnace lining, high-temperature insulation or heat exchanger.

- 1 Longitudinal section of a green tape with graphite platelets.
- **2** Wound and sintered outlet nozzles.
- **3** Cross section of a 7-layer symmetrical, graded component.
- 4 Various demonstrators for alternative applications.




AGING-RESISTANT ZrO₂ CERAMICS MADE OF COMMERCIAL POWDERS

Dipl.-Chem. Martina Johannes, Dipl.-Ing. Jens Schneider


Yttrium stabilized zirconia (Y-TZP) has excellent mechanical properties such as a bending strength of more than 1000 MPa and a fracture strength of up to 8 MPam-1/2. For this reason, Y-TZP has been known as biocompatible material for joint and knee implants for several years. For about ten years, it has mainly been used as material for dental restoration processed with the help of CAD/CAM processes. On account of hydrothermal aging, however, the long-term stability of Y-TZP is influenced. Generally, the aging resistance of Y-TZP can be improved by reducing the grain size and homogeneously distributing the stabilizer (yttrium oxide). From literature it is known that fine-grained, aging-resistant microstructures can be realized by using cost-intensive (nano)powders and complex manufacturing methods. The results described in this article show that dense, finest-particle and aging-resistant zirconia can be reliably produced from commercial submicrometer powders when modern, scalable grinding techniques and grinding media (≥ 50 µm) are used. In order to show the difference, two Y-TZP batches were compared. Batch Z-1 was prepared using a standard method, batch Z-2 using an optimized method. The powders (TZ3Y-SE, Tosoh, Japan) were prepared to slurries using an attrition mill. Then they were shaped by slip casting. The obtained grain sizes for slurry and raw material can be seen in the following diagram. On account of the obtained grinding fineness, the sintering activity was significantly increased for the Z-2 batch.


The relative densities of the sintered or hot isostatically pressed bodies came to more than 99.5 % of the theoretical density of 6.1 gm/cm³. The surface of the samples was polished (Ra 0.01 to 0.008 µm). The samples were hydrothermally treated up to




120 h in an autoclave at 134°C and 2 bar water vapor atmosphere. The phase composition of the aged samples was measured by XRD and quantified by Rietveld refinement. Furthermore, the mean grain size of the microstructure was determined using the linear intercept method: 340 ± 30 nm for Z-1 and 150 ± 30 nm for Z-2.

The diagram below shows the kinetic behavior of the hydrothermal aging process for Z-1 and Z-2. Whereas the Z-1 sample showed a fast increase of the monoclinic phase, no increase was observed for the Z-2 sample. Identical results were obtained for the TZ3Y-S raw material (Tosoh, Japan).







It was proved that the sintering activity of commercial powders can be increased by modern preparation techniques. The ceramics manufactured from these raw materials (TZ3Y-SE, TZ3YS) have a new material quality. So a method was developed, how long-term stable biocompatible ceramic implants can be produced from cost-effective commercial powders. In follow-up studies, the mechanical, optical (transparency) and wear properties of the fine disperse 3Y-TZP ceramics are investigated. Furthermore, it is examined if the results can be transferred to spray granulation and pressing technologies.

Services offered


- Preparation of slurries and dispersion/grinding of the used raw material, e.g. alumina, zirconia and other dispersions
- Adjusting of process parameters in laboratory attrition mills (batches from 800 g to 5 kg) and upscaling to industrial plants (50 kg batches) using grinding balls \geq 50 μ m

microstructure (150 \pm 30 nm).

¹ SEM image of the TZ3Y-SE material.

² SEM image of the Z-1 microstructure (340 ± 30 nm).
3 SEM image of the Z-2





TRANSPARENT MgAl₂O₄ CERAMICS BY AUTOMATED UNIAXIAL PRESSING

Dr. Uwe Reichel, Dipl.-Ing. Henry Ludwig

Motivation


New transparent polycrystalline ceramic materials combine the advantages of advanced ceramics including high fracture toughness, hardness, chemical resistance and reliability with the special optical properties of glasses or single crystals. Using these new materials, the optical application can also be enhanced. In this case, there is the theoretical possibility, for physical reasons, to manufacture materials with outstanding optical properties (e.g. very low/high refractive index or specific spectral properties).

However, the optical principles place high demands on the polycrystalline material. In order to achieve maximum transmission, a defect-free microstructure (no pores, cavities or crystal defects) is necessary. For non-cubic materials, a maximum crystallite size in the sub µm range (smaller than 500 nm up to below 50 nm) is required to suppress birefringence. This, again, places high demands on the quality of the starting materials.


Under the aspect of a cost-effective series production, highpurity and highly disperse commercial raw materials should be used as starting material for the new transparent spinels to be developed (diagram on the right hand side). Polydisperse starting powders are essential for dense, pore-free ceramic microstructures, and thus for transparent ceramics. On the one hand, the materials should have a broader distribution of primary particle diameters below 150 nm, and on the other hand they should be free of coarser particles. In order to adjust the material to the requirements of ceramic shaping techniques, it is necessary to add suitable dispersants as well as binders and compaction aids. Uniaxial pressing was chosen as economic shaping technique. Here, Fraunhofer IKTS has extensive knowledge. Within the framework of this project, the compatibility of the starting materials was to be improved.

Approach

On the basis of a commercially available spinel powder with $d_{\rm 50}$ = 180 nm, SSA = 30 m²/g (BET) and a purity of > 99.95 %, compactable granulates ($d_{\rm 50}$ = 40 μm) were realized by aqueous powder preparation in high-performance attrition mills and spray drying (two-fluid nozzle). By uniaxial pressing with compaction pressures of 200 to 300 MPa and hot isostatic pressing (HIP) that followed at 1600°C/2h under argon atmosphere, transparent spinel ceramics were manufactured.








Results

For the obtained spinel ceramics with a sintering density of > 99.7 % of the theoretical density, transmission values of up to 98 % of the theoretically possible transmission (theoretical maximum transmission according to refractive index is T = 86.9 % – see diagram below) were measured. Thus, it was proved that transparent spinel ceramics can be manufactured by automated uniaxial pressing. In further studies, the mechanical properties of the transparent spinel ceramics are to be characterized.

Services offered

- Development of single-phase and multi-phase oxide ceramic components for optical applications
- Uniaxial pressing of prototypes



Acknowledgments

The presented results are part of a current project (BMWi Reg. Nr. MF090093).

- 1 View through a spinel window.
- **2** Sub-μm spinel starting powder.
- 3 Uniaxial powder press for automated production.
- 4 Microstructure of a transparent spinel.

RESEARCH FIELD ENVIRONMENTAL ENGINEERING AND BIOENERGY

Department head: Dr. Ingolf Voigt

Profil

The research field "Environmental Engineering and Bioenergy" encompasses the development of materials, technologies, and systems for the efficient, safe, economical generation, conversion, transportation, storage, and utilization of energy, especially bioenergy. Technologies and processes are also being developed for water and air purification.

At the core of the research activities are ceramic membranes for liquid filtration, pervaporation, vapor permeation, and gas separation as well as catalysts for exhaust gas purification and wet chemical catalysis. Another focus is on high-performance batteries and accumulators for buffering energy peaks from renewable energy sources. Powerful process technologies for comminution and disintegration of biogenic substrates as well as membrane modules and systems for substance separation and reaction are also being developed. The integration of these technologies into existing technologies (e.g., for biogas and bioalcohol generation) results in a significant increase in efficiency and offers new approaches for process development.

For environmental protection and resource conservation, innovative solutions for substitution or economical use of chemical additives are designed and efficient technologies for recovery and reuse of resources developed.

Services offered

The services we offer range from development, optimization, and planning to scientific support in the installation of facilities and transfer to continuous industrial operation. Innovative treatment technologies and extensive know-how in ultrasonic treatment, biological catalysis, and fermentation are used to enable highly efficient use of natural raw materials and biogenic waste materials.

- Situation and systems analysis at customer site and in laboratory
- Innovative process development and specification for biomass treatment
- Determination of gas potential of biogenic substrates
- Optimization of reaction kinetics for anaerobic breakdown processes
- Processes for wastewater purification and water treatment in municipal and industrial plants
- Ultrasonic application for degassing and disintegration
- Energy optimization of stirring processes
- Membrane development and testing
- Application and piloting of membrane processes
- Catalyst development and testing
- Supply of samples of ceramic membranes and catalysts for pilot and demonstration systems
- Membrane system development and prototype manufacture
- Engineering of biogas plants using new, innovative process steps
- Development of batteries and accumulators for stationary energy storage
- Provision of expert opinions and reports





Department head
Dr. Ingolf Voigt
Phone +49 36601 9301-2618
ingolf.voigt@ikts.fraunhofer.de



Water Technology
Dr. Burkhardt Faßauer
Phone +49 351 2553-7667
burkhardt.fassauer@
ikts.fraunhofer.de



Nanoporous Membranes
Dr. Hannes Richter
Phone +49 36601 9301-1866
hannes.richter@ikts.fraunhofer.de



Bioenergy
Dr. Eberhard Friedrich
Phone +49 351 2553-7826
eberhard.friedrich@
ikts.fraunhofer.de



Membrane Process Technology and Modeling Dr. Marcus Weyd Phone +49 36601 9301-3937 marcus.weyd@ikts.fraunhofer.de



Mixed Conductors and Catalysis
Dr. Ralf Kriegel
Phone +49 36601 9301-4870
ralf.kriegel@ikts.fraunhofer.de





CNT FILMS FOR MEMBRANE SEPARATION AND CATALYSIS

Dipl.-Ing. (FH) Susanne Kämnitz, Dr. Hannes Richter


Hydrogen plays an increasing role as an energy source in the further expansion of renewable energies and their way to become profitable. In order to use hydrogen for automotive, industry and household applications efficiently, special separation processes and storage materials that achieve a storage capacity of 6.5 weight percent of hydrogen, are required. Zeolites and metal hydrides have already met these targets but the high desorption temperature and slow desorption rates have limited the range of applications so far. Carbon nanotubes (CNTs) are discussed as another high potential class of materials. Their use is currently focused on electrode materials for energy storage and the production of electrically conductive composites.


Fraunhofer IKTS developed a CVD system which allows to produce thin CNT films on the inner surface of porous ceramic tubes with different tube diameters and lengths. The deposition of the CNT films can be made from various liquid or gaseous carbon precursors. The reaction steps during the CVD processes can be analyzed directly by coupled analysis methods like IR spectroscopy and gas chromatography.

Catalyzed supports, e.g. alumina, were used for CNT deposition. The growth behavior of the deposited CNT films can be influenced by the specific selection of the catalysts, the supports and the carbon precursors. The catalytic decomposition of the carbon precursor shifted with increasing catalyst content to lower temperatures and higher CNT yield.

Uniform CNT films with thicknesses < 5 microns were deposited on porous, ceramic supports. Depending on the

process parameters, oriented or unoriented CNTs with average tube diameters < 200 nm were prepared. The tube ends of the deposited CNTs were frequently closed with metal particles or carbon caps. In the gas permeation measurements, the CNT layers showed adsorption-selective gas separation properties. Single gas permeance and permselectivities were changed by varying the catalyst. An increase of the permeance and $\rm H_2/CO_2$ permselectivity was found with increasing catalyst concentration and therefore increasing CNT yield. The rise in $\rm H_2$ permeance is explained by adsorption and capillary effects on the surface of the nanoscale tube geometry. By adsorption measurements, the adsorption of hydrogen in the CNT films was detected.







Application

The presented CNT films show high potential for the separation of gases with different molecular sizes, such as the separation of H₂ and CO₂. Furthermore, it should be possible to use these CNT films for the separation of gases with similar molecular sizes but different adsorption, such as paraffin/olefin separation. Because of their special properties, carbon nanotubes are of growing interest for future application fields, such as the provision of fuels. In addition to membrane applications, CNT layers might be used as an ideal material for the storage of gases and as a microreactor in catalytic processes.

- Deposition of CNT films on porous, ceramic tubes and flat discs
- Optimization and further development of CNT films for applications in membrane separation, gas storage and catalysis
- Combination of membrane separation and catalytic conversion (membrane reactor)
- Customer-specific tests
- Stability tests



- **1** CVD system at Fraunhofer IKTS Hermsdorf.
- **2** Porous, ceramic support before and after CNT deposition.
- **3** FESEM image of a deposited CNT film and HRTEM image of a closed CNT.
- **4** FESEM image with aligned CNTs.






HYDROTHERMALLY STABLE ZEOLITE MEMBRANES FOR H₂ SEPARATION

Dipl.-Chem. Christiane Günther, Dr. Hannes Richter

According to a study of the International Energy Agency the global electrical energy demand will increase by the factor of two in the next twenty years. The main energy source will remain fossil fuels (coal, oil and natural gas), which actually produce about 60% of the energy in Germany. In 2050, about 70 % of the global energy will be produced from fossil fuels. Therefore, the emissions of greenhouse gases like CO₂ will also continue to increase. Currently, about one third of the global CO₂ emmissions are produced by power plants. To decrease the CO₂ emmissions of future power plants the coal can be gasified to H₂ and CO₂ before combustion (IGCC) and subsequently the hydrogen separated from CO₂. The hydrogen can be burned in a gas turbine and the produced water steam is driving a steam turbine. In addition to the reduced CO₂ emission, the efficiency increases in comparison to conventional fossil power plants.


To decrease the very high efficiency losses of gas separation with conventional methods like gas scrubbing or adsorption, nanoporous membranes can be used for $\rm H_2$ and $\rm CO_2$ separation. This separation has to be carried out directly after the water gas shift reaction (sweet shift, 350°C, 25 bar, 25 % $\rm H_2O$) setting high requirements in terms of membrane stability.

Zeolites are crystalline tectosilicates with defined nanopores. Deposited as a thin layer on top of porous substrates, comparatively cheap, thermal and hydrothermally stable membranes of high selectivity should be obtained. Sodalite (SOD) exhibits pore sizes in the range of the molecule diameter of hydrogen. Therefore, sodalite membranes are promising candidates for H_2/CO_2 separation.



First, different sodalite powders were synthesized and their hydrothermal behavior was tested. The classical easy-to-synthesize hydroxosodalite (H-SOD) was not hydrothermally stable. The Si-SOD without alumina shows excellent stabilities but could not be synthesized as a crack free membrane. Therefore, a new method was developed to stabilize the H-SOD by intercalation of sulfur into the crystal framework. The S-SOD synthesized by this method exhibits excellent thermal and hydrothermal stability and allowed the preparation of crack free membranes for the first time (figure 1).






The zeolite membranes were synthesized on the inside of asymmetric, tubular, porous, ceramic substrates (I = 250 mm). Substrates of different supporting top layers made of α -Al₂O₃ and γ -Al₂O₃ with different pore sizes were tested. The supports were seeded with zeolite powder (slurry seeding) or zeolite nanoseeds (figure 2). Under hydrothermal conditions in autoclaves the seeds grow into closed layers (figure 3).

First optimizations of seeding and synthesis led to properly intergrown layers with a thickness in the range of a few micrometers and without impurities (figure 4). By single gas permeation a 14 times higher permeation of hydrogen in comparison to CO_2 was measured. So, a thermally and hydrothermally stable membrane for a size selective separation (molsieving effect) of a H_2/CO_2 mixture was prepared for the first time. It is the objective of ongoing research to reduce the membrane defects (permeation of big molecules) still existing and to increase the H_2 permeance. That is essential for an industrial application of the new zeolite membranes.


Acknowledgments

Financial support from the Helmholtz Association of German Research Centres (Initiative and Networking Fund) through the Helmholtz Alliance MEM-BRAIN is gratefully acknowledged.

- Development of membranes for separation of customerspecific gas mixtures
- Separation tests for membranes (single and mixed gas measurements, vapors and liquids) according to customer requirements and under consideration of technical possibilities



- 1 SEM image of S-SOD powder.
- 2 Seeding of a membrane.
- 3 Hydrothermal synthesis in autoclaves.
- **4** SEM image of the cross section of an S-SOD membrane.



DESIGN AND PREPARATION OF MEMBRANE COMPONENTS FOR OXYGEN PRODUCTION

Dr. Ralf Kriegel, Dr. Matthias Schulz

Oxygen permeable ceramic membranes

By using oxygen for combustion processes it is possible to save primary energy and to reduce CO_2 emissions. The combustion with pure oxygen ("oxyfuel") makes it easy to separate CO_2 . Oxygen separation with the help of mixed conducting ceramic membranes at high temperature is a promising alternative to cryogenic air distillation and pressure swing adsorption because of its lower energy demand. However, for transferring this technology to industry applications, it is necessary to reduce the membrane costs significantly and thus to further develop the single channel membrane tubes available at Fraunhofer IKTS (figure 1).


Increase of oxygen permeation

An increase of O_2 permeation results in a reduction of capital costs as well as in smaller reaction chambers. At given operational conditions (e. g. for O_2 production using vacuum) and with suitable membrane materials, O_2 permeation can be realized by minimizing the membrane thickness (figure 2) and/or by maximizing the membrane surface building up complex membrane components (figure 3). In both cases, a minimal critical leakage rate must be ensured by an error-free coating process and by a gas-tight joining of single parts. The diagram at the lower left corner of page 45 shows the O_2 flux experimentally determined as well as the O_2 flux normalized to the membrane area for different BSCF membranes (Ba $_{0.5}$ Sr $_{0.5}$ Co $_{0.8}$ Fe $_{0.2}$ O $_{3.8}$). Highest flux is observed for an asymmetric membrane tube, but thin-walled capillaries also provide

higher fluxes than a monolithic membrane tube with 1.5 mm membrane thickness. The weakening of the flux curve at higher driving forces is caused by pressure drops inside the evacuated capillary. This seems to be uncritical since an energy-efficient operation is limited to driving forces below 1 in most cases.


Evaluation of mechanical stress


Oxygen production driven by pressure differences between feed and permeate is always entailed by mechanical stress but only the maximal level of tensile stress is critical for ceramics. Tensile stress in tubular membranes with overpressure at the outside only occurs if the roundness varies. Flat membranes, however, are always under tensile stress. The maximal tensile stress grows for flat membranes with increasing distance of the supporting props. Correspondingly, a channel width of 1 mm seems to be critical. Additionally, chemical stress is induced by crystal lattice expansion increasing with decreasing oxygen partial pressure. In general, chemical stress dominates the whole stress situation. The diagram on the right shows the oxygen stoichiometry at the membrane surfaces and the calculated maximum tensile stress for tubular and flat membranes in dependence of the feed pressure. Also in this case, tubular membranes obviously show significant lower tensile stresses. So, a longer life-time can be expected.



Economic efficiency and realization


In order to evaluate the economic efficiency of the different membrane components, the costs for the production of 10,000 m² membrane surface, the O_2 flux as well as the size of the reaction chamber were calculated for the determined operating conditions. More than 50 % of the total costs were caused by the raw material for this preliminary stage of a series production. According to that, significant economic advantages were obtained for capillary bunches because of the reduced material quantities. Assuming an operating life time of five years, the total production costs were related to the amount of oxygen produced per year. In this case, capital costs of $7 \notin I O_2$ were obtained for the capillary bunches, $50 \notin I O_2$ for single channel membrane tubes, and $30 \notin I O_2$ for planar stacks. Because of the versatile advantages of capillary bunches or multichannel tubes ceramic parts were prepared





(figure 4). In addition, machining and joining procedures were developed (figure 5) and first membrane components (figure 6) were realized. The $\rm O_2$ permeation of the capillary bunches experimentally determined agrees well with the prediction.

- **1** Extrusion of single channel membrane tubes.
- **2** Cross section of an asymmetric BSCF membrane.
- 3 CAD draft: stack of planar cells, capillary bunch.
- 4 Tubes, capillaries, capillary bunch, supply tube.
- 5 Structure of membrane components.
- 6 Bunch made of seven capillaries with supply tube.





CONCENTRATION OF ALCOHOLS USING HYDROPHOBIC MEMBRANES

Dr. Marcus Weyd, Dr. Hannes Richter, Dipl-Ing. Oliver Tröber


Alcohols derived by fermentation of renewables are an important alternative and supplement to fossil fuels. The carbon dioxide released during the fermentation process and the use of the alcohol was bond during the growth of the plant. Besides ethanol, which is used as additive to fuels, butanol is of rising interest in the field of fuels because its properties better come together with established fuels and their infrastructure. Butanol has a higher caloric value as compared to ethanol and is miscible with gasoline in any proportion. Furthermore, it is the only biofuel that can be added to kerosene. It is a drawback of butanol fermentation that the concentration which can be achieved by fermentation is much lower as compared to ethanol fermentation. Optimized production processes are important for an ecological and economical application of these alternative fuels.


The concentration and dewatering of alcohols, in particular, are energy consuming and cost intensive. For this application, nanoporous membranes are an interesting alternative to conventional separation processes. At Fraunhofer IKTS, ceramic membranes for the efficient dewatering of solvents (e.g. ethanol) above the azeotropic composition were developed. These membranes are applied in ethanol dewatering on industrial scale.

Membranes that are capable to selectively extract alcohols from aqueous solution by pervaporation are in the focus of current research. This process works at the fermentation temperature in order to recycle the retained components of fermentation and to save thermal energy as compared to conventional distillation.

This process is of special interest when only low concentrations of alcohols are obtained by fermentation, so for example in the production of second generation biofuels and butanol.

The enrichment of alcohols from fermentation is very demanding in terms of membrane performance. So, the alcohol molecules are bigger than the water molecules that means a "sieving on a microscopic level" is not possible. Furthermore, the multi-component mixture of the fermentation broth leads to a high risk of membrane fouling. For this reason, Fraunhofer IKTS pursues two strategies: the development of pure inorganic zeolite membranes as well as the development of mixed matrix membranes where zeolite particles are embedded into a polymeric matrix.








Both membrane configurations have specific advantages. So, inorganic zeolite membranes show higher fluxes and selectivities, and have a tubular shape with optimal fluid properties. With mixed matrix membranes large specific membrane areas can be realized. Additionally, their production is more costefficient. The zeolite membranes can be coated with additional layers in order to improve anti-fouling properties. In comparison, the properties of the mixed matrix membrane surface can be influenced by the selection of the polymer.

Pervaporation tests with binary mixtures were performed. At a feed temperature of 40°C the developed zeolite membranes showed permeate fluxes of about 0.8 kg/(m²h) and highest selectivities. So, 80 % ethanol can be extracted from a feed mixture of 5 % ethanol within one membrane step. Using mixed matrix membranes, up to 55 % ethanol was achieved. In case of butanol, 45 % butanol was extracted within one membrane step from an aqueous mixture of only 1.4 % butanol. The zeolite membranes as well as the mixed matrix membranes are suited to enrich alcohols from low concentrated mixtures even at low temperatures.

Acknowledgments

The Federal Ministry of Food, Agriculture and Consumer Protection, the Federal Ministry of Economics and Technology (22006508 and MF090032) as well as GFT Membrane Systems GmbH are gratefully acknowledged for their financial support.

- Customer-specific testing of membranes
- Application-oriented membrane development
- Engineering, construction and equipment of membrane (test) plants
- Supply of membrane prototypes



- **1** Cross section of a zeolite membrane (SEM).
- **2** Ceramic supporting tubes for zeolite membranes.
- 3 Cross section of a mixed matrix membrane (SEM).
- **4** Coating of mixed matrix membranes on pilot scale.



BIOENERGY APPLICATION CENTER PÖHL

Dr. Eberhard Friedrich, Dr. Karin Jobst, Dipl.-Ing. André Wufka

The operation and construction of biogas plants have to meet increasing demands to stabilize and strengthen their position among future energy supply systems. Taking substrates and residues into account that have not been economically usable so far, can help to reduce the competition in biomass supply. Furthermore, it is the aim of current developments to additionally reduce the greenhouse gas potential. This includes the steady increase of efficiency of the biogas technology, an increase of the utilization rates of the substrates, the reliability and availability of equipment, and the improvement of process stability by adapted process control. New reactor designs and better materials as well as adapted energy-efficient stirring systems allow for a significant improvement of biogas technology.

Within this context, Fraunhofer IKTS is working successfully in several joint projects together with regional SMEs. These projects are funded by the EU, the Free State of Saxony, the Federal Ministry for the Environment, Nature Conservation and Nuclear Safety (BMU) as well as the Federal Ministry of Education and Research (BMBF). The results of these projects are ready for testing on pilot scale. For this purpose, Fraunhofer IKTS founded the Bioenergy Application Center Pöhl at the beginning of 2011. It is located near the demonstration biogas plant (500 kW) of LEHMANN Maschinenbau GmbH.

With the establishment of the Bioenergy Application Center, Fraunhofer IKTS is able to run its fully automated pilot biogas plant for process and product testing. This is combined with extensive experiences and comprehensive skills of LEHMANN Maschinenbau GmbH in the field of design and manufacture

of equipment and systems for biogas technology. Thus, the chain from research and development to design and manufacture was closed. With the retransfer of knowledge from large-scale long-term processes, new ideas and projects can be created for the benefit of our customers.

Technical equipment

Equipment in the Bioenergy Application Center under the responsibility of Fraunhofer IKTS:

- Container for substrate pretreatment (technical equipment for deconservation as well as a twin-screw extruder incl. measurement and control technology)
- 3-stage pilot biogas plant (hydrolysis, two fermenters each 5 m³)
- Two fermenters incl. stirring systems (each 1 m³) for evaluation of mixing processes
- Reactors for gas purification and desulphurization
- Ultrasonic reactor for degasification of digestate
- Planned: biotechnical laboratory incl. analytics as well as membrane technology for accumulation of methane in the biogas


Priority tasks

The Bioenergy Application Center offers best conditions to demonstrate the mechanisms and opertional results in the direct application. Recent R&D results are annually presented on conferences on site. The organization of thematic trainings for






Developed reactor for degasification of digestate from biogas plants by means of high-power ultrasound



Designed and produced multi-stage substrate pretreatment system based on the developed DECONDIS® method



planners of biogas plants, institutions and specialized agencies are also carried out. In the same context national and international conferences are planned at Fraunhofer IKTS. The Bioenergy Application Center offers best prospects for qualification of young scientists and engineers in the field of future technologies. On the one hand, young academics are promoted and on the other hand new jobs are created.

- Analysis and evaluation of gas and tail gas potentials of substrates and biogenic residues as well as nutrient and trace elements application in digestion processes
- Design of digestion processes including regional substrate sources as well as special solutions; proof of profitability
- Cooperation and support for design, implementation and approval of plants and systems
- Technical and scientific monitoring of increased performance of installed biogas plants
- Development and implementation of special solutions in the field of gas purification and digester effluent treatment

- 1 Pilot biogas plant.
- 2 Demonstration plant of 500 kW.
- 3 Wheat straw agricultural residue with high energy potential.
- 4 Wheat straw different states of particle size reduction.

RESEARCH FIELD SINTERING AND CHARACTERIZATION

Department head:
Dr. habil. Mathias Herrmann

Profile

Extensive sintering and analysis know-how in this research field is concentrated at both the Hermsdorf and the Dresden location. With diverse characterization methods, thermodynamic and kinetic modeling, and extensive furnace equipment from the laboratory to the pilot scale as a basis, targeted development of materials, components, and processes is possible.

Existing methods range from particle and suspension characterization and ceramographic sample preparation using conventional and ion beam-based techniques to quantitative phase and microstructural analysis. In addition, a wide range of thermoanalytical and thermophysical characterization techniques and methods for tribological, mechanical, and electrical characterization are available. Mastery of these sophisticated analytical methods is coupled to detailed process know-how as well as materials and scientific knowledge, enabling well-founded interpretation of results.

We also test electrical devices and equipment in accordance with national and international standards as well as customer-specific requirements and possess a wide range of possibilities for environmental simulation and calibration of measurement systems.

Services offered

Development projects and individual contracts for characterization of powder metallurgical and ceramic feedstocks and materials as well as for heat treatment of materials and components:

- Particle characterization from micro- to nanoscale
- Application-specific suspension characterization for all concentrations
- Determination of thermoanalytical and thermophysical characteristics
- Investigation of sintering behavior of materials and components
- Design, execution, and optimization of heat treatments, including scale-up to industrial scale
- Characterization of materials and components in terms of microstructure, phase composition, and mechanical and tribological properties
- Testing of electrical devices and equipment (CE and GS marks, in cooperation with TÜV and VDE)
- Simulation of environmental effects (temperature, climate, mechanical loads, corrosion)
- Component failure analysis and consulting on use of ceramic materials
- Calibration of measuring devices (length, temperature, electrical measurement parameters)
- Consulting on quality and environmental management systems





Department head

Ceramography and Phase Analysis Dr. habil. Mathias Herrmann Phone +49 351 2553-7527 mathias.herrmann@ ikts.fraunhofer.de



Thermal Analysis and
Thermal Physics
Dr. Tim Gestrich
Phone +49 351 2553-7814
tim.gestrich@ikts.fraunhofer.de



Quality Assurance Laboratory and Mechanics Laboratory Dipl.-Ing. Roy Torke Phone +49 36601 9301-1918 roy.torke@ikts.fraunhofer.de




Heat Treatment
Dipl.-Ing. Gert Himpel
Phone +49 351 2553-7613
gert.himpel@ikts.fraunhofer.de



Chemical and Structural Analysis Dipl.-Phys. Jochen Mürbe Phone +49 36601 9301-4946 jochen.muerbe@ ikts.fraunhofer.de



Powder and Suspension Characterization Dr. Annegret Potthoff Phone +49 351 2553-7761 annegret.potthoff@ ikts.fraunhofer.de



SUPERHARD SIC-DIAMOND CERAMICS

Dr. habil. Mathias Herrmann, Dipl.-Ing. Björn Matthey


Diamond coatings or polycrystalline diamond (PCD) materials are used in cutting materials, rock drills, sensor windows, and other applications in which high hardness and chemical resistance are paramount. However, their use is limited by the high cost and size restrictions associated with the high-pressure process needed to produce them. CVD diamond coatings for ceramics were recently developed for mechanical seals in cooperation with Fraunhofer IKTS (DiaCer®) [1] and successfully introduced to the market as Diamondfaces® by EagleBurgmann Germany GmbH & Co. KG [2]. These materials also have drawbacks, namely, the lengthiness of the coating process (> 10 to 20 h) and restrictions on geometry and service life. In addition, CVD diamond coatings quickly reach their limits in abrasive loading conditions (e.g., sandblasting) and applications in which wear of more than several hundreds of microns or millimeters is tolerable.


Hence, alternatives are currently being sought with the most promising one being SiC-bonded diamond. This material contains approx. 90 % diamond and is produced commercially in high-pressure processes for drill bits [3, 4] at a comparable cost to that of traditional PCD materials or with lower diamond content and diamond grain sizes ≥ 10 µm at ambient pressure. At Fraunhofer IKTS, a fundamentally new solution for cost-effective production of diamond materials has been developed [5]. The diamond-SiC material is based on a graded composite with a SiSiC substrate and a 1- to 3-mm-thick SiC-bonded diamond coating (with a diamond content of 30 to 50 vol %) as a wear surface. The diamond particles are bonded to the SiC matrix through infiltration of the graded substrate material formed from SiC and diamond powder with silicon.

The silicon reacts with the diamond and the binder used for shaping to form SiC with no change in component dimensions, thus enabling high diamond contents and a strong bond between the diamond particles and the matrix. Grading of the materials allows for a reduction in raw material and production costs. Use of diamonds with grain sizes of less than 5 to 10 µm yields completely new possibilities for material design.

Current work is focused on developing the technology for materials production and microstructural formation [6] as well as investigating the tribological behavior (interactions with metals and simulation of wear in drawing processes) in collaboration with Fraunhofer IWM in Freiburg. This work also comprises development of methods for microstructural imaging of these superhard materials and quantification of the phases and stresses to form a basis for understanding the relationships between microstructure and properties. The pronounced effect of the graphite layer thickness at the diamond-SiC interface on the hardness and wear properties is illustrated in the diagram on the right. With appropriate adaptation of the production parameters, the graphite layer thickness can be controlled and materials with hardness levels of greater than 47 GPa can be reproducibly produced.

For the investigation of the microstructure new preparation methods had to be developed due to the high wear resistance. These methods can also be used for other materials which are difficult to polish like cBN or PCD materials. They allow a detailed analysis of the interface between the hard component and the matrix or binder.







Even if cost-effectiveness and diamonds seem to be mutually exclusive, the low current price of diamond powders (less than 1€/g), the availability of an effective production technology, and a service life ten times higher than that of conventional ceramic- or hard metal-based solutions enable cost-effective production of components based on these materials. Interested industry partners are invited to participate in the upcoming preliminary testing of samples and prototypes in application conditions.


References

- [1] www.fraunhofer.de/ueber-fraunhofer/wissenschaftlicheexzellenz/fraunhofer-wissenschaftspreise/Preis-Stifterverband
- [2] www.eagleburgmann.com
- [3] P. N. Tomlinson, et al., IDR., 6, (1985)299-304
- [4] ScD Werbeblatt elementsix (2010)
- [5] M. Herrmann, H. P. Martin, DE 10 2007063517 B3
- [6] M. Herrmann, B. Matthey, S. Höhn, I. Kinski et al. Diamond-ceramics composites – New materials for a wide range of challenging applications; J. Europ. Ceram. Soc. (online verfügbar)



- 1 Microstructure of SiC-diamond ceramics (dark diamond, grey SiC).
- **2** Schematic of material formation.
 - A Preform with starting silicon infiltration.
 - B Structure of diamond layer after infiltration.
- **3** *Microstructure of material compound.*






WAFER CUTTING, ABRASIVE FLOW MACHIN-ING – ABRASIVE PARTICLES IN SUSPENSIONS

Dr. Annegret Potthoff, Dipl.-Ing. Sören Höhn

For the accurate and energy-efficient finishing of high-performance elements, technologies such as abrasive flow machining or water jet cutting are used. Silicon wafers as essential components of semiconductor and photovoltaic industries are cut from silicon ingots using wire saws. The efficiency of all these processes is mainly determined by the properties of the used suspensions.


Silicon or boron carbides are commonly used as abrasive particles in grinding or sawing suspensions. The original particle sizes range from below 5 μ m up to 500 μ m. Whereas the size can be defined by sampling of raw materials, surface texture and particle shape are determined by the manufacturing process, and thus, their adjustment is limited. All parameters




have in common that they vary during the finishing process. Therefore, relevant particle properties have to be ideally determined by offline and online analysis.

For the analysis of particle shapes, an image evaluation method was developed. Using this method, differences which cannot be recognized visually but are potentially relevant for the application can be reliably detected (figures 1 and 2). The processing steps of "embedding of sample – sample preparation by grinding and polishing – ion-beam preparation with edge sharpness – image acquisition with high resolution – detection of particles by gray-scale analysis – quantification of particles using software for image evaluation" are tools to analyze particles of all sizes (figures 3 and 4). It can be proved by measurements that particles which have been subjected to mechanical stress and recycled afterwards differ in particle shape parameters according to ISO/DIS 9276-6 such as circularity or aspect ratio.

The static image analysis provides the advantage of a very good sensitivity but the efforts for sample preparation are very high. In contrast, the dynamic image analysis is characterized by easy sample preparation and very good statistics, i.e. a large quantity of particles can be analyzed in short measurement times. Measurement systems which can also partly be used online are avaiable for coarser particles. In order to realize the analysis of finer materials (e.g. F800 grain size after application) further research and development is needed. The properties of SiC or B₄C particles in the suspension fluid during the application significantly determine the efficiency of the process. Therefore, this aspect is also subject of current re-





search. Conclusions about the electrostatic stability and thus the agglomeration behavior of particles in fluids can be drawn from the results of surface charge measurements. Reactions at particle surfaces which are induced due to contaminations during the process or due to the (partial) formation of an oxide layer can be detected indirectly. The flow behavior of the suspension is not only determined by solid concentration and temperature but also by steric effects which can be caused, for example, by the formation of amorphous oxide compounds.

The complex characterization of particles, dissolved materials and fluids (water, organic solvents) in suspensions establishes new possibilities for the optimization of various processes such as wafer cutting, abrasive flow machining or water jet cutting. The results provide a basis for particle-based simulations. It is the aim of the joint project "AbraSus" of Fraunhofer IWM, IKTS and IPK to better understand processes by combining experimental methods and multiscale modeling.

- Application-specific evaluation of (abrasive) particles
- Characterization of particle shapes in the nanometer and millimeter range
- Analysis of particle properties in aqueous and organic suspensions by surface charge measurements, sedimentation analysis and rheological measurements

- 1 Original SiC particle.
- 2 Recycled SiC particle.
- 3 SiC sample after preparation.
- **4** Classification of particles according to a particle shape parameter.

RESEARCH FIELD ENERGY SYSTEMS

Department heads:

Dr. Mihails Kusnezoff

Dr. Matthias Jahn

Dr. Christian Wunderlich

DEPARTMENT

MATERIALS AND COMPONENTS

Profile

The "Materials and Components" department is involved in the development and preparation of functional ceramic materials and their application in functional elements. Traditional fields are thick film technology, glass development, high-temperature fuel cells (SOFCs), and high-temperature chemical sensors. Extensive experience and outstanding technical equipment allow complex requirements and interactions in sophisticated applications such as fuel cells, lithium ion batteries and supercaps, sensors, microsystems, and packaging in complex materials systems to be controlled. At the Dresden institute branch, screen printing pastes, inks, and slurries are developed to be used in electrochemical components and microsystems.

Materials development in combination with different coating methods – especially for applications in electrochemistry and joining technology – form the basis for the development of new components (SOFC/SOEC, thermoelectric generators, sensors).

Close meshing with the "Modules and Systems" and "Industrialization Systems" departments ensures the practical relevance of the results. This allows us to give our customers attractive offers for materials, prototypes, and services along the entire process chain.

- Development and preparation of pastes for screen printing, dispensing and roll coating as well as their pilot plant production
- Development and preparation of nanoinks for ink-jet and aerosol jet printing
- Development and preparation of sealing glasses and elements as well as solders
- Glass development for specific applications
- Development of electrode materials and coatings for lithium ion batteries and supercaps
- Testing and inspection capacity for materials and functional high-temperature components for gas sensors, SOFC/SOEC and thermoelectric generators
- Development, manufacture, and testing of SOFC stacks
- Packaging for ceramic systems
- Consulting and materials analysis





Department head Materials and Components

Dr. Mihails Kusnezoff Phone +49 351 2553-7707 mihails.kusnezoff@ ikts.fraunhofer.de



Joining Technology
Dr. Jochen Schilm
Phone +49 351 2553-7824
jochen.schilm@ikts.fraunhofer.de



High Temperature Electrochemistry and Catalysis Dr. Nikolai Trofimenko Phone +49 351 2553-7787 nikolai.trofimenko@ ikts.fraunhofer.de



Ceramic Energy Converters
Dr. Stefan Megel
Phone +49 351 2553-7505
stefan.megel@ikts.fraunhofer.de



CFY STACKS: TECHNOLOGY FOR ROBUST SYSTEMS

Dr. Stefan Megel, Dr. Mihails Kusnezoff


By means of long-term stable and robust solid oxide fuel cell stacks (SOFC), stationary power supply systems can be built up in modular design and controlled with minimum sensing. Planar SOFC stacks are characterized by high energy density and high electric efficiency. Using electrolyte supported cells made from fully stabilized zirconium dioxide (10ScSZ), power densities > 500 mW/cm² can be reached. On account of the thermomechanical properties of these cells, the high performance potential can only be used in stacks with CFY interconnects (Cr5Fe1Y material of Plansee SE).


The newly developed MK351 stack design consists of only a few component parts and allows for a simple and automated assembly (diagram on the right). The stack is built up from components which are either commercially available or produced in pilot scale and supplied by industry partners. The interconnects having dimensions of 130 x 150 mm are the largest interconnects that are currently manufactured by a powder metallurgical route worldwide. Within the framework of a joint development program, Plansee SE supplies these interconnects with an integrated protection layer. In collaboration with SCHOTT Electronic Packaging GmbH, the glasses for stack production are developed. The quality specifications of the part components (cells, interconnects, glass sealings) which are essential and important for stack production are determined at Fraunhofer IKTS. The tolerance chain suitably selected for all stack components guarantees for high yield, even for manual production. All stack components withstand high temperatures, temperature cycling and repeated oxidation and subsequent reduction at the gas side (redox test) under relevant operating conditions. Different studies at test samples are

performed to support materials development for protective and contact layers as well as glass sealings. Joining is one main aspect of stack manufacture. For this reason, a joining apparatus was developed where joining and activation process as well as quality control of the stacks (figure 3) are automated.

The produced stacks are integrated in hot boxes for lifetime tests and thermal cycling so that simple interfaces and standardized practice-relevant testing procedures for system integration can be established. Currently, the performance degradation of a 30-cell stack (performance > 800 W) integrated in a hot box is < 1.5%/1000 h.

Performance degradation in stacks is caused by different effects: (i) formation of an oxide layer on the cathode side of the interconnect, (ii) degradation of cell performance, (iii) defects





in cell or glass sealing, and (iv) reduction of contact surfaces between cell and bipolar plate. At low absolute stack resistances in particular, small degradation effects become visible. The degradation aspect is studied within the framework of a comprehensive research program including material tests, analysis of stack failure and effects of operational conditions. Long-term degradation is to be reduced by newly developed protective layers in the future.

Stability against cyclic loading (thermal and redox cycles), in particular, is a challenge for solid oxide fuel cells. The use of a stable ceramic substrate and a thin anode layer makes it possible that the stack withstands air flush to the fuel side without total failure although nickel is oxidized in the anode. Thus, the stacks can be heated up and cooled for several times without feeding protective gases. A minimum performance loss of < 1 % was measured after 20 thermal cycles without gas supply. By studying the thermal cycles and the varying reduction and oxidation of the anode (redox test), the degradation can be referred to the change in the anode and its bonding, and degradation could be reduced.

A CFY stack with 30 cells was successfully integrated into a system developed at Fraunhofer IKTS for converting biogas into electricity. Together with partners from Plansee SE, AVL List GmbH, SCHOTT Electronic Packaging GmbH and Forschungszentrum Jülich a demonstration system with an electric power of > 5000 W is under development based on this stack design. The system is powered with natural gas and has an electrical efficiency of > 50 % (figure 4). This prototype is to pave the way to large SOFC systems.

- Testing of SOFC stack components: determination of suitability and durability under real SOFC operating conditions
- Stack integration into modules
- Supply of SOFC stacks or stack modules in the power range between 0.5 to 10 $\ensuremath{\mathrm{kW_{al}}}$

- 1 Assembly of a 30-cell stack.
- 2 Joined 30-cell stack.
- 3 Joining apparatus.
- 4 Stack module made of eight 30-cell stacks.



SCALEABLE ELECTRODE MANUFACTURING TECHNOLOGY FOR SUPERCAPS


Dr. Marco Fritsch, Dr. Mihails Kusnezoff, Dr. Michael Schneider, M. Sc. Mathias Weiser

Electrical energy storage systems play a crucial role in future energy supply concepts. Supercaps comprise a group of high-performance capacitors such as electric double layer capacitor (EDLC), pseudo capacitor or hybrid capacitor. They are characterized by high power densities, short charge and discharge times and a high cycle life. In combination with lithium ion batteries, there are many interesting applications for mobile and stationary self-sustaining energy storage systems. In order to realize a change in energy policy and the predicted goals of electric mobility, scalable manufacturing technologies for components of supercaps are required.

Common EDLC supercaps store electric energy (capacitance) by forming an electric double layer on the surface of microporous carbons. The production technologies for such activated carbon powders are well advanced worldwide. At Fraunhofer IKTS, functional powders are processed to thin electrode films using material scientific and manufacturing approaches. Ceramic technologies are decisive for the dispersion of powders, preparation of casting slurries and coating of the electrodes in a continuous tape casting process. It is important that the so fabricated electrode film can be passed as a roll on downstream manufacturing processes like calendering or winding of electrode and separator.


The attainable storage capacity and the internal resistance of such a capacitor depend significantly on the electrode microstructure. The electrical contact between the activated carbon powders is of great importance. By integrating conductive nanoparticle powders like carbon black or carbon nanotubes (MWCNT) it was shown that the gravimetric capacity can be

increased. The conductive powder shows negligible self-capacitance, but rather electrically isolated regions will be avoided in the electrode microstructure.



For CNT containing electrodes a dispersion procedure was developed which separates the nanotubes in the casting slurry and leads to a homogeneous electrode film after the casting process. The coating was applied on both sides of an aluminum collector tape. After densification of the electrodes by calendering, electrochemical tests were performed with Swagelok cells as well as with wound capacitors of 100 farad to evaluate the performance. The time-dependent charge and





discharge behavior was significantly improved by integrating carbon nanotubes in the electrode microstructure. This was also proved with the help of increased sheet conductivities and a negligible internal resistance of the electrode film in the supercap.

The supercap development attaches importance to the use of environmental and health friendly materials. With substantial market penetration of such supercaps questions of safety, disposal and recycling will come to the fore. For this reason, Fraunhofer IKTS evaluates the use of propylene carbonate instead of acetonitrile based electrolytes. Propylene carbonate electrolytes show significantly higher temperature stability but lower intrinsic conductivity. This leads to an increase of the internal supercap resistance, which can be reduced by using thin separators. In this case, however, high demands on the surface quality of the prepared electrode film must be met as short circuits due to a penetration of surface electrode roughness through the thin separator have to be avoided. Together with

Cyclic voltammetry of activated carbon based EDLC films (Swagelok® cell)

0.3

0.2

0.0

0.0

-0.1

-0.2

-0.3

-3

-2

-1

0

1

2

3

Potential in V

Film based on a composite of AC and carbon black
Film based on a composite of AC and MWCNT

industry partners the transfer of such supercap films into capacitor production is currently evaluated.

Acknowledgments

The German Federal Ministry of Education and Research (BMBF) as well as the project management organization PT Jülich are gratefully acknowledged for their financial support within the "SuperCap" project (03X0076B).

- Recipe formulation of slurries and pastes
- Casting technologies for electrode films
- Evaluation of processability and performance of active materials in the manufacturing process
- Microscopic, electrochemical and mechanical characterization of thin electrodes
- Manufacture of electrode films in laboratory scale and upscaling for pilot plant solutions

- 1 Tape caster.
- **2** Coating of the electrode.
- 3 Casting slurry.
- **4** Electrode microstructure based on activated carbon and carbon nanotubes.

RESEARCH FIELD ENERGY SYSTEMS

Department heads:

Dr. Mihails Kusnezoff

Dr. Matthias Jahn

Dr. Christian Wunderlich

DEPARTMENT

MODULES AND SYSTEMS


Profile

The working groups of the "Modules and Systems" department cover all subareas required for development of energy systems with their defined core research areas. Systems for the efficient provision of electricity and heat are designed, constructed, and tested under realistic conditions. Of essential importance are those systems which utilize high-temperature fuel cells (SOFC) as energy converters for stationary power supply (e.g. micro CHP with $P_{\rm el}=1~{\rm kW}$).

Furthermore, electrode materials for supercaps and batteries for storage of electrical energy are investigated. Apart from the implementation of new materials and manufacturing technologies, their characterization and modeling are additional focal points.

The methodical basis for this is formed by extensive activities in the fields of multiphysics modeling and simulation of applications (SOFC, heterogeneous catalysis and batteries), as well as (spectro)electrochemistry are providing a methodological basis.

- Component and system layout
- Simulation of chemical and electrochemical processes and reactors
 - CFD with Ansys/CFX
 - Multiphysics with Matlab, PlexPDE, Comsol and Modellica/Dymola
- Design and construction of systems
- Investigation of reaction processes in test stands and systems
- Catalyst development
- Gas analysis (FID-GC, WLD-GC, PFPD-GC and GC/MS)
- Anodic and galvanic functional layers for dielectrics, photovoltaics, corrosion and wear protection, sensors and fuel cell technology
- Developments for high-throughput screening for applications in chemical and biochemical analysis
- Microelectrochemical and spectrochemical characterization of materials for batteries and capacitors
- Investigations on electrochemical machining (ECM)
- Lifecycle analysis for components and systems





Department headModules and Systems


Process Systems Engineering
Dr. Matthias Jahn
Phone +49 351 2553-7535
matthias.jahn@ikts.fraunhofer.de



Modeling and Simulation Dr. Wieland Beckert Phone +49 351 2553-7632 wieland.beckert@ ikts.fraunhofer.de



Electrochemistry
Dr. Michael Schneider
Phone +49 351 2553-7793
michael.schneider@
ikts.fraunhofer.de



SURFACE MODIFICATION OF ELECTRODES FOR BIOSENSOR APPLICATIONS

Dr. Thomas J. Rabbow, Dipl.-Ing. Uta Gierth, Dr. Michael Schneider


Screen printing and ceramic multilayer technology are an ideal basis for building up cheap sensor systems in large quantities. The chemical inertness of the ceramic material and the easy integration of different functionalities into the sensor system are further advantages of these technologies. Electronic circuits for the analysis of measurement signals or fluidic structures can be integrated into the ceramic component as well as different sensors in a multisensor array for the screening of complex analytic fluids. The modification of the surface of a sensor by electrolytic deposition, electrophoretic layers or chemical attachment of monolayers and polymers offers the possibility to functionalize the sensor for various applications.


Highly sensitive microelectrodes


Microelectrode arrays for medical applications are developed to analyze with high local resolution and to stimulate biochemical processes in cell tissue and neurocytes. The miniaturization requires highly sensitive single microelectrodes in order to integrate a high number of sensor elements. The electrophoretic deposition with chemically modified carbon nanotubes makes it possible to significantly increase the electrochemically active sensor surface of the microelectrodes. Alternatively, modified carbon nanotubes can be molecularly attached on monolayers on the sensors.


H,O, sensor

Hydrogen peroxide is a promising biomarker for respiratory gas diagnostics in case of chronic obstructive pulmonary disease. The inorganic semiconductor Prussian blue ($Fe_4^{\text{III}}[Fe^{\text{II}}(CN)_6]_3$) works as electrocatalyst for the oxidation and reduction of hydrogen peroxide. By an optimized electrochemical deposition of Prussian blue it is possible to detect hydrogen peroxide in the nanomolar range. For this purpose, it is necessary to build an open layer of Prussian blue with a high boundary surface where hydrogen peroxide can be accumulated and react with the electrocatalyst. The sensitivity can be further enhanced by an additional layer of gold nanoparticles being deposited by galvanic pulse plating. Screen printed carbon electrodes, which can be easily integrated into ceramic sensor systems, are very well suited as basis for Prussian blue sensors.










Acknowledgments

AiF and BMBF are gratefully acknowledged for funding the projects "Biosensor" (KF2087309AJ9) and "InMEAs" (16SV5323).

- Chemical modification of surfaces
- Electrochemical und electrophoretic functionalization
- Development and test of sensors
- Spectroelectrochemical characterization of layers and sensors



- 1 Microstructure of gold layers.
- **2** Prussian blue layer on sensor with gold nanoparticles.
- **3** Electrophoretic deposition of carbon nanotubes.
- 4 Electrochemical multisensor array.





ELECTROCHEMICAL AND SPECTROSCOPIC CHARACTERIZATON OF BATTERY MATERIALS

Dr. Michael Schneider, Dipl.-Chem. Ulrike Langklotz

The development of energy storage systems with improved performance and better safety is essential for the future use of renewable energies. The wide range of stationary and mobile applications requires long-living, customized materials with high power and energy density. Fraunhofer IKTS has extensive experiences in developing and manufacturing ceramic-based electrode materials with improved properties. A comprehensive understanding of the electrochemical processes, which are the basis for new energy storage concepts, as well as the electrochemical characterization of the materials are essential for this process.

The "Electrochemistry" working group at Fraunhofer IKTS offers a wide range of electrochemical and spectroscopic methods to investigate electrochemical processes during charge






and discharge processes as well as the behavior of the electrode materials. Currently, the focus is on cathode materials such as lithium-containing oxides and phosphates as well as on anode materials such as carbon, lithium titanate and silicon nanowires. For material characterization the following electrochemical methods are successfully used:

- Cyclovoltammetry (CV)
- Electrochemical impedance spectroscopy (EIS)
- Various cyclic charge-discharge experiments (e.g. CC/CV)
- Galvanostatic and potentiostatic pulse methods (GITT, PITT)






In addition to the determination of technologically significant material parameters (cell voltage, capacity, water content, cycle stability) electrochemical mechanisms are investigated. Their understanding is essential for various working groups at Fraunhofer IKTS to push the development of new materials and manufacturing technologies faster and more efficiently.

The demand for fundamental understanding of material behavior and electrochemical mechanisms requires the combination of different investigation techniques. This approach includes the development of special measuring cells and spectroscopic measurements in combination with electrochemical experiments (spectroelectrochemistry). The in-situ application of spectroscopic methods (infrared spectroscopy, Raman spectroscopy), in particular, offers various possibilities of characterizing battery materials, e.g.:

- Determination of the state of lithiation of electrode materials
- Evaluation of the state of charge
- Degradation mechanisms of electrode materials


In-situ spectroelectrochemistry allows for the direct linking of electrochemical behavior and structural properties of the electrode materials as well as the investigation of solid-electrolyte interactions.

- Electrochemical and spectroscopical characterization of electrode materials and electrolytes
- Determination of water content in electrode materials and electrolytes (Karl-Fischer titration)
- Investigation of electrochemical mechanisms



- 1 Glovebox.
- 2 Screw cells for electrochemical material characterization.
- 3 Karl-Fischer titration for determination of water content.
- **4** Measuring cell for in-situ Raman spectroscopic investigations.





DEVELOPMENT AND AUTOMATED OPERATION OF A BIOGAS SOFC SYSTEM

Dipl.-Ing. Marc Heddrich, Dr. Matthias Jahn, Dr. Mihail Kusnezoff, M. Sc. Ralf Näke, Dipl.-Ing. Aniko Weder

Motivation


Coupling regenerative biogas production and electrochemical conversion within SOFC systems is very attractive not only for the reason of a high electric efficiency. The solid oxide fuel cell (SOFC) allows the use of biogas without prior separation of carbon dioxide. Not even water has to be made available which is normally essential for good fuel reforming resulting in a high electric efficiency. Thermodynamic calculations clearly indicate that dry reforming of biogas will yield reformate of great quality containing $x_{H2} + x_{CO} > 0.75$ at T = 800°C. Dry reforming of biogas is similar to steam reforming. Carbon dioxide replaces water as reforming agent making only a very small fraction of oxygen (λ_{ref} < 0.1) necessary. Further calculations show that this highly endothermic process has the potential for ideal electric efficiencies of up to $\eta_{\text{el,id}}$ = 0.6. This makes reaching real gross efficiencies of $\eta_{el, gro} > 0.5$ without any water management possible.

Process development

To achieve the development objectives, after system and process design the main focus lies on the reformer. Here, the strongly endothermic reforming reactions must be intelligently coupled with the exothermic anode tail gas oxidation reactions. Component testing showed that the necessary heat flux for the reforming reactions is provided for the entire projected operating range. The precalculated thermodynamic equilibrium concentrations are reached.

Automation

The aims of all our automation activities within system development are safe and unsupervised operation with fully automated system management and simple system handling with a minimal number of input requirements for the operator. The uncertainties of real-life device operation are explicitly taken into account (load rejection from the electric grid, unknown fuel compositions etc.).








To accomplish the desired unsupervised operation, a stable gas flow control with near-to-market BoP components is implemented. The control strategies especially for degradation effected components rely on adaptive model based controllers. The system controller links up and prioritizes the component controllers, and it is being set to well defined states (start up, nominal operation etc.) by the superordinate sequence control system. With all that implemented, the user merely has to enter the simplest commands like "on", "off", "nominal" or "partial load".

Results

The biogas SOFC system was put into operation on schedule and could directly be set to continuous operation due to the structured development process. The gross electric efficiency amounts to $\eta_{\text{el,gro}} > 45$ % for nominal operation. The good thermal coupling of the reformer allows for extremely low



Specification of biogas SOFC system		
Fuel	Biogas	
Composition	$x_{CH4} = 0.40.7$ $x_{CO2} = 0.30.6$	
El. power, gross (per number of stacks)	0.75 kW	
Reformer air-to-fuel ratio	0.1	
Stack	CFY 30 layers	
Operating temperature	850°C	
Fuel utilization	75 %	
El. efficiency, gross	0.450.51	
Therm. efficiency	0.400.48	
Total efficiency	0.880.94	
Start/stop capability	Yes	
Emissions	According to "Blauer Engel"	

air-to-fuel ratios down to $\lambda_{ref} = 0.05$. As safety and risk management methods accompany the development process, a customer desired product certification is always taken into consideration.

- Component and system dimensioning
- Multiphysics simulations of chemical and electrochemical processes and reactors
- Development and operation of systems
- Reaction engineering analyses of reactors
- Catalyst development
- Operating life analyses for components and systems
- Gas analyses (FID-GC, WLD-GC, PFPD-GC and GC/MS)
 - 1 Straw for biogas production.
 - 2 CFY stack of Fraunhofer IKTS.
 - 3 System design.
 - 4 System assembly.







INVESTIGATION OF THE DYNAMIC BEHAVIOR OF CATALYTIC REFORMERS

Dipl.-Ing. Markus Pohl, Dipl.-Chem. Manuela Breite, Dipl.-Chem. Dorothea Männel, Dr. Matthias Jahn

Motivation and objective


In hydrocarbon operated fuel cell systems, the necessary hydrogen and carbon monoxide containing fuel is generated by reforming processes including steam reforming, partial oxidation or a mixture of both methods. Partial oxidation is preferred for a simple and robust system concept. The reformer has to react dynamically on state changes. When starting the fuel cell system, the ignition temperature as well as the time in which an almost stationary state is reached, should be as low and short as possible. The dynamic behavior of the reformer can be influenced by a suitable reactor design and catalyst material.






Development of the catalyst


Coated ceramic foams are used as catalysts. Their manufacturing method is shown in the diagram on the left. First, the ceramic foam is coated with a wash coat. Then, noble metal or nickel is applied as active component by pore volume impregnation. It is the aim to use as little noble metal as possible. The knowledge about the ignition temperature and the axial temperature profile is gained by measuring prototypes. When igniting the reformer, the temperature profile should be as flat as possible, i.e. the maximum temperature should be as low as possible.





In combination with a small amount of iridium, the ignition temperature of a nickel-loaded catalyst can be reduced. The starting process is finished within 120 s after adding the educts. SiC, in comparison with cordierite, is characterized by high thermal conductivity, and thus is well suited as support material for catalysts. Tests with ceramic foam structures and ethanol show that significantly lower temperature gradients can be realized than with commercial cordierite honeycombs. Additionally, the maximum temperatures measured on the catalyst decrease.

Ignition conditions: $P_{CH4} = constant$, $\lambda = constant$			
Active component	Tignition	Catalyst	
Nickel	> 500°C	Free of noble metals	
Iridium	< 350°C	Containing noble metals	
Nickel/iridium	< 500°C	Low amount of iridium	



- Development of reactors and tests of catalytic reactions and processes
- Development of catalysts
- Measurement equipment for the validation of various fuels for different catalysts
- Development of coated foams for gas processing and aftertreatment

- 1 Catalyst pellets.
- 2 SiC catalyst support.
- 3 Catalyst surface with active component.
- 4 Reaction with porous medium.

RESEARCH FIELD ENERGY SYSTEMS

Department heads:

Dr. Mihails Kusnezoff

Dr. Matthias Jahn

Dr. Christian Wunderlich

DEPARTMENT

INDUSTRIALIZATION ENERGY SYSTEMS

Profile

The "Industrialization Energy Systems" department – an interface between application and customer – pools the expertise of Fraunhofer IKTS in the field of materials and technology development. Its aim is the development of complete energy systems. Currently, research activities are focused on fuel cell generators and battery storage systems as well as other energy storage systems.

This focus enables the department to realize the development of specific systems based both on market and customer requirements and on available technological options. Based on a comprehensive validation and gap analysis of technology maturity, both the feedback into material and components development and the quick solution of identified technical aspects are guaranteed. Component availability and technologies issues identified along various steps of the value chain again are addressed together with material and component research teams.

In order to develop large series production processes and quality assurance methods, a small series production of prototypes can first be carried out in the laboratories and pilot plants of Fraunhofer IKTS or in cooperation with our customers. Thus, Fraunhofer IKTS is qualified as a contractor for the complete process of technology development and the stepwise knowledge transfer into series production at the customer's site.

Services offered

- System concepts, including simulation-assisted synthesis and dynamic simulation of complex energy conversion and storage systems
- Multi-criteria optimization of system structures according to the Pareto principle based on the customer's functional goals
- Prototype assembly, functional tests and validation of performance and lifetime parameters of energy systems in specially equipped laboratories within the performance range provide energy generation of some mW and 10 kW (focus: fuel cell and battery systems)
- Construction and operation of test stands for the study of specific aspects, e.g. in the high-temperature range
- Realization of prototype production and quality assurance processes on a laboratory, pilot plant and industrial scale





Department head Industrialization Energy Systems

Dr. Christian Wunderlich Phone +49 351 2553-7232 christian.wunderlich@ ikts.fraunhofer.de



System Concepts
Thomas Pfeifer
Phone +49 351 2553-7822
thomas.pfeifer@ikts.fraunhofer.de



Validation
Jens Baade
Phone +49 351 2553-7338
jens.baade@ikts.fraunhofer.de



Energy Storage Systems
Dr. Mareike Wolter
Phone +49 351 2553-7971
mareike.wolter@
ikts.fraunhofer.de





CHARACTERIZATION OF MATERIALS AND PRO-CESSES FOR LITHIUM BATTERY PRODUCTION

Dr. Mareike Wolter, Dipl.-Phys. Diana Leiva, Dipl.-Ing. Georg Fauser, Dr. Christian Bretthauer


High-performance energy storage devices significantly gain in importance due to the increasing share of renewable energies and the shift towards electric mobility. In the field of electric mobility lithium ion batteries (LIB) are considered to be a key technology as they are characterized both by high energy/ power densities and high cycling capability. In addition LIB are expected to be the most promising candidate for short term and small scale energy storage devices in the field of smart grid and off grid power.

Production of lithium battery cells in pilot scale

The use of high-performance storage materials as well as their processing plays a crucial role for the quality of LIB. Together with industry partners, the "Energy Storage Systems" working group at Fraunhofer IKTS is developing and optimizing innovative, pilot-scale manufacturing technologies for LIB. Cost-effective, modular and flexible (in terms of cell geometry and cell chemistry) production equipment is the primary focus. Currently one of the main tasks of Fraunhofer IKTS is to prepare optimized slurry systems and to develop production-oriented coating technologies. Production effects on life and performance are investigated by the characterization of electrodes for button and pouch cells and the subsequent post-mortem analysis. Suitable test and characterization methods are developed which can be integrated into the production process as in-line process control for quality assurance.

Electrical and thermal characterization

The sizes and properties of LIB cells are as widespread as the application fields. The spectrum ranges from micro batteries with a storage capacity of some milliampere hours up to large cells for industrial and automotive applications with a capacity of hundreds of ampere hours. In order to be able to characterize this spectrum of cells, various test systems are available at Fraunhofer IKTS. So, studies on button cells are performed to characterize the material properties of electrode films developed at Fraunhofer IKTS (diagram below). Commercial cells, in








contrast, are tested under application-relevant conditions, in order to investigate their qualification for stationary energy storage systems or for electric vehicles.

Furthermore, the characterization is used to identify failure mechanisms. Typical load cycles of these applications can be simulated with the help of test systems available at Fraunhofer IKTS. In particular, the influence of the ambient temperature on the electrical properties of the cells has to be taken into account. Conclusions on the quality of the production process can be drawn from the obtained data such as performance density, cycle life or internal resistance of the cells.

Post-mortem analysis

In post-mortem analyses it is investigated why batteries failed or degraded. For this purpose, imaging methods like computed tomography, optical microscopy, SEM and AFM (diagram on the right) are used in combination with analytical methods such as energy dispersive X-ray and Raman spectroscopy as well as BET and DSC measurements. Thus, detailed information about the particular failure mechanism can be obtained and aging and failure mechanisms such as dendrite formation, exfoliation, separator densification, corrosion or contamination can be localized. These studies, again, form the basis to optimize materials and processes to electrode and cell manufacturing.



- **1** Manufacturing of button cells
- **2** Characterization of button cells.
- 3 Characterization of a commercial pouch cell in a temperature test chamber.
- 4 Post-mortem analysis.

RESEARCH FIELD SMART MICROSYSTEMS

Department heads: Dr. Andreas Schönecker Dr. Uwe Partsch

DEPARTMENT

SMART MATERIALS AND SYSTEMS

Profile

The "Smart Materials and Systems" department is specialized in developing dielectric functional ceramics and integrating them into devices, microsystems and active structures. Research covers all aspects of the value chain, ranging from materials synthesis to functional verification in prototype systems.

Functional optimization is accordingly performed on several scales, through utilization of property combinations of composites, functional consolidation in materials, and adaptation of components to the system environment.


Special materials expertise exists in the field of complex perovskites, which, as high-performance piezoceramic or dielectric ceramics, provide sensing, actuating, and electronic functions in monolithic components and composites with polymers, metals, glasses, and other ceramics. Thick film, multilayer, and piezocomposite technologies are available as closed technology chains.

Preparation of thin film structures is done by CVD, PVD, and sol-gel processes in combination with reactive ion etching for structuring. With this technology portfolio, we offer new materials solutions for semiconductor technology and wear protection. With regard to system applications, unique design and characterization tools are being

developed and used. These tools describe the interaction of piezoelectric transducers with both electronic circuits and mechanical and acoustic subsystems and lead to innovative developments in piezotechnology, adaptronics/mechatronics and ultrasound technology.

Services offered

- Development, production and characterization of dielectric ceramics
- Technology development based on powders, fibers and coatings
- Development of components for specific applications in sensor, actuator, and ultrasound technology as well as electronics, wear protection and light-weight construction with integrated functions
- Modeling and simulation on the material, component and system level
- Characterization of dielectric, piezoelectric, and ferroelectric functional properties
- Vibration and sound field measurements
- Scientific instrument design, electronics, and software development





Department headSmart Materials and Systems

Multifunctional Materials and Components Dr. Andreas Schönecker Phone +49 351 2553-7508 andreas.schoenecker@ ikts.fraunhofer.de



Functional Layers for Microelectronics and Wear Protection
Dr. Ingolf Endler
Phone +49 351 2553-7693
ingolf.endler@ikts.fraunhofer.de



Piezo Systems Thomas Rödig Phone +49 351 2553-7709 thomas.roedig@ikts.fraunhofer.de



BACKSIDE PASSIVATION OF CRYSTALLINE SILICON SOLAR CELLS BY ALD

Dr. Ingolf Endler, Dipl.-Phys. Mario Krug


Introduction

Crystalline silicon solar cells are predominant in photovoltaic applications because of their advantageous cost/performance ratio. The declining buyback price for PV electricity results in an increasing cost pressure for the production and sale of new PV modules. An enhancement of the efficiency of the solar cell can be realized by applying a backside passivation layer leading to an increased carrier life time due to reduction of undesired carrier recombination. In this way, the production costs per watt peak of PV cells can be considerably reduced.

Results


For the deposition of thin, single oxide or mixed oxide coatings Fraunhofer IKTS uses two ALD lab-coaters for substrate sizes of up to 300 mm in diameter. In the ALD process, the precursors are sequentially added, separated by purge gas pulses. A mixed oxide layer of (Al,Si)O_x is deposited by inserting SiO₂-ALD cycles into Al₂O₃-ALD cycles. Trimethylaluminum (TMA), trisdimethylaminosilane (3DMAS) and ozone are used as precursors.

The stoichiometry of the mixed oxide layer can be reproducibly adjusted by the ALD-cycle ratio for both oxides. The upper diagram shows the silicon and aluminum content of the resulting mixed oxide layers.



The measured carrier life time for such backside passivated silicon in dependence on the silicon content in the $(Al,Si)O_x$ layer after different steps of thermal treatment is shown in the diagram on the right side. The carrier life time can be increased by incorporating silicon. A significant enhancement of the carrier life time can be achieved by additional thermal treatment. A maximum of the carrier life time is observed at low silicon concentration in $(Al,Si)O_x$ passivation layers. The type of thermal treatment has no significant influence on the peak value. For pure Al_2O_3 layers as well as for $(Al,Si)O_x$ layers with a higher silicon content the carrier life time is dependent on the kind of thermal treatment. Therefore, $(Al,Si)O_x$ passivation layers with optimal silicon content increase the efficiency of solar cells substantially.






Further applications

Besides the possibility of using ALD layers for backside passivation of crystalline solar cells, ALD layers are commonly used for the deposition of very thin layers with excellent conformality in microelectronic applications, e.g., for high-k layers. Because of the very low defect density and well controllable layer thickness, ALD layers are also suitable for precision optical applications as well as for barrier coatings.

Acknowledgments

This work was done in cooperation with NaMLab gGmbH, Fraunhofer CNT and Technical University of Dresden and was financially supported by the Saxon Ministry for Science and Art (Project No. 12461/2043 MERLIN) by means of the European Regional Development Fund and the Free State of Saxony.





Services offered

- Testing of new ALD precursors including determination of reaction products by mass spectrometry and laser absorption spectroscopy
- Development of ALD processes
- Depositions of prototype layers for product development
- Complex characterization of deposited layers

- 1 ALD 300 lab-coater in the clean room of Fraunhofer CNT.
- **2** ALD 100 lab-coater at Fraunhofer IKTS.
- 3 Laser absorption spectrometer Q-MACS.







PREPARATION AND CHARACTERIZATION OF ACOUSTIC TRANSDUCERS BASED ON KNN

Dr. Andreas Schönecker, Dipl.-Ing. Thomas Rödig

Motivation

The driving force for developments of lead-free piezoceramics results from environmental concerns and issued regulations by the EU. Strong support of R&D activities during the recent years resulted in a significant step forward in the development of lead-free alternatives with KNN based ceramics as one of the most promising candidates. In our work we studied possible benefits for ultrasonic transducer applications that may arise from much lower acoustic impedance of KNN based piezoceramics, compared to conventional PZT materials. The here considered samples were prepared based on our in-house standard KNN preparation process using an optimized chemical composition. Two aims were pursued: to qualify processing in order to obtain high performing acoustic transducers and to evaluate their functional benefits if used as acoustic transducers for sensing in media with low acoustic impedance.

KNN material preparation


KNN ceramics were prepared by conventional mixed oxide technology using analytical grade metal oxide or carbonate powders as raw material. Further doping of 0.5 mol % Mn was done to enhance dielectric stability. The starting powders were dried, weighed according to the desired composition and mixed with ZrO₂ balls for 24 h in isopropanol. After calcining at 800°C for 6 h, the calcine was ball-milled with ZrO₂ balls in isopropanol again. The final powders were then pressed to pellets obtaining sintered discs with 10 mm diameter and 1.5 to 2 mm thickness. The discs were sintered at 1125°C and 4 h


in oxygen atmosphere. Finally, thick-film electrodes were applied on both parallel surfaces.

Texture formation was achieved by reactive templated grain growth using in-house developed NaNbO $_3$ (NN) platelets. Seed preparation was based on a two-step salt melting process with formation of anisotropic seeds from Na $_2$ CO $_3$, Bi $_2$ O $_3$, Nb $_2$ O $_5$ in a first step and transforming them into NN seeds again in a NaCl melt. In both steps, seeds were washed out from the matrix by hot water.

Textured KNN-NN ceramics of required thickness with defined contents of NN seeds were obtained by a multilayer process using single tapes with < 50 μm in thickness to get the seed aligned. The addition of NN seeds corresponded to slight NN doping. As result, the relative permittivity ϵ_r decreased, whereas the transition temperature between orthorhombic and tetragonal symmetry remained almost unchanged in the range between 0°C and 20°C. XRD measurement showed a clear (100)-texture of the seeded KNN-NN ceramics. In order to get 1-3 composites, the "dice & fill" technology was applied using the water-cooled automatic dicing saw Disco 3350.

The ceramic elements were regularly arranged with pitch 250 μ m, kerf 50 μ m and depth of trench 800 μ m. After filling with epoxy, grinding, electrode deposition and poling, usable transducers elements were obtained.





Acoustical measurements

Acoustical characterization was carried out by scanning the sound field in water using a sensitive hydrophone in a commercial test stand (AIMS Scanning Tank, Onda Corp.). The hydrophone voltage was measured which is proportional to the sound pressure. We obtained the following results:

- KNN transducers showed higher values of output power.
- Assuming a given effective acoustic impedance, KNN composites allow for higher ceramic volume fraction which causes higher sound pressure.
- High acoustic sound velocity of 5850 m/s of KKN results in a higher resonance frequency at a given thickness. This allows for higher operation frequency for a given technology compared to PZT ceramics.
- KNN transducers have the potential of increased bandwidth (expectation 20 %) allowing for higher sensitivity especially of composite transducers.

According to our results, KNN based ultrasound transducers are expected to have high potential for high frequency, wide band applications especially for objects with low acoustic impedance. Improved acoustic transducer characteristics are expected by appropriate matching and backing. This work is still in progress.


Services offered

- Development and characterization of acoustic transducers
- Studies on the use of KNN based piezoceramics in ultrasound applications

Acknoledgments

We gratefully acknowledge BMBF (Project RealMAK 03X4007H), Germans Research Foundation (Collaborative Research Center/Transregio 39 "PT-PIESA") and AIF (Project PiezoFAST 15805 BR) for funding the projects.

- **1** FESEM micrograph showing the polished cross section of KNN piezoceramics.
- 2 NN seeds of optimum shape.
- 3 Cross section through a KNN green tape with aligned NN seeds.
- **4** Diced KNN disc, ready for 1-3 composite preparation.



ULTRASONIC TRANSDUCER ARRAYS FOR PARTICLE MANIPULATION

Dr. Sylvia Gebhardt

Motivation

Methods for trapping and handling of small particles are especially needed in the fields of biotechnology and life science. Applications include separation and sorting of cells, investigation of cell characteristics, measurements of cell forces, and tissue engineering [1]. Ultrasonic particle manipulation tools

Ultrasonic particle manipulation


Reflector
Pressure wave mode
Particles in fluid
Carrier
Transducer array
Trapping of particles

Inactive element
Active element
Transport of particles

allow for trapping and moving particles with dimensions of less than 1 µm up to hundreds of micron, e.g. cells and cell clusters. The principle of this so-called ultrasonic tweezers is based on the generation of standing ultrasound waves within a fluid channel between a transducer and a reflector layer. Particles can be trapped at the pressure node plane (diagram on the left). For some applications, movement and manipulation of particles is of special interest. Ultrasonic transducer arrays made of individually addressable elements enable for stepwise driving. Switching active single elements or subsets of elements along the array makes it possible to move trapped particles along the microfluidic chamber. Size, pitch, and number of transducer elements define precision of position control. There is a need to develop cost-effective technologies to produce 2D ultrasonic transducer arrays which allow for 3D structured acoustic fields.

Thick-film ultrasonic transducer arrays

Piezoceramic thick films based on lead zirconate titanate (PZT) offer the possibility of integrated microsystems solutions. The piezoceramic component is thereby directly applied onto the substrate material which results in a strong coupling between both components. Ground electrode, PZT thick film, insulation layers, and top electrode are prepared by repeated screen printing and subsequent sintering. The screen printing technology allows for excellent reproducibility and printing of patterned thick-film structures on substrates like ZrO₂, Al₂O₃, silicon and low temperature co-fired ceramics (LTCC).



To fabricate multi-element ultrasonic devices a 2D transducer array based on 6 x 6 PZT elements with 2 mm feature width and 2.3 mm pitch was screen printed on a 250 μ m thick Al_2O_3 substrate (figure 1). PZT thickness was adjusted to 90 μ m and 140 μ m by multiple coating. Insulation and electrode layers were applied to achieve electrical connection to each single PZT element. Multilayer substrates with internal electrode layers and vias can be used if termination at the back side of the substrate has to be provided.

For preparation of a 2D ultrasonic transducer array with 900 elements and smaller electrode pitch, a crossed electrode design (figure 2) was built by printing a continuous PZT layer between 30 perpendicular arranged bottom and top electrode lines. The lines had a width of 300 μm and a pitch of 500 μm . The crossed electrode design allows for simple fabrication and connectivity with small electrode and element width.

Both designs enable for specific driving of single transducer elements or element clusters within the 2D ultrasonic array. The generation of structured acoustic fields and their application for trapping and positioning of particles or cells within a fluid chamber is under investigation.

References

[1] C. Demore, Y. Qiu, S. Cochran, P. Glynne-Jones, C. Ye, M. Hill: Transducer Arrays for Ultrasonic Particle Manipulation, Proc. Ultrasonics Symposium (IUS) 2010, IEEE, S. 412-415

Acknowledgments

We gratefully acknowledge co-operational research with the Institute for Medical Science and Technology of Dundee University, UK within the "Sonotweezers" project.

Services offered

- Preparation of patterned PZT thick films on ZrO₂, Al₂O₃,
 LTCC and Si
- Development of ultrasonic transducers, sensors and actuators based on PZT thick films
- Design and construction of planar sensor and actuator systems and performance simulation

- 1 2D ultrasonic transducer array.
- **2** Crossed electrode ultrasonic transducer array.
- **3** Transmitted light image of figure 2.

RESEARCH FIELD SMART MICROSYSTEMS

Department heads: Dr. Andreas Schönecker Dr. Uwe Partsch

DEPARTMENT

HYBRID MICROSYSTEMS

Profile

The department "Hybrid Microsystems" is focused on the development of functional ceramic materials, miniaturized components and systems. Fields of applications are electronics packaging, high-power electronics, sensors, and energy technology (e.g. micro-fuel cells, battery technology and photovoltaics).

In addition to the development of customized pastes and inks for classic applications in hybrid electronics (e.g. conductor, resistor and encapsulating pastes for AIN), our customers benefit from an extensive know-how in the development and adaptation of magnetic materials as well as non-linear dielectrics and resistors (PTC, NTC). Furthermore, we are experts in the development and preparation of our own application-specific glasses which are used as essential composites in pastes, inks and tapes.

For the deposition of functional layers, both classic screen printing technology and additional mask-based (stencil and gravure printing) and digital printing processes (aerosol and inkjet printing) can be used, depending on the application requirements. The minimum lateral resolution of these printing methods is $< 10 \mu m$.

One main focus of our research activities is on the "Tape Casting Competence Center". At the Hermsdorf institute branch, we are able to develop and prepare customized ceramic tapes on a pilot scale. According to the requirements on tapes and

properties of the applied slurries, different tape casting methods are used (e.g. doctor blade, comma bar and slot die).

To further process these tapes into 3D-structured components, a complete ceramic multilayer technology line (LTCCs, HTCCs) is available at Fraunhofer IKTS. In cooperation with industry partners, we also run two pilot plants in which developed materials and processes are tested and optimized with consumers in a semi-industrial environment (PV pilot plant with Roth & Rau AG, battery pilot plant with ThyssenKrupp System Engineering GmbH).

In the field of electronic packaging, we also offer our customers a wide range of technologies for electrical contacting (soldering, gluing, bonding) and for mechanical and microstructural characterization of electrical connections.

Services offered

- Development, preparation, and characterization of application-specific functional ceramic materials (inks, pastes and tapes)
- Component design, development, and characterization
- Electrical systems integration of ceramic components
- Development and optimization of technologies and assessment of scalability





Department head Hybrid Microsystems

Dr. Uwe Partsch Phone +49 351 2553-7696 uwe.partsch@ikts.fraunhofer.de



Thick Film Technology and Photovoltaics Dr. Markus Eberstein Phone +49 351 2553-7518 markus.eberstein@

ikts.fraunhofer.de



Microsystems, LTCC and HTCC Dr. Steffen Ziesche Phone +49 351 2553-7875 steffen.ziesche@ ikts.fraunhofer.de




Functional Materials for Hybrid Microsystems Dr. Stefan Barth Phone +49 36601 9301-1868 stefan.barth@ikts.fraunhofer.de



Systems Integration and Electronic Packaging Dr. Lars Rebenklau Phone +49 351 2553-7986 lars.rebenklau@ikts.fraunhofer.de






CUSTOMER AND TECHNOLOGY SPECIFIC PASTES AND INKS FOR PV APPLICATIONS

Dr. Markus Eberstein, Dr. Jochen Schilm, Dr. Christel Kretzschmar

Dr. Marco Fritsch, Dipl.-Ing. (FH) Robert Jurk, Dr. Sindy Mosch


Metallization is a key process step in the fabrication of crystalline Si solar cells. It determines the solar cell design and the resulting efficiency to a large extent, and is also a major cost component in the solar cell production process. Despite a number of established cell designs, metallization by screen printing and firing of thick-film pastes is preferred by the majority of cell manufacturers. Against this background, silver based pastes and inks were developed in various projects for conventional screen printing and a number of new technologies such as fine line double printing, hot melt printing and contacting of selective emitters.



The development of pastes and inks considers not only the single components (silver, glass frit, additives, organic binders) but also the basic interactions of complex pastes systems with the Si wafers as well as the formation of the microstructure during the firing process. Sintering kinetics of glass-based Ag powders were studied to draw conclusions regarding paste adhesion and electrical contact formation on the silicon wafer. Strong effects of the particle size of the silver powders and the glass viscosity were demonstrated. Furthermore, the formation of Ag colloids at the paste/Si wafer interface during firing was found to be crucial for low electrical series resistances of the front side contact, and thus also for the final efficiency of the solar cell. The composition of the paste glass represents a key feature regarding the Ag colloid formation at the paste/Si wafer interface. Figure 1 shows the influence of various heavymetal-free glass frits used as additives in silver pastes, on the solar cell efficiencies after front side metallization. For testing the pastes in an industrial environment, a 10 MW pilot line shared by Fraunhofer IKTS and Roth & Rau AG, Hohenstein-Ernstthal, is used. A new front side paste yielding 16.5 % efficiency on 60 Ohm/sq standard wafers in the pilot line could be introduced in summer 2011. Current development is focused on lead-free front side pastes as well as on pastes for n-type cells.

Ink-jet printing is a digital printing method where droplets of a material ink are printed precisely and contactless directly on a substrate surface. For the front side metallization of PV-cells it is benficial that very thin und breakable cells can be handled and that Ag-finger width and cell shading can be reduced. Using a nanoparticle synthesis process developed at Fraunhofer





IKTS, water based Pb-free and Cd-free inks were prepared which can be printed directly on the antireflex coating (ARC) of crystalline solar cells. The optimization of the Ag particles dispersing method led to highly filled Ag inks having a solids content of up to 75 wt % and a viscosity of 20 mPas which is low enough for ink-jet printing. Using this printing method, exceptional high film thicknesses and aspect ratios of the Ag metallization of 1:3 (50 μ m line width at 15 μ m film thickness) were realized. The compatibility of the inks was demonstrated by means of industrial print heads from FUJIFILM Dimatix Inc. Inks with a particle size of 50 to 300 nm and a solid loading of 40 wt % turned out to be satisfactory and reproducible during the printing process.

During a rapid firing process of the cell, the ink etched the ARC – comparable to present-day thick-film pastes – and realized the electrical contact to the silicon cell. The resulting electrical conductivity of the metallization was in the range between 5 and 7 μ Ohmcm. Ink additives based on metal oxides play an important role in the contact mechanism as they form numerous silver seeds at the interface to the silicon. Con-

Behavior of contact resistance of an ink-jet printed Ag metallization on mc-Si with ARC

Total Parameters of an ink-jet printed Ag metallization on mc-Si with ARC

Total Parameters of an ink-jet printed Ag metallization on mc-Si with ARC

Total Parameters of an ink-jet printed Ag metallization on mc-Si with ARC

Total Parameters of an ink-jet printed Ag metallization on mc-Si with ARC

Total Parameters of an ink-jet printed Ag metallization on mc-Si with ARC

tact resistances below 10 mOhmcm² were sufficiently low, so that a prior opening of the ARC was not necessary. In cooperation with Roth & Rau, solar cells of 6 inch (mc-Si 60 Ohm/sq and 75 Ohm/sq) were produced using this technology in a pilot line. Efficiencies of 15.9 % (best cell, 15.7 % average for eight cells of one batch) demonstrate the potential of this new printing method.

Services offered

- Paste and ink development
- Process development for thick-film and ink-jet printing
- PV-specific characterization methods

- **1** Monitoring of screen printing results.
- 2 Microstructure of a screenprinted metallization.
- 3 Ink-jet printing of a solar cell.
- 4 Microstructure of an ink-jet printed Ag metallization.





WIRELESS INTERROGABLE TEMPERATURE SENSORS BASED ON CERAMIC SUBSTRATES

Dr. Michael Arnold

Motivation

Passive wireless interrogable temperature sensors based on surface acoustic wave transducers (SAW) are of great interest for wireless supervision and control of complex technical processes. One example is the acquisition of temperature values in closed reaction rooms

The operation of such SAW sensors is based on particular crystal surfaces of piezoelectric single crystals, e.g. quartz, LiNbO₃, langasit or gallium orthophosphate, on which interdigital transducers are applied by thin-film processes. If certain resonance conditions are met, acoustic surface waves can be excited on these interdigital structures by means of high-frequency impulses. These generate a response signal due to the piezoelectric effect by imaging the crystal's surface and oscillation state. This state is dependent on temperature and pressure. Thus, the response signal can be used to determine these physical values.

Although single crystalline SAW sensors reached technical maturity about 20 years ago and different systems have been commercially available since then, their application is currently limited by two aspects: the upper application temperature and the delicacy. The upper application temperature of conventional SAW sensors is limited by strong volume oscillations, high dielectric losses, phase shifts and increasing electric conductivity. For this reason, wireless interrogable temperature sensors can only be used up to temperatures of 350°C.

Approach

By applying piezoelectric thin films, the two main disadvantages of sturgeon oscillations, e.g. bulk waves, and high dielectric losses can be avoided. For this purpose, new SAWs were developed by applying a monocrystalline, piezoelectric layer on a polycrystalline substrate of high lattice symmetry and high surface quality by thin-film processes. In this case, only the piezoelectric layer with a thickness of about 10 μm is excited by a high frequency impulse so that bulk waves are mainly prevented.

Yttrium aluminum garnet (YAG) was chosen as substrate material on account of its high lattice symmetry. ZnO and AlN were used as thin-film compatible piezoelectric materials. The polycrystalline YAG substrates were produced by cold isostatic pressing (CIP) of reactive powders and subsequent sintering under high vacuum between 1700 and 1800°C. The sintering density obtained was 99.98 % of the theoretical density. Then, the sintered YAG blocks were cut into discs of 0.5 mm thickness, polished, sputtered with aluminum nitride and metalized with interdigital structures.

By combining substrates from YAG ceramics and sputtered single crystalline aluminum nitride layers, a piezoelectric multilayer system was realized which shows comparatively low impedance losses at high thermal loads. This was mainly caused by the lower damping due to the reduced decoupling of bulk waves. Using a complete ceramic housing for the wireless interrogable temperature sensors, their thermal and mechanical stability in terms of packaging technology was significantly improved.





Results


New passive SAW transducers were developed in thin-film technology which can be used to build up wireless interrogable temperature sensors for the 433 MHz band. So, temperatures up to 450°C can be reproducibly measured with a resolution of 3 K above 400°C.

Acknowledgments

The results were obtained within the framework of a joint BMWi project (Reg.-Nr. IW091116) together with Micro-Hybrid Electronic GmbH, Siegert Thinfilm Technology GmbH and the Institute of Photonic Technology.

Services offered

- Supply of YAG substrates
- Development of application samples



Transparent YAG ceramics.
 Wireless interrogable temperature sensors up to 450°C with ceramic housing.
 Temperature sensors in an

industrial furnace.

EVENTS AND EXHIBITIONS







April 14, 2011 Royal visit to Dresden

The Queen Beatrix of the Netherlands, Prince Willem-Alexander and Princess Máxima were on a state visit to Germany in April. Aside from the economic relations between both countries the focus was on the development, which Germany had taken after its reunion. On their journey the royal family also came to Dresden where they visited the Fraunhofer Institute Center. There, the Queen took part in the "Dutch-German" Seminar on Energy Innovations – Connecting PV Industries from Saxony and the Netherlands". About 150 Dutch and German experts accepted the invitation to join the Dutch-German Seminar on Energy Innovations which was organized by the embassy of the Netherlands in collaboration with the economic development agencies of Brabant and Saxony as well as the Fraunhofer Institute Center Dresden. It was the aim of the event to establish and develop cross-border cooperation activities in the field of photovoltaics. Thus, Dutch as well as German companies and research institutions can significantly strengthen their position in global competition.

September 21, 2011 First Hermsdorf Material and Technology Colloquium

At the suggestion of the Federal Association of Small and Medium-Sized Enterprises (BVMW), local association of the Jena/Saale-Holzland region, the first Hermsdorf Material and Technology Colloquium was organized at Fraunhofer IKTS. In three presentations, current developments in the field of energy and environmental technology, materials characterization and plastics engineering were examined. Within the framework of a lab tour, 60 participants had the opportunity to inform about the services offered by Fraunhofer IKTS.

September 21–23, 2011 ISPA 2011 – International Symposium on Macro Fiber Composite Applications

From September 21 to 23, the fifth International Symposium on Piezocomposite Applications ISPA took place in "Die Gläserne Manufaktur" of Volkswagen in Dresden. The aim of the ISPA symposium 2011 was to give participants from industry and research an overview of the variety of advanced applications as well as latest commercial developments and trends in the field of active structures. The symposium was organized by Fraunhofer IKTS, Volkswagen AG and Smart Material Corp. The program included more than 30 presentations of internationally renowned engineers and scientists, open discussions during the workshop, a poster session as well as a product display. More than 100 scientists and leading managers from nine countries, amongst them the USA, Canada, Spain, France and Singapore, came to Dresden and used this excellent platform to exchange ideas and to contact other interested partners for the collaboration of new marketable products in the field of piezoceramics. Due to the great interest the symposium series will be continued. The next ISPA will take place in Dresden in September 2013.

- 1 Prof. Michaelis receives Queen Beatrix of the Netherlands within the framework of the "Dutch-German Seminar on Energy Innovations"
- **2** Prince Willem-Alexander during his speech at the seminar.
- 3 Participants of the fifth ISPA in "Die Gläserne Manufaktur" of Volkswagen in Dresden.





July 1, 2011 Long Night of Sciences

On July 1, Dresden universities and research facilities invited for the "Long Night of Sciences". This event, which took place for the ninth time, found general approval of the visitors. The Fraunhofer Institute Center also opened its doors and addressed children and teenagers in particular. So, little detectives could make their finger prints visible, do a jigsaw puzzle while getting information on the production process and possible applications of ceramic foams, or play chess with ceramic chess men. Furthermore, the visitors had the opportunity to observe microorganisms purifying waste water in a glassy waste water treatment plant, and to look over the shoulder of Fraunhofer scientist during automated injection molding of ceramic components.

November 4–6, 2011 Fraunhofer Talent School

After the success of 2009 and 2010, three Dresden Fraunhofer Institutes once more invited students of the tenth to thirteenth grade to a researcher's course. For one weekend, 35 young persons interested in science had the opportunity to discuss about current research topics as well as to experiment and develop own ideas in one of three workshops. At Fraunhofer IKTS, the students learned in exciting experiments, how different kinds of fuel cells work, where they can be used and how energy technology, thermodynamics, chemistry and materials sciences are combined to develop fuel cells. In 2011, the Fraunhofer Talent School took place at ten Fraunhofer institutes in Germany. The Dresden Fraunhofer institutes plan to host the fourth Fraunhofer Talent School in November 2012. www.talent-school-dresden.de

November 10, 2011 Fourth Saxon Fuel Cell Day

The Fuel Cell Initiative Saxony and EnergieCity Leipzig hosted the fourth Saxon Fuel Cell Day in Leipzig. This seminar was meant to be a presentation, information and communication platform for Saxon fuel cell developers and researchers, thus serving as German network in the field of systems development. Aside from presentations in the field of fuel cells, ten presentations dealt with chemical energy storage systems which will gain in importance in form of hybrid systems in mobile as well as stationary applications.

Awards

Böttger medal awarded to Dr. Bärbel Voigstberger

Dr. Bärbel Voigtsberger, deputy director of the Fraunhofer IKTS, Hermsdorf institute branch, was awarded the Böttger medal at the annual meeting of the German Ceramic Society (DKG). This medal made from brown Böttger stoneware at the Meissen Porcelain Manufactory has been awarded since 1929 by the DKG's board for outstanding services to the cooperation between science and industry in the field of ceramics. This prize honors the contributions of Dr. Bärbel Voigtsberger as vice chair and member of the DKG committee and as chairperson of the "Advanced Ceramics" committee.

Thuringian Research Award honors the development of ceramic membranes for oxygen generation

Dr. Ralf Kriegel and his colleagues from the Fraunhofer Institute for Ceramic Technologies and Systems in Hermsdorf are one of three prizewinners of the Thuringian Research Award 2011, which was awarded by Christoph Matschie, the Thuringian Minister of Education, Science and Culture, on April 1, 2011. The prize, which has been awarded since 1995 for outstanding



research and development results, honors the pioneering work in the field of "Ceramic membranes for oxygen generation". Kriegel's research group developed a new production method for ceramic membranes which can separate 100-percent oxygen from other gases at high temperatures. This way 170 I pure oxygen can be produced per hour using a transportable testing device. Aside from power plant engineering and steel production, the ceramic membranes can be used in the glass and ceramic industry or for biomass gasification.

Professor Alexander Michaelis receives Bridge Building Award by the American Ceramic Society

Prof. Alexander Michaelis, director of the Fraunhofer Institute for Ceramic Technologies and Systems IKTS, was awarded the ACerS Bridge Building Award at the 36th International Conference and Exposition on Advanced Ceramics and Composites (ICACC) in Daytona Beach on January 23, 2012. With more than 1,100 participants from more than 50 countries, this conference is one of the most important international events in the field of advanced ceramics. The Bridge Building Award, which is annually awarded by the American Ceramic Society, recognizes individuals who have made outstanding contributions to engineering ceramics and thus significantly contributed to the visibility of the field and international advocacy. The award, in particular, recognizes the contribution of Prof. Michaelis in the field of energy and environmental technology.

Two apprentices at Fraunhofer IKTS honored for their good results

Since 2004, the Fraunhofer-Gesellschaft has been honoring its best apprentices who completed their apprenticeship with the examination mark "very good" or as best of the respective chamber of commerce and industry. In this year's ceremony, the Fraunhofer board honored two Fraunhofer IKTS apprentices and their trainers: Stephanie Kaiser (chemical laboratory

technician) and her trainer Dr. Annegret Potthoff as well as Andreas Böhme (physics laboratory technician) and his trainer Christine Peschka.

- 1 Prof. Sabine von Schorlemer, Saxon State Minister for Science and Arts, visiting the Long Night of Sciences.
- **2** Participants of the fuel cell workshop during the third edition of Fraunhofer Talent School in Dresden.
- 3 Research group of Fraunhofer IKTS Hermsdorf receives Thuringian Research Award.

PARTICIPATION IN TRADE FAIRS AND EXHIBITIONS



January

Enertec/Terratec

Leipzig, January 25-27, 2011

February

nano tech

Tokyo, February 16–18, 2011 Joint stand of Fraunhofer-Gesellschaft

March

Innovation Materials and Technologies

Moscow, March 1-3, 2011

Z Zuliefermesse

Leipzig, March 1–4, 2011

Joint stand of Fraunhofer AutoMOBILE Production Alliance

International Dental-Schau IDS

Cologne, March 22-26, 2011

April

Hannover Messe

Hanover, April 4-8, 2011

- Joint stand of Fraunhofer IKTS/TASK GmbH
- Joint stand of Fraunhofer Fuel Cell Initiative Saxony
- Joint stand of Fraunhofer Energy Alliance
- Joint stand of LEG Thüringen

May

SMT/HYBRID/PACKAGING

Nuremberg, May 3–5, 2011 Joint stand "Future Packaging"

International Biomass Conference Leipzig

Leipzig, May 24–25, 2011

Joint stand with Fraunhofer UMSICHT





June

Sensor + Test

Nuremberg, June 7–9, 2011 Joint stand of Saxony

9th Dresden Engine Colloquium

Dresden, 8-9 June, 2011

Energy Harvesting and Storage

Munich, June 21-22, 2011

September

EU PVSEC

Hamburg, September 5-8, 2011

October

EuroPM

Barcelona, October 9-12, 2011

IMPAS

Long Beach, October 9-13, 2011

POWTECH

Nuremberg, October 11-13, 2011

Biotechnica

Hanover, October 11–13, 2011 Joint stand of Saxony

Materialica

Munich, October 25-27, 2011

November

FAD Conference

Dresden, November 2-4, 2011

Agritechnika

Hanover, November 13-19, 2011

Productronia

Munich, November 15–18, 2011 Joint stand with ANCeram GmbH

Hagen Symposium

Hagen, November 24-25, 2011

December

Euromold

Frankfurt/Main, November 29 – December 2, 2011 Joint stand of Fraunhofer Additive Manufacturing Alliance

- 1 The "electricity from straw" exhibit is presented to the executive board of the Fraunhofer board as well as industry customers on the joint booth of the Fraunhofer Energy Alliance at Hannover Messe.
- 2 Thuringian Minister President Christine Lieberknecht visiting Ceramics Meeting Point at Hannover Messe.
- 3 First-time presentation of the transparent exhaust system at Z Zuliefermesse in Leipzig.

COOPERATION IN GROUPS, ALLIANCES AND NETWORKS

Scientists at Fraunhofer IKTS are active in numerous thematically oriented groups, networks and associations. Our customers benefit from this by having a coordinated range of joint services available to them.

DECHEMA – Society for Chemical Engineering and Biotechnol-

Membership in Fraunhofer groups, alliances, networks and demonstration centers	European Research Association for Sheet Metal Working e.V. (EFB)
Association for Manufacturing Technology and Development	Expert Group on Ceramic Injection Molding (Working Group in the German Ceramic Society)
e.V. (GFE) Association of Electrochemical Research Institutes e.V. (AGEF)	Fraunhofer Adaptronics Alliance
Association of German Engineers (VDI)	Fraunhofer Additive Manufacturing Alliance
Association of the Thuringian Economy e.V., committee of	Fraunhofer AdvanCer Alliance
research and innovation Association of Thermal Spraying e.V. (GTS)	Fraunhofer Demonstration Center AdvanCer Fraunhofer Energy Alliance
BioMeT Dresden Network	Fraunhofer Group for Materials and Components – MATERIALS
Ceramics Meeting Point in Dresden	Fraunhofer Nanotechnology Alliance

Alliance

Fraunhofer Sensor Network

Fraunhofer Numerical Simulation of Products, Processes

Fraunhofer Water Systems Alliance (SysWasser)

ogy e.V.

DKG/DGM Community Committee

European Powder Metallurgy Association (EPMA)

Fuel Cell Initiative Saxony e.V. (BZS)

German Ceramic Society e.V. (DKG)

German Society for Materials Research e.V. (DGM)

International Zeolite Association

Materials Research Network Dresden e.V. (MFD)

Meeting of Refractory Experts Freiberg e.V. (MORE)

Micro-Nanotechnology Thuringia e.V. (MNT)

NanoMat – Supraregional Network for Materials Used in Nanotechnology

Nanotechnology Center of Excellence for "Ultrathin Functional Layers"

ProcessNet – an Initiative of DECHEMA and VDI-GVC

Research Association for Diesel Emission Control Technologies e.V. (FAD)

Research Association on Welding and Allied Processes of the German Welding Society (DVS)

Silicon Saxony e.V.

Society for Knowledge and Technology Transfer of TU Dresden mbH (GWT)

TransNanoPowder Information and Consulting Center

University of Applied Sciences Jena, university council

GROUPS, ALLIANCES, NETWORKS

THE FRAUNHOFER GROUP FOR MATERIALS AND COMPONENTS – MATERIALS

Fraunhofer research in the field of materials science and technology covers the entire value chain from the development of new materials and the improvement of existing ones to manufacturing technology on a semi-industrial scale, the characterization of materials' properties and the assessment of their performance. This work extends to the components produced from the materials and their performance in systems. In addition to experimental tests in laboratories and pilot plants, numerical simulation and modeling techniques are applied in all these areas. The Fraunhofer Group for Materials and Components – MATERIALS encompasses the entire field of metallic, inorganic-nonmetallic, polymer and sustainable materials, as well as semiconductor materials.

The Group concentrates its expertise in the Energy & Environment, Mobility, Health, Machinery & Plant Engineering, Construction & Living, Microsystems Technology, and Safety business sectors. System innovations are achieved by means of tailor-made material and component developments and customer-specific performance assessment.

Key aims of the Group are

- To increase safety and comfort and to reduce the consumption of resources in transport, mechanical engineering and plant construction
- To raise the efficiency of systems for generating, converting and storing energy
- To improve the biocompatibility and functioning of materials used in medical engineering and biotechnology
- To increase the integration density and improve the utility properties of components in microelectronics and microsystem technology

- To improve the use of raw materials and the quality of the products made from them

The Group comprises the Fraunhofer Institutes for

- Applied Polymer Research IAP
- Building Physics IBP
- Structural Durability and System Reliability LBF
- Chemical Technology ICT
- Manufacturing Technology and Advanced Materials IFAM
- Wood Research, Wilhelm-Klauditz-Institut, WKI
- Ceramic Technologies and Systems IKTS
- High-Speed Dynamics, Ernst-Mach-Institut, EMI
- Silicate Research ISC
- Solar Energy Systems ISE
- Systems and Innovation Research ISI
- Mechanics of Materials IWM
- Non-Destructive Testing IZFP

Permanent guests of the Group are the Institutes for:

- Industrial Mathematics ITWM
- Interfacial Engineering and Biotechnology IGB.

Chairman of the Group

Prof. Dr.-Ing. Holger Hanselka Fraunhofer Institute for Structural Durability and System Reliability, LBF

www.materials.fraunhofer.de



FRAUNHOFER ADVANCER ALLIANCE

Systems development with high-performance ceramics

The application of high-performance ceramics allows for new applications in energy technology, mechanical and plant engineering, and medical technology. Well-known examples are combustion-chamber linings, roller bearings and implants. This innovative area has become an established field of expertise of the Fraunhofer-Gesellschaft.

Seven Fraunhofer institutes (IKTS, IPK, IPT, ISC, IWM, IZFP and LBF) have joined together to form the Fraunhofer AdvanCer. The research activities of the alliance extend along the entire value added chain – from modeling and simulation through application-oriented materials development, production and machining of ceramic parts to component characterization, evaluation and non-destructive testing under application conditions. Current R&D activities focus on joining and integration methods.

Since 2005, the Fraunhofer Demonstration Center AdvanCer has been offering training courses for technicians and engineers. The three parts being offered follow one after another, but can also be taken as single courses.

Fields of cooperation

- Materials development for structural ceramics, functional ceramics, fiber-reinforced ceramics, cermets, ceramic composites and adaptive composite materials
- Component design and development of functional prototypes
- Systems integration and verification of batch-production capabilities

- Development of powder, fiber and coating technologies
- Materials, component and process simulation
- Materials and component testing, proof-testing and nondestructive testing
- Defect analysis, failure analysis, quality management

Services offered

- Consulting and execution of feasibility studies
- Method and technology development
- Prototype development, technology transfer
- Completion of contract research, conceptualization and execution of alliance projects
- Workshops, seminars, training programs

Spokesperson of the alliance

Dr. Michael Zins Fraunhofer IKTS michael.zins@ikts.fraunhofer.de

www.advancer.fraunhofer.de

1 Shot-peened ceramic gears.

GROUPS, ALLIANCES, NETWORKS



CERAMICS MEETING POINT

Industry partners increasingly use the fast access via Ceramics Meeting Point to the research infrastructure of the Fraunhofer-Gesellschaft. The cooperation of Fraunhofer IKTS, TASK GmbH and its various members forms the basis for various industry projects, ranging from the analysis and characterization of materials to the exclusive development project for large-scale production. The opportunity to see the latest research topics in one room and to get in contact with possible suppliers is considered as added value when visiting Fraunhofer IKTS. Further Fraunhofer institutes are integrated via the Fraunhofer AdvanCer Alliance.

The institute and the ceramic manufacturers draw a bow from raw materials to systems and from prototypes to series components. TASK GmbH supports the Fraunhofer Demonstration Center AdvanCer in conducting its workshops and training courses by providing the required practice-relevant and market information. Close collaboration between the researchers of the Fraunhofer Demonstration Center AdvanCer and the ceramic manufacturers has enabled users to quickly realize their ideas. Thus, a project forum for small and medium-sized companies has developed facilitating contacts to project initiators and research institutes.



By visiting Ceramics Meeting Point within the framework of numerous events taking place at Fraunhofer IKTS once again 1850 visitors could inform about ceramic product innovations and manufacturers in 2011. Lots of the new exhibits focus on energy and environmental technology. Suppliers' interest in this sector is growing. In addition to Hannover Messe, CERAMITEC in Munich will be one strategic focus in this field.

1 Visitors tour through Ceramics Meeting Point.

NAMES, DATES, EVENTS

PATENTS

Granted patents 2011

Adler, J.; Standke, G.; Quadbeck, P.; Hauser, R.; Stephani, G. Offenzellige Titan-Metallschäume DE 10 2009 054 605 B3

Boden, G.; Ruthendorf-Przewoski von, M.; Heckmann, K.; Müller, R.; Knapp, M.

Verfahren zur Konditionierung nichtoxidischer Feinstpulver DE 101 30 161 B4

Boden, G.; Thiele, S.; Nebelung, M. Verfahren zur Dispergierung und Passivierung von feinteiligen Pulvern in Wassern und wässrigen Medien CA 2 564 450 EP 1 742 726 B1 IN 247 938 CN 101027120 B

Böer, J.; Grützmann, D.; Rothe, P.; Sikora, J.-R. Vielschichtkaltleiter und Verfah-

JP 4 792 589

Vielschichtkaltleiter und Verfal ren zu seiner Herstellung DE 198 38 067 B4

Goldberg, A.; Partsch, U.; Schneider, M.; Männel, D.; Jurk, R. 3D-Mikro-Strukturierung zur Erzeugung von Misch- und Kanalstrukturen in Multilayertech-

nologie zur Verwendung in oder

zum Aufbau von Reaktoren

DE 10 2009 038 019 B4

Goretzki, L.; Hoyer, T.; Kriegel, R.; Reinhardt, W.; Voigt, I.; Reinhardt, T. Oberflächenbehandelter Betonwerkstein und Verfahren zu dessen Herstellung

EP 1 492 743 B1

Grzesiak, A.; Lenk, R.; Refle, O.; Richter, H.-J. Vorrichtung und Verfahren zur

Beschickung einer Materialschicht auf eine Bauplattform oder auf wenigstens eine auf der Bauplattform befindlichen Materialschicht zur Herstellung eines Gegenstandes im Wege eines generativen Herstellungsverfahrens

Herrmann, M.; Klemm, H.; Moritz, T.; Lenk, R.; Goettler, A.; Richter, H.-J.

DE 10 2009 024 334 B4

Glühkerze und Verfahren zu ihrer Herstellung CN 1973163 B

Herrmann, M.

JP 4815440

Werkstoff auf Basis von α -/ β -SiA-LON, Verfahren zu dessen Herstellung und dessen Verwendung DE 10 2006 059 403 B4

Herrmann, M.; Bales, A.; Weise, B.; Räthel, J.

Werkstoff auf Siliciumnitrid-Basis, Verfahren zu dessen Herstellung und dessen Verwendung

DE 10 2006 059 402 B4

Jurk, R.; Scheithauer, U.; Schneider, M.; Pfeifer, T. Verfahren für die Herstellung einer offenporigen und von einem Fluid durchströmbaren Struktur sowie eine Verwendung der mit dem Verfahren hergestellten Struktur DE 10 2009 033 716 B4

Kaps, C.; Kühnert, J.-T.; Rotter, F.; Schöps, W.; Bettziesche, H.; Buchwald, A.; Hohmann, H.; Hohmann, M.

Verfahren zur Herstellung geformter und gebrannter Bauelemente aus Schaumton DE 103 00 043 B4

Kriegel, R.; Kircheisen, R.; Ritter, K. Verfahren zur hochtemperaturfesten Verbindung von sauerstoffpermeablen Oxidkeramiken auf der Basis substituierter Erdalkalicobaltate durch dotierungsunterstützendes diffusives Reaktionssintern DE 10 2009 050 019 B3 Kusnezoff, M.; Beckert, W.; Milcheva I.; Stelter, M.;

Waeschke, U.

Verfahren und System zum Betreiben einer Hochtemperaturbrennstoffzelle

DE 10 2006 003 740 B4

Martin, H.-P.; Herrmann, M.; Petasch, U.; Kaskel, S.; Kockrick, E. Verfahren zur Herstellung poröser SiC-Komposite und mit diesem Verfahren hergestelltes SiC-Komposit DE 10 2007 031 537 B4

Moritz, T.; Lenk, R.

Verfahren zur Herstellung keramischer und pulvermetallurgischer geformter Körper

DE 103 24 828 B4

Neubert, H.; Partsch, U.
Sensor zur Ermittlung der elektrischen Leitfähigkeit flüssiger
Medien und ein Verfahren zu
seiner Herstellung
EP 2 018 547 B1

Otschik, P.; Eichler, K.; Megel, S.
Stapelbare HochtemperaturBrennstoffzelle
US 7 897 289

Partsch, U.

Ceramic pressure sensors and method for producing the same US 8 079 268 B2

PATENTS, PATENT APPLICATIONS, BOOKS AND PERIODICAL CONTRIBUTIONS

Sauchuk, V.; Otschik, P.; Eichler, K.; Kusnezoff, M.

Katalytisch aktives Bauelement für Thermoionisationsdetektoren zum Nachweis von halogenhaltigen Verbindungen und Verfahren zur Herstellung eines oxidkeramischen Werkstoffs für das Bauelement

TW I 350 277

Scheithauer, U.; Schönecker, A.; Seffner, L.; Gebhardt, S.; Michaelis, A.

Verfahren zur reproduzierbaren Herstellung keramischer Formkörper

DE 10 2008 056 721 B4

Standke, G.; Böttge, D.; Adler, J.
Offenzellige Keramik- und/oder
Metallschäume mit rauer umhüllender Oberfläche und Verfahren zu ihrer Herstellung
DE 10 2008 054 596 B4

Trofimenko, N.; Kusnezoff, M.; Mosch, S.; Lucke, K. Elektrisch leitfähiger Aufbau aus zwei Bauteilen und Verfahren zur Herstellung des Aufbaus DE 10 2006 055 836 B4

Trofimenko, N.; Mosch, S.; Sauchuk, V.; Lucke, K.; Kusnezoff, M. Funktionsschicht für Hochtemperaturbrennstoffzellen und Verfahren zur Herstellung EP 2 210 308 B1

Tupaika, F.; Voigtsberger, H.-J.; Grützmann, D. Elektrisches Widerstandsheizelement mit einem Wabenkörper DE 100 60 301 B4

Tupaika, F.; Sikora, J.-R.; Esefeld, S. Verfahren und Anordnung zum Aufbringen elektrisch leitender Schichten mit hoher Stromtragfähigkeit auf die Wandungen der von einem zu erwärmenden Medium zu durchströmenden Kanäle eines elektrischen Widerstandsheizelementes

DE 10 2009 057 289 B3

Patent applications 2011

Adler, J.; Heymer, H.; Gusek, C.; Eisner, F.; Hülstrung, J.; Jindra, F.; Willeke, B.-H.; Blumenau, M.; Kovac, M.; Jendrischik, G.; Peitz, A.; Schönenberg, R. Vorrichtung zur Druckminderung in Hohlkörpern in Medien bei höheren Temperaturen

Breite, M.; Jahn, M.; Goldberg, A. Vorrichtung zur Verdampfung flüssiger Kohlenwasserstoffverbindungen oder von Flüssigkeiten in denen Kohlenwasserstoffverbindungen enthalten sind sowie deren Verwendung

Endler, I.; Scholz, S.

Hartstoffbeschichtete Körper aus
Metall, Hartmetall, Cermet oder
Keramik sowie Verfahren zur
Herstellung derartiger Körper

Grzesiak, A.; Graf, C.; Visotschnig, R.; Refle, O.; Richter, H.-J.; Haderk, K.; Kraft, T.; Ziegler, T.; Schäfer, R. Verfahren zur Herstellung eines keramischen Formkörpers

Herrmann, M.; Matthey, B. Verbundbauteil und Verfahren zu seiner Herstellung

Herrmann, M.; Räthel, J.;

Matthey, B.

Verfahren zur Herstellung eines
Werkstoffes, in dem Diamantkristalle oder cBN-Partikel enthalten sind, und mit dem
Verfahren hergestellter Werkstoff

Krell, A.; Strassburger, E.

Transparente Komposit-Scheibe
für Sicherheitsanwendungen

Kusnezoff, M.; Trofimenko, N.; Belda, C.; Girdauskaite, E.; Guth, U.; Vashook, U. Bauelement für Hochtemperaturanwendungen Verfahren zu seiner Herstellung und seine Verwendung

Lausch, H.; Arnold, M.; Brand, M. Anordnung zur topischen Stimulation der Ossifikation/Osteo-/ Soft-Tissue-Genese und/oder Suppression

Lausch, H.; Brand, M.; Arnold, M.
Monitoringzelle und Verfahren
zur Analyse eines Zell- und Gewebewachstums

Pawlowski, B.; Fischer, G.; Müller, M.; Prehn, V.; Betz, T. Gesintertes flächiges Zirkonprodukt

Pfeifer, T.; Nousch, L.

System und Verfahren zum Betreiben von Festoxid-Brennstoffzellen

Räthel, J.; Herrmann, M.; Weise, B. Druckstempelwerkzeug für das Funkenentladungssintern oder das feldaktive Sintern

Richter, H.; Lenke, N.; Voigt, I. Verfahren zur Herstellung eines mikroporösen Materials für die molsiebende Gastrennung

Schilm, J.; Rost, A.; Kusnezoff, M. Festelektrolyt für den Einsatz in Lithium-Luft- oder Lithium-Wasser-Akkumulatoren Scheithauer, U.; Haderk, K.; Richter, H.-J.; Zins, M.; Bergner, A. Brennhilfsmittel, als Träger für Bauteile bei einer Wärmebehandlung

Scheithauer, U.; Richter, H.-J.; Moritz. T.

Vorrichtung zur Herstellung von Grünfolien aus keramischen und/ oder metallischem Werkstoff

Scheithauer, U.; Haderk, K.; Reuber, S.; Goldberg, A. Wärmedämmendes Isolationselement für Hochtemperaturanwendungen und ein Verfahren zu ihrer Herstellung

Schubert, R.; Fischer, G.; Häusler, A.; Roßberg, A.; Uehlin, T.; Lopatin, S. Kompositwerkstoff, Formkörper, elektronisches Gerät mit Formkörper, und Verfahren zur Herstellung für einen Formkörper

Schweizer, S.; Henke, B.; Miclea, P.T.; Wehrspohn, R.B.; Kinski, I.; Meinhard, S.

Solarzellen mit verlängerter und ausgleichender Wirkungsdauer

Slawik, T.; Baumann, A.; Scholl, R.; Handke, T.; Moritz, T.; Richter, H.-J.; Scheithauer, U.; Zins, M.; Zelm, R. Keramische und/oder pulvermetallurgische Formteile und Verfahren zu ihrer Herstellung Trofimenko, N.; Sauchuk, V.; Kusnezoff, M.; Lucke, K.; Michaelis, A.; Bandner, M.; Schmid, J.; Venskutonis, A. Schicht zur Vorsehung zwischen einem Interkonnektor und einer Kathode

Books and periodical contributions

Ahlhelm, M.; Fruhstorfer, J.; Moritz, T.; Michaelis, A. Die Herstellung von Feuerleichtsteinen über die Gefrier-Direktschäumungsmethode Keramische Zeitschrift 63(2011), No.6, in press

Ahlhelm, M.; Fruhstorfer, J.; Moritz, T.; Michaelis, A. The manufacturing of lightweight refractories by direct freeze foaming technique Interceram – International Ceramic Review 60(2011), No.6, p.394-399

Baumann, A.; Michaelis, A. (Hrsg.)
Pulverspritzgießen von MetallKeramik-Verbunden
Stuttgart: Fraunhofer Verlag, 2011
(Kompetenzen in Keramik. Schriftenreihe, 9), Zugl.: Freiberg, Univ.,
Diss., 2010

ISBN 978-3-8396-0236-2

Boyko, T.D.; Zvoriste, C.E.; Kinski, I.; Riedel, R.; Hering, S.; Huppertz, H.; Moewes, A. Anion ordering in spinel-type gallium oxonitride Physical Review. B 84(2011), No.8, Art.085203

Busch, W.; Bastian, S.; Trahorsch, U.;

Iwe, M.; Kühnel, D.; Meißner, T.; Springer, A.; Gelinsky, M.; Richter, V.; Ikonomidou, C.; Potthoff, A.; Lehmann, I.; Schirmer, K. Internalization of engineered nanoparticles into mammalian cells in vitro: Influence of cell type and particle properties Journal of Nanoparticle Research 13(2011), No.1, p.293-310

Chen, H.; Klemm, H.
Environmental barrier coatings
for silicon nitride
Key engineering materials
484(2011), p.139-144

de Moraes, I.R.; Scholz, S.; Lüssem, B.; Leo, K. Analysis of chemical degradation mechanism within sky blue phosphorescent organic light emitting diodes by laser-desorption/ionization time-of-flight mass spectrometry Organic Electronics 12(2011), No.2, p.341-347 de Moraes, I.R.; Scholz, S.; Lüssem, B.; Leo, K. Role of oxygen-bonds in the degradation process of phosphorescent organic light emitting diodes Applied Physics Letters 99(2011),

No.5, 053302

Eckhard, S.; Nebelung, M.
Investigations of the correlation
between granule structure and
deformation behavior
Powder Technology 206(2011),
No.1/2, p.79-87

Farack, J.; Wolf-Brandstetter, C.;

Glorius, S.; Nies, B.; Standke, G.; Quadbeck, P.; Worch, H.; Scharnweber, D. The effect of perfusion culture on proliferation and differentiation of human mesenchymal stem cells on biocorrodible bone replacement material Materials Science and Engineering, B. Solid state materials for advanced technology 176(2011), No.20,

Freemantle, C.S.; Johnson, O.T.; Sigalas, I.; Herrmann, M. Interaction of boron suboxide with compacted graphite cast iron Ceramics international: CI 37(2011), No.3, p.1121-1125

p.1767-1772

BOOKS AND PERIODICAL CONTRIBUTIONS

Freund, S.; Gaal, A.

AdvanCer Newsletter

Ausgabe 2011/1-3

Dresden: Fraunhofer IKTS, 2011

Füssel, A.; Klemm, H.; Böttge, D.; Marschallek, F.; Adler, J.; Michaelis. A.

Advancement of cellular ceramics made of silicon carbide for burner applications

IOP conference series. Materials science and engineering 18(2011), Symposium 12, Art.182001

Füssel, A.; Böttge, D.; Adler, J.; Marschallek, F.; Michaelis, A. Cellular ceramics in combustion environments

Advanced Engineering Materials. Special Issue: Cellular Materials 13(2011), No.11, p.1008-1014

Glöß, B.; Fries, M.; Nebelung, M. Keramische Pressgranulate: Mechanische Eigenschaften und deren Einfluss auf das Fließverhalten

Chemie Ingenieur Technik 83(2011), No.5, p.626-631

Herrmann, M.; Matthey, B.; Höhn, S.; Kinski, I.; Rafaja, D.; Michaelis, A. Diamond-ceramics composites – New materials for a wide range of challenging applications

Journal of the European Ceramic

Society (2011), doi:10.1016/j.jeur-ceramsoc.2011.11.005, online first

Herrmann, M.; Swarnakar, A.K.; Thiele, M.; van der Biest, O.; Sigalas, I.

High temperature properties of B6O-materials

Journal of the European Ceramic Society 31(2011), No.13, p.2387-2392

Herrmann, M.; Räthel, J.; Höhn, S.; Eichler, J.; Michaelis, A. Interaction of titanium diboride/boron nitride evaporation boats with aluminium Journal of the European Ceramic Society 31(2011), No.13, p.2401-2406

Herrmann, M.; Höhn, S.; Bales, A. Kinetics of rare earth incorporation and its role in densification and microstructure formation of $\alpha\mbox{-Sialon}$

Journal of the European Ceramic Society (2011), doi:10.1016/j.jeurceramsoc.2011.05.026, online first

Herrmann, M.; Thiele, M.;
Jaenicke-Rößler, K.;
Freemantle, C.S.; Sigalas, I.
Oxidation resistance of B₆O-materials with different additives
Journal of the European Ceramic
Society 31(2011), No.9, p.1771-

Herrmann, M.; Bodkin, R.; Coville, N.J.; Sigalas, I.; Thiele, M. Sintering mechanical properties of AlMgB14 composite materials Journal of Ceramic Science and Technology 2(2011), No.1, p.55-60

Höhn, S.; Sempf, K.; Herrmann, M. Artefact-free preparation and characterization of ceramic materials and interfaces

cfi - ceramic forum international 88(2011), No.11-12, p.E1-E5

Höhn, S.; Eckhard, S.; Fries, M.; Matthey, B.; Herrmann, M.; Michaelis, A.

Methods of quantification of the internal structures of spray granules

Journal of Ceramic Science and Technology 2(2011), No.2, p.75-88

Kahle, I.; Tröber, O.; Trentsch, S.; Richter, H.; Grünler, B.; Hemeltjen, S.; Schlesinger, M.; Mehring, M.; Spange, S. Functional mesoporous aluminosilicate nanoparticles as host material to fabricate photo-switchable polymer films Journal of Materials Chemistry 21(2011), No.13, p.5083-5088

Kailer, A.; Amann, T.; Krummhauer, O.; Herrmann, M.; Sydow, U.; Schneider, M. Influence of electric potentials on the tribological behaviour of silicon carbide

Wear 271 (2011), No.9/10, p.1921-1927

Klemm, H.; Nake, K.; Bales, A.

Bestimmung der Warmhärte von metallischen und keramischen

Hochtemperaturwerkstoffen

HTM Journal of Heat Treatment and Materials 66(2011), No.5, p.269-274

Klimke, J.; Trunec, M.; Krell, A. Transparent tetragonal yttriastabilized zirconia ceramics: Influence of scattering caused by birefringence

Journal of the American Ceramic Society 94(2011), No.6, p.1850-1858

Krell, A.; Bales, A.

Grain size-dependent hardness
of transparent magnesium aluminate spinel

International Journal of Applied Ceramic Technology 8(2011), No.5, p.1108-1114

Kriegel, R.; Schulz, M.; Ritter, K.; Kiesel, L.; Pippardt, U.; Stahn, M.; Voigt, I.

Advanced membrane design for oxygen separation

Efficient Carbon Capture for Coal Power Plants, Book of Extended Abstracts, Frankfurt/M.: Dechema (2011), p.114-117 Kurama, S.; Schulz, I.; Herrmann, M.

Wear properties of α - and α -/ β -SiALON ceramics obtained by gas pressure sintering and spark plasma sintering

Journal of the European Ceramic Society 31(2011), No.5, p.921-930

Langklotz, U.; Schneider, M.; Seifert, C.; Michaelis, A. Investigation concerning the applicability of raman spectroscopy for prospective inline monitoring of electrode processing for lithium ion batteries

Materialwissenschaft und Werkstofftechnik 42(2011), No.9, p.820-826

Machaka, R.; Derry, T.E.; Sigalas, I.; Herrmann, M.

Analysis of the indentation size effect in the microhardness measurements in $B_{\varepsilon}O$

Advances in Materials Science and Engineering. Online journal 2011(2011), Art.539252

Mannschatz, A.; Ahlhelm, M.; Moritz, T.; Michaelis, A. 3D visualization of flow patterns in injection moulded ceramic green parts

Powder injection moulding international: PIM 5(2011), No.2, p.60-65

Mannschatz, A.; Müller, A.; Moritz, T.

Influence of powder morphology on properties of ceramic injection moulding feedstocks
Journal of the European Ceramic
Society 31(2011), No.14, p.25512558

Matizamhuka, W.R.; Sigalas, I.; Herrmann, M.; Dubronvinsky, L.; Dubrovinskaia, N.; Miyaji,a, N.; Mera, G.; Riedel, R. Characterization of the materials synthesized by high pressurehigh temperature treatment of a polymer derived t-BC₂N ceramic

mic Materials 4(2011), No.12, p.2061-2072

McKie, A.; Winzer, J.; Sigalas, I.; Herrmann, M.; Weiler, L.; Rödel, J.; Can, N.

Mechanical properties of cBN-Al composite materials

Ceramics international: CI 37(2011), No.1, p.1-8

Megel, S.; Girdauskaite, E.; Sauchuk, V.; Kusnezoff, M.; Michaelis, A.

Area specific resistance of oxide scales grown on ferritic alloys for solid oxide fuel cell interconnects

Journal of power sources 196(2011), No.17, p.7136-7143 Meulenberg, W.A.; Voigt, I.; Kriegel, R.; Baumann, S.; Ivanova, M.; van Gestel, T. Materials for membrane separation of CO₂

Efficient Carbon Capture for Coal Power Plants/ed. by D. Stolten Weinheim: Wiley-VCH, 2011, p.319-350 ISBN 978-3-527-33002-7

Meyer, A.; Lenzner, K.; Potthoff, A.
Influence of energy input on
suspension properties

Advances in science and technology 62(2011), p.141-146

Missal, W.; Kita, J.; Wappler, E.; Gora, F.; Kipka, A.; Bartnitzek, T.; Bechtold, F.; Schabbel, D.; Pawlowski, B.; Moos, R. Miniaturized ceramic differential scanning calorimeter with integrated oven and crucible in LTCC technology

Sensors and Actuators. A, Physical 172(2011), No.1, p.21-26

Neher, R.; Herrmann, M.; Brandt, K.; Jaenicke-Rößler, K.; Pan, Z.; Fabrichnaya, O.; Seifert, H.J. Liquid phase formation in th

Liquid phase formation in the system SiC, Al₂O₃, Y₂O₃
Journal of the European Ceramic Society 31(2011), No.1-2, p.175-181

Paepcke, A.; Michaelis, A. (Hrsg.) Untersuchung des Hochtemperaturbrennstoffzellenstapels unter realen Betriebsbedingungen durch Finite-Elemente-Modellierung

Stuttgart: Fraunhofer Verlag, 2011 (Kompetenzen in Keramik. Schriftenreihe, 8), Zugl.: Dresden, Univ., Diss., 2010 ISBN 978-3-8396-0224-9

Pönicke, A.; Böhm, G.; Schilm, J.; Schnee, D.

Aktivlöten von Kupfer mit Aluminiumnitrid- und Siliziumnitridkeramik

Keramische Zeitschrift 63(2011), No.5, p.334-342

Rabbow, T.J.; Junker, N.; Schneider, M.; Michaelis, A. Screen-printed gold thick films for electrochemical sensor applications

Materialwissenschaft und Werkstofftechnik 42(2011), No.9, p.777-783

Reinfried, M.; Stephani, G.; Luthardt, F.; Adler, J.; John, M.; Krombholz, A.

for multifunctional applications
Advanced Engineering Materials.
Special Issue: Cellular Materials
13(2011), No.11, p.1031-1036

Hybrid foams – A new approach

BOOKS AND PERIODICAL CONTRIBUTIONS, PRESENTATIONS AND POSTERS

Riedel, S.; Neidhardt, J.; Jansen, S.; Wilde, L.; Sundqvist, J.; Erben, E.; Teichert, S.; Michaelis, A. Synthesis of SrTiO₃ by crystallization of SrO/TiO₂ superlattices prepared by atomic layer deposition

Journal of applied physics 109(2011), No.9, Art.094101

Rödel, C.; Müller, M.; Glorius, M.; Potthof, A.; Michaelis, A. Effect of varied powder processing routes on the stabilizing performance and coordination type of polyacrylate in alumina suspensions

Journal of the European Ceramic Society 32(2012), No.2, p.363-370

Sauchuk, V.; Megel, S.; Girdauskaite, E.; Trofimenko, N.; Kusnezoff, M.; Michaelis, A. Influence of protective layers on SOFC operation

Russian Journal of Electrochemistry 47(2011), No.5, p.522-530

Scheithauer, U.; Haderk, K.; Richter, H.-J.; Petasch, U.; Michaelis, A. Laminated multilayer for thermal shock resistant refractories based on the material system calcium-aluminate

Refractories Manual. Interceram Special Edition 60(2011), No.2, p.103-107 Schilm, J.; Rost, A.; Pönicke, A.; Kusnezoff, M.

Fügetechnologien für SOFC Info-Service Fachgesellschaft Löten (2011), No.23, p.6-10

Schmidt, J.; Michaelis, A.; Kinski, I.; Uhlig, S.

pour deposition of ZnO for photovoltaic TCO application Photovoltaics International 14(2011), p.144-150, in press

Plasma-enhanced chemical va-

Schneider, M.; Schroth, S.; Richter, S.; Höhn, S.; Schubert, N.; Michaelis, A. In-situ investigation of the interplay between microstructure and anodic copper dissolution under near-ECM conditions – Part 1: The active state Electrochimica Acta 56(2011), No.22, p.7628-7636

Schneider, M.; Lämmel, C.; Heubner, C.; Michaelis, A. In-situ temperature measurement on the metal/oxide/electrolyte interface during the anodizing of aluminum Materials and Corrosion 62(2011), doi:10.1002/maco.201106129, online first

Schneider, M.; Langklotz, U.; Michaelis, A. Thickness determination of thin anodic titanium oxide films – a comparison between coulometry and reflectometry Surface and Interface Analysis 43(2011), No.12, p.1471-1479

Schulz, M.; Kriegel, R.; Kämpfer, A. Assessment of CO₂ stability and oxygen flux of oxygen permeable membranes

Journal of membrane science 378(2011), No.1-2, p.10-17

Schulz, M.; Michaelis, A. (Hrsg.)
Charakterisierung und Modellierung des Material- und Bauteilverhaltens keramischer
Membranen für die Sauerstoffbereitstellung des Systems
Sr_{0.5}Ca_{0.5}Mn_{1-y}Fe_yO₃₋₈ unter Einbeziehung von Gas-FestkörperWechselwirkungen

Stuttgart: Fraunhofer Verlag, 2011 (Kompetenzen in Keramik. Schriftenreihe, 10), Zugl.: Weimar, Univ., Diss., 2010

ISBN 978-3-8396-0245-4

Schwarz, B.; Friedrich, E.; Jobst, K.; Lincke, M.; Wufka, A. Möglichkeiten der Substratvorbehandlung: Stand und neue Entwicklungen Forum New Power (2011), No.3, p.19-23

Stosiek, C.; Ludwig, H.; Reichel, U.; Scholz, G.; Kemnitz, E. Nanoscopic metal fluorides as promising sintering aids for high-performance alumina ceramics

Journal of Ceramic Science and Technology, 2(2011), No.1, p.31-38

Sydow, U.; Sempf, K.; Herrmann, M.; Schneider, M.; Kleebe, H.-J.; Michaelis, A. Electrochemical corrosion of liquid phase sintered silicon carbide ceramics

Materials and Corrosion 62(2011), doi:10.1002/maco.201106283, online first

Thiele, S.; Sempf, K.; Jaenicke-Rößler, K.; Berger, L.-M.; Spatzier, J.
Thermophysical and microstructural studies on thermally sprayed tungsten carbide-cobalt coatings

Journal of Thermal Spray Technology 20(2011), No.1-2, p.358-365

Toma, F.-L.; Scheitz, S.;
Berger, L.-M.; Sauchuk, V.;
Kusnezoff, M.; Thiele, S.
Comparative study of the electrical properties and characteristics of thermally sprayed alumina and spinel coatings
Journal of Thermal Spray Technology 20(2011), No.1-2, p.195-204

Triebert, A.; Matthey, B.; Martin, H.-P. Untersuchungen zu Ta-Ni-Legierungen als Hochtemperaturlot für SiC-SiC Verbunde Keramische Zeitschrift 63(2011),

No.5, p.322-328

Vashishta, L.; Voigt, I.; Weyd, M. **Solvent separation by pervapo ration and vapour permeation** PharmaBioWorld 9(2011), No.7, p.40-42

Wätzig, K.; Michaelis, A.

Transparente MgAl₂O₄-Keramik
aus Precursor-abgeleiteten Spinell-Pulvern oder per Reaktionssintern von MgO-/Al₂O₃Gemischen

Stuttgart: Fraunhofer-Verlag, 2011 (Kompetenzen in Keramik. Schriftenreihe 11). Zugl.: Freiberg, TU, Diss., 2011 ISBN 978-3-8396-0335-2

Zgalat-Lozynskyy, O.; Herrmann, M.; Ragulya, A. Spark plasma sintering of TiCN nanopowders in non-linear heating and loading regimes Journal of the European Ceramic Society 31(2010), No.5, p.809-813

Ziesche, S.; Rebenklau, L.;
Partsch, U.
Sensoren in keramischer Mehrlagentechnik – aktuelle Entwicklungen am Fraunhofer IKTS

Produktion von Leiterplatten und

Systemen: PLUS 13(2011), No.5, p.1167-1171

Zschippang, E.; Klemm, H.; Herrmann, M.; Sempf, K.; Guth, U.; Michaelis, A. Electrical resistivity of silicon nitride-silicon carbide based ternary composites

Journal of the European Ceramic Society 32(2012), No.1, p.157-165

Presentations and posters

Ahlhelm, M.; Zybell, K.; Gorjup, E.; von Briesen, H.; Moritz, T.

Freeze-foaming: A new approach to manufacture cermic cellular structures allowing the ingrowth and differentiation of mesenchymal stem cells

13th Congress on Ceramics, Cells and Tissues, Faenza, Italy

(17.-20.5.2011), presentation

Ahlhelm, M.; Moritz, T.

Herstellung eines biokompatiblen Hydroxylapatit-ZrO₂-Hybridschaums über die Methode der Gefrier-Direktschäumung

18. Symposium Verbundwerkstoffe und Werkstoffverbunde, Chemnitz

(30.3.-1.4.2011), p.531-536, presentation

Ahlhelm, M.; Fruhstorfer, J.; Moritz, T. The manufacturing of refractories with larger dimensions by direct freeze-foaming technique 17th International Conference on Refractories, Praha, Czech Republic (10./11.5.2011), presentation

Arnold, M.; Suphan, K.-H.; Kessler, E.; Ihring, A.; Brode, W. Fernabfragbare Temperatursensoren auf Basis keramischer YAG-Substrate

Thüringer Werkstofftag, Jena (30.3.2011), poster

Bachmann, E.; Breite, M.; Jahn, M.; Koszyk, S.; Männel, D.; Weder, A. Stabilisierung von Al₂O₃-Trägermaterialien durch Imprägnierung mit Lathan und Kalium 44. Jahrestreffen Deutscher Katalytiker mit Jahrestreffen Reaktionstechnik, Weimar (14.-18.3.2011), poster

Barth, S.; Pawlowski, B.; Bierlich, S.; Töpfer, J.; Bartnitzek, T. Keramische Funktionswerkstoffe für die Integration passiver Komponenten in LTCC Thüringer Werkstofftag, Jena (30.3.2011), poster

Bartsch, H.; Walther, F.; Krümmer, R.; Reimann, T.; Barth, S.; Müller, J. Characteristics of buried capacitors in LTCC multilayer packages Proceedings of the SSI 2011: European Conference & Exhibition on Integration Issues of Miniaturized Systems, Dresden (22./23.3.2011), presentation

Beckert, W.; Nousch, L.; Pfeifer, T.; Reuber, S. Energieeffizienz in Brennstoffzellensystemen Zukunft Energie, Dresden

Beckmann, B.; Hohe, J.; Reinfried, M.; Luthardt, F.

(11.-13.5.2011), presentation

Numerische Bestimmung der makroskopischen Eigenschaften hybrider Schäume 18. Symposium Verbundwerkstoffe

18. Symposium Verbundwerkstoffe und Werkstoffverbunde, Chemnitz (30.3.-1.4.2011), p.543-548, presentation and poster

Belitz, R.; Jahn, M.; Koszyk, S.; Männel, D.; Michaelis, A. Langzeitstabile Katalysatoren für die Abgasnachbehandlung in SOFC-Systemen auf Basis von SSiC-Schaumkeramik 44. Jahrestreffen Deutscher Katalytiker mit Jahrestreffen Reaktionstechnik, Weimar (14.-18.3.2011), poster

Belitz, R.; Heddrich, M.-P.; Jahn, M.; Näke, R.M.; Paulus, J.; Pohl, M. System tests and operation control strategies of an SOFC-CHP-

device for field testing

12th International Symposium on Solid Oxide Fuel Cells – SOFC-XII, Montreal, Canada (1.-6.5.2011), p.279-284, presentation

Benner, F.; Kupke, S.; Jakschik, S.; Erben, E.; Knaut, M.; Müller, J.; Rose, M.; Schroeder, U.; Mikolajick, T.

Dielectric backside passivation – improvements by Si-doped Al₂O₃ dielectrics

11th international Conference on Atomic Layer Deposition, Cambridge, Massachusetts, USA (26.-29.6.2011), presentation

Boer, J.

Nanosize powders prepared by flame pyrolysis and their agglomeration

5th International Seminar »Nanotechnology, energy, plasma, lasers«, Hermsdorf/Jena (1.-3.11.2011), presentation

Böhm, G.; Brunner, D.; Sichert, I.; Pönicke, A.; Schilm, J.

Properties and reliability of silicon nitride substrates with AMB copper conductor

44th International Symposium on Microelectronics, International Microelectronics And Packaging Society – IMAPS 2011, Long Beach, USA (9.-13.10.2011), p.777-784, presentation Böse, C.; Jahn, M.; Michaelis, A.; Pohl, M.

Zündverhalten edelmetallfreier katalytischer Schaumkeramik bei der partiellen Oxidation

44. Jahrestreffen Deutscher Katalytiker mit Jahrestreffen Reaktionstechnik, Weimar (16.-18.3.2011), poster

Breite, M.; Jahn, M.; Männel, D.; Weder, A.

Ni/Al₂O₃- und NiCu/Al₂O₃-Mischkatalysatoren für die partielle Oxidation von Ethanol 44. Jahrestreffen Deutscher Kataly-

tiker mit Jahrestreffen Reaktionstechnik, Weimar (16.-18.3.2011), poster

Brückner, B.; Gerlach, G.; Winkler, A.; Hu, W.; Hufenbach, W.A.; Michaelis, A.; Modler, N.; Schönecker, A.; Suchaneck, G. Novel approaches for the deter-

mination of the process specific polarization of piezoceramic modules embedded in thermoplastic composites

3rd Scientific Symposium CRC/Transregio 39 PT-PIESA – Integration of active functions into structural components, Chemnitz (12./13.10.2011), p.91-96, present.

Burkhardt, T.; Bruchmann, C.; Kamm, A.; Hornaff, M.; Beckert, E.; Gebhardt, S.; Müller, J.; Hoffmann, M.; Eberhardt, R.; Tünnermann, A. Smarte adaptive-optische Mikro-

systeme – Aufbautechnologie und thermomechanische Charakterisierung

Mikrosystemtechnik-Kongress 2011, Darmstadt (10.-12.10.2011), presentation

Busch, J.; Meißner, T.; Potthoff, A.; Oswald, S.

Plating of nano zero-valent iron (nZVI) on activated carbon: A fast delivery method of iron for source remediation GeoHydro, Quebec, Canada

(28.-31.8.2011), poster

Buß, W.; Richter, H.; Bartnitzek, T.; Brode, W.; Heymel, A.; Walther, T. Embossed ceramic reflectors with nano dispersive coatings for compact optoelectronic systems

IMAPS European Microelectronics Packaging Conference – EMPC-2011, Brighton, UK (12.-15.9.2011), poster

Conze, S.; Schnelle, W.; Veremchuk, I.; Michaelis, A.; Grin, Y.; Kinski, I. Herstellung von Titansuboxiden über die Precursorenroute Workshop »ECEMP – European Centre for Emerging Materials and Processes Keramik/Energie«, Dresden (29.6.2011), presentation

Conze, S.; Veremchuk, I.; Koban, R.; Michaelis, A.; Grin, Y.; Kinski, I.

Microstructure of precursor-derived titanium suboxides for the application as thermoelectric material

Frühjahresschule Thermoelektrik, Köln (28.3.-1.4.2011), poster

Conze, S.; Veremchuk, I.; Schnelle, W.; Michaelis, A.; Grin, Y.; Kinski, I. Precursor-derived titanium oxides – as thermoelectrics

9th European Conference on Thermoelectrics, Thessaloniki, Greece (28.-30.9.2011), poster

de Moraes, I.R.; Scholz, S.; Lüssem, B.; Leo, K.

Observation of a common degradation mechanism within the oxygen free and Ir-based green phosphorescent emitter Ir(ppy)3 in organic light emitting diodes 4th International Symposium on flexible Organic Electronics – ISFOE11, Thessaloniki, Greece (10.-13.7.2011), presentation

de Moraes, I.R.; Seifert, R.; Scholz, S.; Lüssem, B.; Leo, K. Photoinduced degradation process of Fir6 emitter molecules: A laser desorption/ionization timeof-flight mass spectrometry investigation

75. Jahrestagung der DPG, Frühjahrstagung der Sektion AMOP (SAMOP) und der Sektion Kondensierte Materie (SKM), Dresden (13.-18.3.2011), presentation

Dietrich, S.; Kusnezoff, M.; Ziesche, S.

Wärmeleitfähigkeitsdetektoren – Array zur selektiven Gasanalyse 10. Dresdner Sensor Symposium – DSS, Dresden (5.-7.12.2011), presentation

Eberstein, M.; Seuthe, T.; Schilm, J. Glas in Silberpasten zur Frontseitenmetallisierung von Solarzellen 85. Glastechnische Tagung der Deutschen Glastechnischen Gesellschaft (DGG), Saarbrücken (30.5.-1.6.2011), presentation

Eberstein, M.; Geier, M.;
Partsch, U.; Völkel, L.; Böhme, R.;
Mann, G.; Bonse, J.; Krüger, J.;
Pentzien, S.; Koter, R.
Towards an industrial laser dopingprocess for the selective emitter using phosphoric acid as dopant

26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), presentation Eckhard, S.; Fries, M.; Svoboda, H.; Nebelung, M.

Investigation of the influence of different organics combination on processing properties of spray dried ceramic granules
5th International Granulation Conference, Lausanne, Switzerland (20.-22.6.2011), presentation

Eckhard, S.; Fries, M.; Lenzner, K. Variation der Produkteigenschaften sprühgetrockneter nanoskaliger SiO₂-Granulate 5. Symposium Partikeltechnologie, Pfinztal (19./20.5.2011), p.219-229, presentation

Ehrt, R.; Johannes, M.

Verblendung von Zirkoniumdioxid mittels pulverisierter Lithiumdisilicat-Glaskeramik

9. Treffen des DGG-DKG AK Glasigkristalline Multifunktionswerkstoffe, Offenbach (24./25.2.2011), present.

Eilers, J.; Zhang, X.; Uhlig, S.; Kinski, I.; Michaelis, A.; Weber, J. Transparentes p-leitfähiges Zinkoxid für die Photovoltaik Zukunft Energie, Dresden (11.-13.5.2011), poster

Endler, I.

Manufacturing and applications
of vertical aligned carbon nanotubes (va-CNT)

PT-PIESA-Workshop »Hochleis-

tungswerkstoffe« des SFB Transregio 39 »PT-Piesa«, Dresden (21.9.2011), presentation

Endler, I.; Meißner, F.

Manufacturing and applications
of vertical aligned carbon nanotubes

International Symposium on Piezocomposite Applications – ISPA 2011, Dresden (22./23.9.2011), presentation

Endler, I.; Höhn, M.

Neue Entwicklungen bei CVD-Verschleißschutzschichten Workshopwoche Vakuumbeschichtung und Plasmaoberflächentechnik – V2011, Dresden (17-20.10.2011), presentation

Ernst, D.; Bramlage, B.; Gebhardt, S. Development of high performance PZT thick film actuators International Symposium on Piezocomposite Applications – ISPA 2011, Dresden (22./23.9.2011), poster

Faßauer, B.; Lincke, M.; Schwarz, B.; Wufka, A.; Friedrich, E. Erhöhte und bedarfsorientierte Biogasproduktion auf Basis des DECONDIS-Verfahrens
6. Fachtagung Biogas 2011 – Energieträger der Zukunft,

Braunschweig (8./9.6.2011), poster

Wasserqualität und deren Beeinflussung

Wasser in der Lausitz, Lauta (2.12.2011), presentation

Faßauer, B.

Feng, B.; Martin, H.-P.;
Hempel-Weber, R.; Michaelis, A.
Preparation and thermoelectric
properties of B₄C-Si-B composites
9th European Conference on Thermoelectrics, Thessaloniki, Greece
(28.-30.9.2011), poster

Fischer, G.; Häusler, A.; Voigt, I.; Richter, H.; Richter, H.-J.; Adler, J. Extrusion of porous ceramic materials

III. International Research and Practice Conference and Specialized Exhibition on Modern Ceramic Materials, Properties, Technology, Applications, Novosibirsk, Russia (14.-19.9.2011), presentation

Fischer, G.; Dohndorf, H.; Häusler, A.; Köhler, B.; Lauenroth, S.

Qualifizierung eines alternativen Porenbildners zur Herstellung offenporiger (großvolumiger) keramisch gebundener Schleifwerkzeuge

Jahrestagung 2011 der Forschungsgemeinschaft Schleiftechnik, Würzburg (24.3.2011), presentation

Fischer, M.; Mache, T.; Bartsch, H.; Müller, J.; Pawlowski, B.; Barth, S. SiCer – an advanced substrate for 3D integrated nano and micro systems

European Conference & Exhibition on Integration Issues of Miniaturized Systems – SSI 2011, Dresden (22./23.3.2011), presentation

Flössel, M.; Gebhardt, S.; Schönecker, A.; Michaelis, A. Development of LPMs (LTCC/PZT Modules)

International Symposium on Piezocomposite Applications – ISPA , Dresden (22./23.9.2011), poster

Flössel, M.; Gebhardt, S.; Schönecker, A.; Michaelis, A. Investigation on LTCC/PZT interface in a novel-actuator-module for metal die casting 20th IEEE International Symposium

20th IEEE International Symposium on Applications of Ferroelectrics jointly held with the International Symposium on Piezoresponse Force Microscopy – ISAF PFM 2011, Vancouver, Canada (24.-27.7.2011), presentation

Fries, M.

Charakterisierung und Vergleich der Eigenschaften von Granulaten aus unterschiedlichen Herstellungsverfahren

DKG-Herbstsymposium »Charakterisierungsverfahren in der kerami-

schen Aufbereitung: Vom Pulver bis zum Grünkörper«, Erlangen (29./30.11.2011), presentation

Fries, M.

Produktdesign keramischer

Pressgranulate

DKG-Fortbildungsseminar »Sprühtrocknung«, Dresden (8./9.11.2011), presentation

Fries, M. **Pulveraufbereitung**

Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Fries, M.

Sprühtrocknung in der Keramik

DKG-Fortbildungsseminar »Sprühtrocknung«, Dresden

(8./9.11.2011), presentation

Fries, M.

Thermische Granulationsverfah-

ren – Einführung, Sprühtrocknung

DKG-Fortbildungsseminar »Technologische Grundlagen der Granulierung und Granulatverarbeitung«, Dresden (14./15.4.2011), presentation

Fritsch, M.; Kusnezoff, M.; Schneider, M.; Weiser, M.; Michaelis, A. Supercap – Kompositelektroden Zukunft Energie, Dresden (11.-13.5.2011), presentation

Füssel, A.; Adler, J.; Belitz, R.; Marschallek, F.; Pohl, M.; Jahn, M.; Michaelis, A. Aktuelle Materialentwicklung

von SiC-Schaumkeramik für Hochtemperaturanwendungen 4. Sächsischer Brennstoffzellentag, Leipzig (10.11.2011), presentation

Füssel, A.; Böttge, D.; Adler, J.; Michaelis, A. Siliciumcarbid-Schaumkeramik für Hochtemperaturanwendun-

Workshop »Funktionelle Materialien für die chemische Technik«, Dresden (6.10.2011), poster

gen

Ganzer, G.; Beckert, W.; Pfeifer, T.; Michaelis, A. Multiphysics simulation of an

anode-supported micro-tubular solid oxide fuel cell (SOFC) Comsol Conference, Stuttgart (26.-28.10.2011), presentation

Ganzer, G.; Beckert, W.

Rechnergestützte Modellierung
von Hochtemperatur-Brennstoffzellen

Fachtagung Regenerative Energie als Zukunftstechnologie, Köthen (13.-14.10.2011), presentation Gebhardt, S.; Flössel, M.;
Schönecker, A.; Michaelis, A.
Design and Characterization of
LTCC/PZT modules (LMPs) for
sensor and actuator applications
3rd Scientific Symposium
CRC/Transregio 39 PT-PIESA – Integration of active functions into
structural components, Chemnitz
(12./13.10.2011), presentation

Integrated piezoelectrics based on PZT thick films: Advantages and limitations

Gebhardt S

International Symposium on Piezocomposite Applications – ISPA 2011, Dresden (22./23.9.2011), presentation

Geier, M.; Eberstein, M.;
Partsch, U.; Völkel, L.; Böhme, R.;
Mann, G.; Bonse, J.; Krüger, J.
Impact of laser treatment on
phosphoric acid coated multicrystalline silicon PV wafers
26th European Photovoltaic Solar
Energy Conference and Exhibition –
EU PVSEC, Hamburg (5.-9.9.2011),
poster

Gestrich, T.

Grundlagen der Thermoanalytik:
Optimierung der Entbinderungsund Sinterprozessen

DKG-Fortbildungsseminar »Thermoplastische Formgebung von Technischer Keramik«, Dresden (5.-6.10.2011), presentation

Gestrich, T.; Jaenicke-Rößler, K.; Herrmann, M.

High temperature corrosion of hardmetals

Powder Metallurgy Congress and Exhibition – Euro PM2011, Barcelona, Spain (9.-12.10.2011), presentation

Gestrich, T.; Jaenicke-Rößler, K.; Leitner, G.; van den Berg, H.; Rödiger, K.

Reaktionen und Praxis beim Sintern von Hartmetallen

30. Hagener Symposium Pulvermetallurgie mit Fachausstellung – Sintern – der zentrale Prozess der Pulvermetallurgie, Hagen (24./25.11.2011), presentation

Gestrich, T.

Thermoanalytik zur Optimierung der Entbinderungsprozesse DKG-Fortbildungsseminar »Entbinderung keramischer Formteile«, Dresden (6./7.10.2011), presentation

Glöß, B.; Fries, M.; Nebelung, M. Flow properties of spray dried granules in dependence of production conditions Powder Flow 2011, London, UK

(6.12.2011), poster

Goldberg, A.

The multilayer technology as integration system for ceramic micro fuel cells

IMAPS European Microelectronics

Packaging Conference – EMPC
2011, Brighton, UK

(12.-15.9.2011), presentation

Günther, C.; Richter, H.; Voigt, I. Entwicklung von Zeolithmembranen für die precombustion Gasaufbereitung in Kraftwerksanlagen

Thüringer Werkstofftag, Jena (30.3.2011), poster

Günther, C.; Richter, H.; Voigt, I.

H₂-permeable zeolite

membranes

23. Deutsche Zeolithtagung, Erlan-

gen (2.-4.3.2011), poster

Dresdner Werkstoffsymposium,

Dresden (9./10.12.2010), poster

Network Young Membranes 2011,

Amsterdam, the Netherlands
(21.07.-23.7.2011), presentation

Haderk, K.; Scheithauer, U.; Richter, H.-J.; Petasch, U.; Zins, M.; Michaelis, A.

Development of graded porous calcium aluminate ceramics by ceramic tape technology for thermal shock resistant refractory materials

17th International Conference on

Refractories, Praha, Czech Republic (10./11.5.2011), presentation

Haderk, K.

Development of graded porous calcium aluminate ceramics by ceramic tape technology for thermal shock resistant refractory materials

54. Internationales Feuerfest-Kolloquium 2011, Aachen (19./20.10.2011), presentation

Heddrich, M.

System tests and operation control strategies of an SOFC-CHPdevice for field testing 219th Electrochemical Society Mee

219th Electrochemical Society Meeting, Montréal, Canada (1.-6.5.2011), poster

Heddrich, M.; Jahn, M.; Michaelis, A.; Reichelt, E. Thermodynamic influence analysis of available fuels and reforming methods on SOFC system efficiency

12th International Symposium on Solid Oxide Fuel Cells – SOFC-XII, Montreal, Canada (1.-6.5.2011), p.955-962, presentation

Hermann, K.; Voigt, I.; Weyd, M.; Duscher, S.; Prehn, V. Pflege heißer, hochalkalischer Flaschenreinigungsbäder durch Einsatz keramischer Membranen DECHEMA/DWA Industrietage Wassertechnik, Frankfurt (7./8.11.2011), presentation

Herrmann, M.; Höhn, M.; Sempf, K.; Matthey, B. Artefaktfreie Präparation und Charakterisierung von keramischen Oberflächen und Interfaces

6. Höhr-Grenzhäuser Keramik-Symposium, Höhr-Grenzhausen (29./30.9.2011), Eingeladener presentation

Herrmann, M.; Sempf, K.; Blug, B.; Höfer, M.; Schäfer, L.; Schrüfer, A; Otschick, J.

DiaCer materials – New materials for a wide range of challenging applications

European Symposium on Friction, Wear and Wear Protection 2011, Karlsruhe (25.-28.10.2011), present.

Herrmann, M.; Matthey, B.; Höhn, S.

Diamant-Keramik Komposite – Neue Werkstoffe für Verschleißanwendungen

DGM/DKG-Symposium Hochleistungskeramik »Hochleistungskeramik »Hochleistungskeramik als Systemkomponenten«:
Abschlusskolloquium des SFB 483
»Hochbeanspruchte Gleit- und Friktionssysteme auf der Basis ingenieurwissenschaftlicher
Werkstoffe«, Karlsruhe
(25./26.10.2011), presentation

Herrmann, M.

Diamond-ceramic-composites – new materials for wide range of applications

Engineering Ceramics 2011 from Materials to Components, Smolenice Castle, Slovakia (8.-12.5.2011), Eingeladener presentation

Herrmann, M.

Gefügedarstellung und -bewertung

Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Freiburg (10./11.11.2011), presentation

Herrmann, M.; Schilm, J.

Hochleistungskeramik für
korrosive Anwendungen
Schulungsprogramm des
Fraunhofer-Demonstrationszentrums AdvanCer, Dresden
(9./10.3.2011), presentation

Herrmann, M.; Gestrich, T.; Neher, R.; Höhn, S.; Michaelis, A. Sintern von Nichtoxidkeramik 30. Hagener Symposium Pulvermetallurgie mit Fachausstellung – Sintern – der zentrale Prozess der Pulvermetallurgie, Hagen (24./25.11.2011), Eingeladener presentation

Herrmann, M.

Structural ceramics – high performance materials for a wide

range of applications

62. Berg- und Hüttenmännischer Tag – Freiberger Forschungsforum, Freiberg (15.-17.6.2011), presentation

Herrmann, M.

Thermische Entbinderungsprozesse: Mechanismen – Methoden – Verfahren

DKG-Fortbildungsseminar »Entbinderung keramischer Formteile«, Dresden (6./7.10.2011), present.

Hildebrandt, S.; Michaelis, A.; Kinski, I.

Kontaktlose Druckverfahren für Metallisierungen am Fraunhofer IKTS – Contactless printing methods for metallization at Fraunhofer IKTS

Nano Goes Makro, Erfurt (10.2.2011), presentation

Hildebrandt, S.; Waltinger, A.; Geier, M.; Eberstein, M.; Mosch, S.; Partsch, U.; Michaelis, A.; Kinski, I. Seedlayer deposition of a novel particle-free nickel ink 26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), p.1803, poster

Himpel, G.

Entbinderungs- und Sintertechnik für spritzgegossene Keramik DKG-Fortbildungsseminar »Thermoplastische Formgebung von Technischer Keramik«, Dresden (5./6.10.2011), presentation

Himpel, G.

Entbinderungstechnik

DKG-Fortbildungsseminar »Entbinderung keramischer Formteile«, Dresden (6./7.10.2011), presentation

Hohlfeld, K.; Gebhardt, S.; Michaelis, A.

Piezoelectric composites based on free-formed PZT elements International Symposium on Piezocomposite Applications – ISPA 2011, Dresden (22./23.9.2011), poster

Höhn, S.

Charakterisierung der Formkörper: Defektentstehung, Nachweis, Vermeidung

DKG-Fortbildungsseminar »Entbinderung keramischer Formteile«, Dresden (6./7.10.2011), present.

Höhn, S.; Herrmann, M.

Charakterisierung von Granulatund Grünkörperstrukturen über Ionenstrahlpräparation und bildanalytische Verfahren

DKG-Herbstsymposium »Charakterisierungsverfahren in der keramischen Aufbereitung: Vom Pulver bis zum Grünkörper«, Erlangen

(29./30.11.2011), presentation

Höhn, S.; Eckhard, S.; Fries, M.; Matthey, B.

Quantification on internal structures of spray-dried granules

12th Conference of the European Ceramic Society – ECerS XII, Stockholm, Sweden (19.-23.6.2011), presentation

Hu, W.; Flössel, M.; Suchanek, G.; Jaenicke-Rößler, K.; Gebhardt, S.; Schönecker, A.; Gerlach, G. Determination of the polarization state in LTCC/PZT piezoelectric sensor-actuator modules International Conference 'PIEZO 2011-Electroceramics for End-Users VI', Sestriere, Italy (28.2.-2.3.2011), presentation

Hufenbach, W.; Fischer, W.-J.;
Michaelis, A.; Gebhardt, S.;
Geller, S.; Tyczynski, T.; Heinig, A.;
Weder, A.; Hohlfeld, K.
Integration of piezoceramic and electronic functional elements in glass fibre-reinforced polyure-thane composite structures
3rd Scientific Symposium
CRC/Transregio 39 PT-PIESA – Integration of active functions into structural components, Chemnitz
(12./13.10.2011), poster

Jackschik, S.; Benner, F.; Kupke, S.; Endler, I.; Mikolajik, T. Dielectric backside passivation – guidance for improvements

26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), 2CV.4.41, poster

Jobst, K.; Deutschmann, A.; Friedrich, E.

Optimierung von Mischprozessen zur Biogaserzeugung – Ein Beitrag zur Steigerung der Effizienz von Biogasanlagen 4. Innovationskongress Biogas 2011, Osnabrück (12./13.5.2011),

Jobst, K.

Optimierung von Mischprozessen zur Biogaserzeugung

p.99-104, presentation

6. Fachtagung Biogas 2011 – Energieträger der Zukunft, Braunschweig (8./9.6.2011), poster

Jobst, K.; Deutschmann, A.; Lincke, M.; Lomtscher, A.; Eberhard, F.

Optimierung von Mischprozessen zur Biogaserzeugung

Fachtagung Regenerative Energie als Zukunftstechnologie, Köthen (13./14.10.2011), poster

Johannes, M.; Lausch, H.; Sandkuhl, O.; Rudolph, H.; Udart, M.; Herold, V. Strukturierung keramischer Implantatoberflächen mittels Schlickerguss Zukunftsarena Oberflächentechnik und 8. Thüringer Biomaterial-Kolloquium 2011, Zeulenroda/Triebes (13.-15.9.011), poster

Johannes, M.; Sandkuhl, O. Strukturierung von Hochleistungskeramik mittels Schlickerguss

DKG-Jahrestagung Saarbrücken (28.-30.3.2011), poster

Junige, M.; Knaut, M.; Geidel, M.; Riedel, S.; Endler, I.; Wojcik, H.; Albert, M.; Merkel, U.; Bartha, J.W. Characterization of ruthenium ALD and PVD thin films for insitu process control by spectroscopic ellipsometry

6. Workshop Ellipsometry des Arbeitskreises Ellipsometrie Paul Drude e.V. (AKE), Berlin (21.-24.2.2011), presentation

Kämnitz, S.; Kaltenborn, N.; Richter, H.; Voigt, I. Adsorption selective carbon membranes on ceramic supports International Congress on Membranes and Membrane Processes – ICOM, Amsterdam, the Netherlands (23.-29.7.2011), poster

Keitel, U.

Characterization of fluid devices International Symposium on Piezocomposite Applications – ISPA 2011, Dresden (22./23.9.2011), presentation

Khavrus, V.O.; Weiser, M.; Fritsch, M.; Ummethala, R.; Salvaggio, M.G.; Schneider, M.; Kusnezoff, M.; Leonhardt, A. CCVD of aligned carbon nanotubes on aluminium foils and their test as components of supercapacitors

International Conference on the Science and Application of Nanotubes – NT11, Cambridge, UK (10.-16.7.2011), poster

Khavrus, V.O.; Weiser, M.;
Fritsch, M.; Ummethala, R.;
Salvaggio, M.G.; Schneider, M.;
Kusnezoff, M.; Leonhardt, A.
Direct growth of aligned carbon
nanotubes on aluminium foils
and their application as components of supercapacitors
4th International Conference on
Carbons for Energy Storage/
Conversion and Environment Pro-

Kinski, I.; Meinhard, S.; Henke, B.; Herrmann, M.; Schweizer, S. Nano-crystalline SrAI₂O₄ persistent phosphors doped with EU²⁺ and Dy³⁺

tection - CESEP, Vichy, France

(25.-29.9.2011), presentation

219th Electrochemical Society Meeting, Montréal, Canada (1.-6.5.2011), presentation Kircheisen, R.; Schulz, M.;
Kriegel, R; Töpfer, J.
Sauerstoffstöchiometrie, Sauerstofffluss und CO₂-Stabilität von
Sr(Co_{0.8}Fe_{0.2})_{1-x}Ti_xO_{3.6} für sauerstoffpermeable Membranen
DKG-Jahrestagung, Saarbrücken
(28.-30.03.2011), presentation
Symposium Hochleistungskeramik,
Karlsruhe (25./26.10.2011), poster

Bartnitzek, T.; Pawlowski, B.; Kipka, A.; Moos, R. Development of a novel LTCCchip for fast DSC-analysis IMAPS/ACerS 7th International Conference and Exhibition on Ceramic Interconnect and Ceramic Microsystems Technologies – CICMT 2011, San Diego, California, USA

Kita, J.; Missal, W.; Wappler, E.;

Klemm, H.

(5.-7.4.2011), poster

Development of ceramic materials for gas turbine applications
4th German-Polish Colloquium
Science and Art in Europe,
Otzenhausen (19.-22.10.2011),
presentation

Klemm, H.; Bales, A.; Nake, K.; Michael, G.

High-temperature characterization of ceramic materials by hothardness measurement

35th International Conference and Exposition on Advanced Ceramics

and Composites – ICACC 2011, Daytona Beach, Florida, USA (23.-28.1.2011), presentation

Klemm, H.

Hochleistungskeramik für Hochtemperaturanwendungen

Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Klemm, H.; Nake, K.; Bales, A.; Michael, G.

Hochtemperaturcharakterisierung von keramischen Werkstoffen durch Wärmehärtemessung

Fachausschusssitzung FA 12 Härteprüfung, Dresden (23./24.3.2011), presentation

Klemm, H.; Kunz, W.; Bales, A.; Oberländer, A.; Schönfeld, K.; Michaelis, A.

Hot gas corrosion of non-oxide ceramic fibre composites

9th International Meeting of Pacific Rim Ceramic Societies – PacRim 9, Cairns, North Queensland, Australia (10.-14.7.2011), presentation

Klemm, H.

Keramische Faserverbundwerkstoffe am IKTS

21. Kuratoriumssitzung, Fraunhofer IKTS, Dresden (10.5.2011), presentation

Klemm, H.; Schönfeld, K.; Herrmann, M.; Lippmann, W. Keramische Faserverbundwerkstoffe für Hochtemperaturanwendungen

Zukunft Energie, Dresden (11.-13.5.2011), presentation

Klemm, H.

Low-cost-Technologien zur Herstellung von Bauteilen aus keramischen Faserverbundwerkstoffen

Fraunhofer-Symposium »Netzwert« 2011, München (28./29.11.2011), presentation

Klemm, H.; Müller, A.

Material- und Verfahrensentwicklung von kostengünstigen
kurzfaserverstärkten Verbundwerkstoffen

6. MV Ceramic Composites im CCeV, Dresden (10./11.10.2011), presentation

Klemm, H.; Kunz, W.; Bales, A.; Oberländer, A.; Schönfeld, K.; Michaelis, A.

Non-oxide ceramic fibre composites

9th International Meeting of Pacific Rim Ceramic Societies – PacRim 9, Cairns, North Queensland, Australia (10.-14.7.2011), presentation

Krell, A.; Wätzig, K.; Klimke, J. Effects and elimination of nano-

porosity in transparent sintered spinel (MgAl₂O₄)

SPIE Defense, Security + Sensing, Window & Dome Technologies and Materials XII, Orlando, Florida, USA (25.-29.4.2011), Paper 801602, presentation

Krell, A.

Hochleistungskeramik für Verschleißanwendungen

Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Krell, A.; Wätzig, K.; Klimke, J.
Influence of the structure of
MgO·nAl₂O₃ spinel lattices on
transparent ceramics processing
and properties

12th Conference of the European Ceramic Society – ECerS XII, Stockholm, Sweden (19.-23.6.2011), presentation

Kriegel, R.; Schulz, M.; Ritter, K.; Kiesel, L.; Pippardt, U.; Stahn, M.; Voigt, I.

Advanced membrane design for oxygen separation

2nd International Conference on Energy Process Engineering, Efficient Carbon Capture for Coal Power Plants, Frankfurt/Main (20.-22.6.2011), presentation Kriegel, R., Voigt, I.

Demonstration of oxygen separation with BSCF membranes

12. Jülicher Werkstoffsymposium (5./6.9.2011), presentation

Kriegel, R.

Entwicklung und Musterfertigung sauerstoffpermeabler keramischer Membranen

22. Treffen des Arbeitskreises »Keramische Membranen«, Frankfurt/Main (5.5.2011), present.

Kriegel, R.; Schulz, M.; Voigt, I.; Sommer, E.

Sauerstoff-Membranen in Kleinanwendungen – Ein Einstieg in die Kommerzialisierung?

Thüringer Werkstofftag 2011, Jena (30.3.2011), poster

Krug, M.

ALD deposition of passivation layers

Novel High k Application Workshop, Dresden (30.3.2011), present.

Kucera, A.

Deep drawing and embossing of tapes

Public Workshop on Tape Assembly, Stockholm, Sweden (29.3.2011), presentation

Kucera, A.; Richter, H.-J.; Moritz, T. Structuring of UV-curable ceramic green tapes 4M 2011 Conference, Stuttgart (8.-10.11.2011), presentation

Kucera, A.; Richter, H.-J.; Moritz, T. Development of UV curable alumina tapes and their 3D structuring

12th Conference of the European Ceramic Society – ECerS XII, Stockholm, Sweden (19.-23.6.2011), poster

Kühnert, J-T.; Voigt, I.; Richter, H.; Weyd, M.; Tusel, E.; Brüschke, H.E.A. Progress in NaA-zeolite membrane preparation and implementation in the bioethanol production process

International Congress on Membranes and Membrane Processes,
Amsterdam, the Netherlands
(23.-29.7.2011), poster

Kühnert, J-T.; Weyd, M.; Richter, H.; Voigt, I.; Tusel, E.; Brüschke, H.E.A. Evolution of membrane supports for dewatering of ethanol International Scientific Conference on Pervaporation, Vapor Permeation and Membrane Distillation, Torun, Poland (8.-11.9.2011), presentation

Kusnezoff, M.; Michaelis, A.; Trofimenko, N. Electrochemical phenomenain

MEA electrodes

Widjaja, Sujanto (Ed.) u.a.; The American Ceramic Society (ACerS): 35th International Conference and Exposition on Advanced Ceramics and Composites – ICACC 2011, Daytona Beach, Florida, USA (23.-28.1.2011), No.4, p.37-60, presentation

Kusnezoff, M.; Sauchuk, V.; Michaelis, A.; Berger, L.-M.; Scheitz, S.; Toma, L.-F. Maßgeschneiderte keramische Schichtheizelemente, hergestellt durch thermisches Spritzen DKG-Jahrestagung 2011, Saarbrücken (28.-30.3.2011), presentation

Lackner, G.; Endler, I.; Meißner, F.; Shvartsman, V.V.; Bezugly, V.; Boucher, R.; Thieme, M.; Mkandawire, M.; Meiss, J.; Pfützner, S.; Michaelis, A.; Lupascu, D.C.

Carbon naotubes in solar cell application

26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), poster

Lackner, G.; Endler, I.; Meißner, F.; Avdoshenko, S.M.; Bezugly, V.; Boucher, R.; Mkandawire, M.; Meiss, J.; Pfützner, S.; Mayer-Uhma, T.; Michaelis, A.; Lupascu, D.C. Carbon nanotubes in solar cell application

2nd International Conference Organic Photovoltaics, Würzburg (21.9.2011), poster

Lackner, G.; Endler, I.; Meißner, F.; Bezugly, V.; Boucher, R.; Lapascu, D.C. Infiltration study of verticallyaligned carbon nanotube forest (va-CNT) with different organic semiconductor materials forming a composite

9th Ferrocene Colloquium, Chemnitz (14.-16.2.2011), present.

Langklotz, U.; Schneider, M.; Seifert, C.; Michaelis, A. Ramanspektroskopie an foliengegossenem LCO-Elektrodenmaterial

Zukunft Energie, Dresden (11.-13.5.2011), poster

Langklotz, U.; Schneider, M.; Michaelis, A.

Thickness dependency of the relative permittivity $\boldsymbol{\epsilon}_{r}$ of very thin oxide films investigated by micro-EIS

International Workshop on Impedance Spectroscopy – IWIS 2011, Chemnitz (28.-30.9.2011), present.

Lankau, V.; Martin, H.-P.

Charakterisierung und Modifikation der elektrischen Eigenschaf-

ten von festphasen-gesintertem SiC

DGM/DKG-Symposium Hochleistungskeramik »Hochleistungskeramik »Hochleistungskeramik als Systemkomponenten« in Verbindung mit dem Abschlusskolloquium des SFB 483 »Hochbeanspruchte Gleit- und Friktionssysteme auf der Basis ingenieurwissenschaftlicher Werkstoffe«, Karlsruhe (25./26.10.2011), poster

Lenz, C.; Ziesche, S.; Partsch, U. Piezoresistive Miniaturkraftsensoren in LTCC

Dresdner Sensor Symposium –
 DSS, Dresden (5.-7.12.2011), poster

Lenzner, K.; Glöß, B.; Eckhard, S. **Granulatcharakterisierung** DKG-Fortbildungsseminar »Technologische Grundlagen der Granulierung und Granulatverarbeitung«, Dresden (14./15.4.2011), presentation

Lenzner, K.; Glöß, B.; Eckhard, S. Granulatcharakterisierung – Werkzeug für Optimierung von Produktentwicklung und Sprühprozessen

DKG-Fortbildungsseminar »Sprühtrocknung«, Dresden (8./9.11.2011), presentation

Lincke, M.; Fassauer, B.; Schwarz, B.; Wufka, A.; Friedrich, E.; Jobst, K.

Erhöhte und bedarfsorientierte Biogasproduktion auf Basis des DECONDIS-Verfahrens: Optimierung von Mischprozessen zur Biogaserzeugung

6. Fachtagung Biogas 2011 Energieträger der Zukunft, Braunschweig (8./9.6.2011), presentation

Lomtscher, A.; Jobst, K.; Friedrich, E.

Bewertung von Mischprozessen mittels Prozess-Tomographie: Ein neuer Weg zur Optimierung von Rührprozessen

14. Köthener Rührer-Kolloquium, Köthen (16.6.2011), presentation

Lubkowski, G.; Kuhnhenn, J.; Suhrke, M.; Weinand, U.; Endler, I.; Meißner, F.; Richter, S. Gamma radiation effects in vertically aligned carbon nanotubes Conference on Radiation Effects on Components and Systems – RADECS, Sevilla, Spain

(19.-23.9.2011), poster

Mannschatz, A.; Ahlhelm, M.; Moritz, T.; Michaelis, A. 3D visualization of flow pattern in injection molded green parts International Conference on Injection Molding of Metals – MIM2011, Ceramics and Carbides, Orlando, USA (14.-16.3.2011), presentation Mannschatz, A.; Moritz, T.; Jegust, S.; von Witzleben, M. Enabling co-sintering of ATZ/ZTA ceramic compounds by twocompoent injection moulding with intermediate green tapes Powder Metallurgy Congress and Exhibition – Euro PM2011, Barcelona, Spain (9.-12.10.2011), presentation

Marschallek, F.; Adler, J.; Böttge, D.; Füssel, A.; Jahn, M.; Michaelis, A. Combustion in porous media – advances in process design and materials longterm stability
8th European Congress of Chemical Engineering – ECCE, Berlin (25.-29.9.2011), poster

Martin, H.-P.; Schilm, J.;
Dannowski, M.; Pfeiffer, P.
Keramikbasierte thermoelektrische Generatoren für Fahrzeuge
9. Dresdner Motorenkolloquium
»Der Dieselmotor – neue Herausforderungen«, Dresden
(8./9.6.2011), p.133-143,
presentation

Martin, H.-P.; Feng, B.; Conze, S.; Kinski, I. Keramische Thermoelektrika als Werkstoff für thermoelektrische Generatoren Zukunft Energie, Dresden

(11.-13.5.2011), presentation

Martin, H.-P.

Untersuchungen zu Ta-Ni-Legie-

rungen als Hochtemperaturlot für SiC-SiC Verbunde Workshop Hochtemperaturfügen 2011 – Anwenderkreis Hochtempe

2011 – Anwenderkreis Hochtemperaturfügen, ifw Jena (3.11.2011), presentation

Mayer-Uhma, T.; Potthoff, A.; Thieme, P. Chemical and physical characterization of slurry and variation of the zeta potential 26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011),

Meißner, F.; Endler, I.; Jakisch, L.; Thomas, J.; Schönecker, A.; Michaelis, A. Composites of aligned carbon nanotubes and polymers International Conference on the

poster

International Conference on the Science and Application of Nanotubes – NT11, Cambridge, UK (11.-16.7.2011), poster

Meißner, T.; Potthoff, A.

Characterization of iron-based nanomaterials in terms of ecoto-xicological relevance

6th International Conference on the Environmental Effects of Nanoparticles and Nanomaterials,

London, UK (19.-21.9.2011), poster

Meißner, T.

Chemical-physical nanoparticle characterization to promote to-xicological investigations
5th International Seminar »Nanotechnology, Energy, Plasma, Lasers« – NEPL-2011, Hermsdorf/Jena (1.-3.11.2011), presentation

Meißner, T.; Potthoff, A.

Fe-NANOSIT – Charakterisierung
von eisenbasierten Nanomaterialien

1. Clustertreffen NanoCare/Nano-Future, Frankfurt (10./11.5.2011), poster

Meulenberg, W.A.; Baumann, S.; Kriegel, R.

Processing and properties of asymmetric oxygen transport membranes

Werkstoffsymposium, Jülich (5./6.9.2011), presentation

Meulenberg, W.A.; Voigt, I.; Kriegel, R.; Baumann, S.; Ivanova, M.; van Gestel, T. Ceramic membranes for gas separation in advanced fossil power plants Efficient Carbon Capture for Coal

Power Plants, Frankfurt/Main (20.-22.6.2011), presentation

Michaelis, A.

Ceramic materials and technologies for fuel cells, batteries and

supercapacitors

Nanotech-Saxony Workshop der WFS, Tokyo, Japan (16.2.2011), presentation

Michaelis, A.

Ceramics for energy and environmental technology with focus on fuel cells, photovoltaics, energy storage systems and membranes

Third International Symposium on Advanced Ceramics and Technology for Sustainable Energy Applications – ACTSEA-2011, Pingtung, Taiwan (30.10.-2.11.2011), present.

Michaelis, A.

Hochleistungskeramik für die Energie- und Umwelttechnik Regionalforum Dresden im Rahmen des DGM-Tages, Dresden (16.6.2011), presentation

Michaelis, A.

Hochleistungskeramik für die Energie- und Umwelttechnologie

MFD-Materialforschungstournee 2010/2011, Dresden (12.1.2011), presentation

Michaelis, A.

Innovationspotenziale für High Tech Märkte durch Einsatz von Hochleistungskeramiken Entwicklung und Perspektiven der Keramik für High Tech Märkte, Ehrenkolloquium zum 60. Geburtstag von Frau Dr. Voigtsberger, Dresden (26.5.2011), presentation

Michaelis, A.

Systeme für die Energietechnologien: Photovoltaik, Batterien und Brennstoffzellen 11. Leibniz-Konferenz »Solarzeitalter 2011«, Lichtenwalde

(12./13.5.2011), presentation

Keramische Materialien und

Michaelis, A.

Keramische Materialien und Systeme für die innovative Energieund Umwelttechnologie EFDS-Hauptjahresversammlung, IKTS Dresden (22.11.2011), present.

Michaelis, A.

Technologien für den Aufbau von Lithium-Ionen-Batterien Workshop: »Technologien für die dezentrale Energiespeicherung«, Dresden (24.3.2011), presentation

Keramische Materialien und

Michaelis, A.

PV technology and the future Dutch-German Seminar on Energy Innovations, Dresden (14.4.2011), presentation

Michaelis, A.

Thickfilm and multilayer ceramic technology for innovative fuel cell systems

35th International Conference and Exposition on Advanced Ceramics and Composites – ICACC 2011, Daytona Beach, Florida, USA (23.-28.1.2011), presentation

Megel, S.; Kusnezoff, M.; Trofimenko, N.; Sauchuk, V.; Michaelis, A.; Venskutonis, A.; Rissbacher, K.; Kraussler, W.; Brandner, M.; Bienert, C.; Sigl, L.S. High efficiency CFY-stack for high power applications 12th International Symposium on

Solid Oxide Fuel Cells – SOFC-XII, Montreal, Canada (1.-6.5.2011), p.269-277, presentation and poster

Moos, R.; Missal, W.; Kita, J.; Wappler, E.; Gora, F.; Kipka, A.; Bartnitzek, T.; Bechtold, F.; Schabbel, D.; Pawlowski, B. Einweg-DSC-Chip

Sensor 2011, fms-Sondersession 2011, Workshop Sensorforschung für Medizin und Technik. Ergebnisse aus der industriellen Gemeinschaftsforschung, im Rahmen der Sensor + Test 2011, Nürnberg (9.6.2011), p.4-9,

Moritz, T.

presentation

Entwicklungstrends im Keramikspritzguss

Entdeckungsreise in eine Welt der Keramik, Koblenz (13.4.2011), presentation Moritz, T.

Fehlerquellen bei der Herstellung keramischer Werkstoffe Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Freiburg

(10./11.11.2011), presentation

Moritz, T.

Formgebung

Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Moritz, T.

Keramische Formgebung unter Verwendung organischer Additive

DKG-Fortbildungsseminar »Entbinderung keramischer Formteile«, Dresden (6./7.10.2011), presentation

Moritz, T.; Mannschatz, A.; Kucera, A.; Baumann, A.; Richter, H.-J.

Multifunctional ceramic component solutions by inmould labeling and multi component injection moulding

III. International Research and Practice Conference and Specialized Exhibition on Modern Ceramic Materials, Properties, Technology, Applications, Novosibirsk, Russia (14.-19.9.2011), presentation

Mosch, S.; Paproth, A.; Partsch, U.; Wolter, K.-J.

Chipanschlusskontaktierung mittels aerosolgedruckter Strukturen

Systemintegration in der Mikroelektronik »smt hybrid packaging«, Nürnberg (3.-5.5.2011), present.

Müller. A.

Injection moulding of carbon short-fibre filled preceramic polymers

Nanocomposite, Paris, France (7.6.-10.6.2011), presentation

Müller, A.

Injection moulding of carbon short-fibre filled preceramic polymers

Euromat 2011, Montpellier, France (12.-15.9.2011), presentation

Müller, S.; Richter, J.; Kaltenborn, N.; Richter, H.; Voigt, I. CNT-films on porous, ceramic membranes for gas separation Jahreskongress 2011 der Innovationsallianz Carbon Nanotubes (Inno.CNT), Karlsruhe (25.-27.1.2011), poster

Müller, S.; Richter, J.; Voigt. I. Entwicklung von CNT-Schichten für Anwendungen in der Gastrennung

Thüringer Werkstofftag, Jena (30.3.2011), poster

Näke, R.

Verfahrenstechnische Entwicklung und automatisierter Betrieb eines Biogas-SOFC-Systems 4. Sächsischer Brennstoffzellentag, Leipzig (10.11.2011), presentation

Oberländer, A.; Michaelis, A.; Pezzotti, G.; Kinski, I. Investigation of the structure and optical properties of cubic gallium oxynitride synthesized using a hydrothermal processing route

7th SRK Workshop on Advanced Materials, Busan, South Korea (10.-12.11.2011), presentation

Oehme, F.
Grünbearbeitung technischer
Hochleistungskeramik:
Methoden, Instrumente und
Entwicklungsrichtungen
Schulungsprogramm des
Fraunhofer-Demonstrationszentrums AdvanCer, Berlin
(4./5.5.2011), presentation

Oehme, F.

Hochpräzisionsbearbeitung
mittels Koordinatenschleifen
Schulungsprogramm des
Fraunhofer-Demonstrationszentrums AdvanCer, Block II:
Bearbeitung, Berlin (4./5.5.2011),

presentation

Ortmann, C.; Oberbach, T.; Richter, H.; Puhlfürß, P. Properties of infiltration prepared ZTA bioceramics

12th International Conference and Exhibition of the European Ceramic Society, Stockholm, Sweden (19.-23.6.2011), presentation

Partsch, U.

Multilayerbasierte Komponenten und Mikrosysteme

Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Pawlowski, L.; Börner, S. Entwicklungsbegleitende Charakterisierung von Rohstoffen und Schlickern in der Folienherstellung

DKG-Herbstsymposium »Charakterisierungsverfahren in der keramischen Aufbereitung: Vom Pulver bis zum Grünkörper«, Erlangen (29./30.11.2011), present.

Pawlowski, B.; Barth, S.; Fischer, M.; Bartsch, H.; Hoffmann, M.; Müller, J. SiCer – ein innovativer Substratwerkstoff für MEMS Thüringer Werkstofftag, Jena (30.3.2011), poster

Peschel, M.; Schilm, J.; Eberstein, M.; Kretzschmar, C.; Krause, J.; Völkel, L.; Partsch, U.; Michaelis, A.

Synthesis and characterisation of new lead-free glasses for the front metallization of solar cells 26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), poster

Peschel, M.; Schilm, J.;
Eberstein, M.; Kretzschmar, C.;
Krause, J.; Völkel, L.; Partsch, U.;
Michaelis, A.
Synthesis and evaluation of new

lead-free glasses for the front metallization of solar cells Materials Science & Technology 2011 Conference & Exhibition, Columbus, Ohio, USA (16.-20.10.2011), presentation

Peschel, M.

Synthesis and characterization of new lead-free low melt sealing glasses

85. Glastechnische Tagung der Deutschen Glastechnischen Gesellschaft, Saarbrücken (30.5.-1.6.2011), poster

Peschel, M.; Schilm, J.; Michaelis, A. Synthesis and characterization of new lead-free low melt sealing glasses

Materials Science & Technology 2011 Conference & Exhibition,

Columbus, Ohio, USA (16.-20.10.2011), poster

Pfeifer, T.; Nousch, L.

System design and process
layout for a SOFC micro-CHP
unit with reduced operating
temperature

European Fuel Cell 2011 Piero Lunghi Conference & Exhibition, Rome, Italy (14.-16.12.2011), presentation

Pigorsch, E.; Pensold, S.; Höhn, S. lon beam etching – A new high-resolution structural analysis method for paper coatings 106. Zellcheming-Jahrestagung, Wiesbaden (28.-30.6.2011), presentation

Pohl, M.

Fast start-up with ceramic fuel cell components

Beitrag zur Achema 2012, Frankfurt am Main (18.-22.6.2012), presentation

Pohl, M.; Jahn, M.; Michaelis, A.; Locke, C.

Prozessintensivierung in Hinblick auf das Temperaturverhalten eines SSiC-Katalysatorsystems bei der partiellen Oxidation 44. Jahrestreffen Deutscher Katalytiker mit Jahrestreffen Reaktionstechnik, Weimar (14.-18.3.2011), poster Pohl, M.

Zündverhalten edelmetallfreier katalytischer Schaumkeramik bei der partiellen Oxidation 44. Jahrestreffen Deutscher Katalytiker mit Jahrestreffen Reaktionstechnik, Weimar (14.-18.3.2011), poster

Pönicke, A.; Triebert, A.; Sempf, K.; Gestrich, T.; Schilm, J.; Martin, H.-P.; Böhm, G.; Schnee, D. Aktivlöten von Kupfer mit Aluminiumnitrid- und Siliziumnitridkeramik für die Hochleistungselektronik DKG-Jahrestagung 2011, Saarbrücken (28.-30.3.2011), presentation

Pönicke, A.; Arnold, S.; Schilm, J.; Kusnezoff, M. Mechanische Eigenschaften induktiv gelöteter YSZ-Metall-Verbunde mit Reaktivloten an Luft

2. W3-Kolloquium »Fügen von Metall, Keramik und Glas«, Hanau (29.11.2011), presentation

Pötschke, J.; Richter, V.; Holke, R. Efficacy of VC and CR₃C₂ grain growth inhibitors in sintering binderless WC

Powder Metallurgy Congress and Exhibition – Euro PM2011,

Barcelona, Spain

(9.-12.10.2011), poster

Posdziech, O.; Mai, B.E.; Wunderlich, C.; Voss, S. Status and market opportunities of solid oxide fuel cells based cogeneration systems International Gas Union Research

Conference - IGRC, Seoul, South

Korea (19.-21.10.2011), poster

Potthoff, A.; Meyer, A.
Charakterisierung des Aggregations- und Agglomerationszustandes nanoskaliger keramischer Partikel
DKG-Herbstsymposium

DKG-Herbstsymposium »Charakterisierungsverfahren in der keramischen Aufbereitung: Vom Pulver bis zum Grünkörper«, Erlangen (29./30.11.2011), present.

Potthoff, A.

Charakterisierung von Nanopartikeln

DGM-Fortbildungsseminar »Nanoanalytik«, Dresden (28.-29.11.2011), presentation

Potthoff, A.

Pulver- und Suspensionscharakterisierung

DKG-Fortbildungsseminar »Technlogische Grundlagen der Granulierung und Granulatverarbeitung«, Dresden (14./15.4.2011), presentation

Räthel, J.; Herrmann, M.

Temperature distribution during

FAST/SPS densification

12th Conference of the European Ceramic Society – ECerS XII, Stockholm, Sweden (19.-23.6.2011), presentation

Rabbow, T.J.; Wachtel, R.; Michaelis, A.; Stepowicz, J.K.; Eichler, R.; Decker, M.; Vonau, W.

Elektrochemische Abscheidung von Preußisch Blau für die Atemgasanalytik – Methodenvergleich und Schichtcharakterisierung

10. Dresdner Sensor Symposium – DSS, Dresden (5.-7.12.2011), poster

Rebenklau, L.

Aspekte der Aufbau- und Verbindungstechnik bei der Verbindungsbildung auf keramischen Dickschichtverdrahtungsträgern und LTCC-Substraten sowie Oberflächen auf der Basis polymerer Dickfilmpasten: Verfahrenscharakterisierung – Eigenschaftsmerkmale – Methoden und Verfahren

TAE-Seminar: Verbindungstechnologien der Aufbau- und Verbindungstechnik in der Elektronik,
Ostfildern-Nellingen (4.-6.7.2011),
presentation

Reichel, U.

Advanced biocompatible ceramics for implants ERA.Net RUS Pilot Joint Call,

Brokerage Event, Yekaterinburg, Russia (28.2.-2.3.2011), presentation

Reichel, U.

Advanced ceramic materials – history-present-prospects

III. International Research and Practice Conference and Specialized Exhibition on Modern Ceramic Materials, Properties, Technology, Applications, Novosibirsk, Russia (14.-19.9.2011), presentation

Reichel, U.

Ceramic nanomaterials – research & development

ERA.Net RUS Pilot Joint Call, Brokerage Event, Yekaterinburg, Russia (28.2.-2.3.2011), poster

Reichel, U.; Ludwig, H.; Kurland, H.-D.; Grabow, J.

DIREKT Heißpressen von nanoskaligen Y-TZP-Pulvern

DKG-Jahrestagung Saarbrücken (28.-30.3.2011), poster Reichel, U.; Ludwig, H.; Kurland, H.-D.; Grabow, J.; Müller, F.A.

DIREKT-Heißpressen nanoskaliger Y-TZP-Pulver

DGM Symposium Hochleistungskeramik, Karlsruhe (25./26.10.2011), poster

Reichel, U.

Durchsichtige Keramik: Vision oder Wirklichkeit?

407. JENAer Carl-Zeiss-Optikkolloquium, Jena (15.11.2011), present.

Reichel, U.; Ludwig, H.; Kemnitz, E.; Scholz, G.; Stosiek, C. Mikrostruktur und Eigenschaften

mit Nanometallfluorid dotierter Aluminiumoxid-Keramik

DGM-Symposium Hochleistungskeramik 2011, Karlsruhe (25./26.10.2011), presentation

Reichel, U.

Structure design of ceramic materials based on nanopowders

III. International Research and Practice Conference and Specialized Exhibition on Modern Ceramic Materials, Properties, Technology, Applications, Novosibirsk, Russia (14.-19.9.2011), presentation

Reinhardt, K.

AgPd pastes for AIN

IMAPS European Microelectronics Packaging Conference – EMPC-2011, Brighton, UK (12.-15.9.2011), presentation

Reinhardt, K.; Partsch, U.; Völkel, L. On the processing of hotmelt screen printing pastes

26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), poster Stelter, M.; Michaelis, A.

Portable micro-SOFC system

based on multilayer technology

Reuber, S.; Schneider, M.;

219th Electrochemical Society Meeting, Montréal, Canada (1.-6.5.2011), presentation

Reuber, S.; Schneider, M.; Stelter, M.; Michaelis, A. Portable µ-SOFC system based on multilayer technology

12th International Symposium on Solid Oxide Fuel Cells – SOFC-XII, Montreal, Canada (1.-6.5.2011), p.251-258, presentation

Richter, H.; Fischer, G.

Full zeolite bodies for zeolite membranes and adsorption applications

12th International Conference and Exhibition of the European Ceramic Society, Stockholm, Sweden (19.-23.6.2011), presentation

Richter, H.; Voigt, I.

Nanoporöse anorganische Membranen für enge Nanofiltration und Gastrennung

DKG-Arbeitskreis »Keramische Membranen«, Frankfurt/Main (5.5.2011), presentation

Richter, H.; Müller, S.; Kaltenborn, N.; Voigt, I. Tailoring of gas separating properties of carbon membranes

on ceramic substrates

4th International conference on carbons for energy storage/storage and environment protection (CESEP'11), Vichy, France (25.-29.9.2011), presentation

Richter, H.; Günther, C.; Voigt, I.

Zeolite membranes for
hydrogen separation

12. Jülicher Werkstoffsymposium (5./6.10.2011), presentation

Richter, H.-J.; Kucera, A.; Moritz, T.

Fabrication of ceramic tapes
with nano-zirconia powder

12th Conference of the European
Ceramic Society – ECerS XII,
Stockholm, Sweden
(19.-23.6.2011), presentation

Richter, H.-J.; Haderk, K.; Grzesiak, A.; Graf, C.; Refle, O. Studies on 3D printing for manufacturing of dental ceramics

12th Conference of the European Ceramic Society – ECerS XII, Stockholm, Sweden (19.-23.6.2011), poster

Richter, J.; Kriegel, R.; Kahn, R.; Glüsing, J.; Ruhe, N.; Beckmann, M.; Böhning, D.; Müller, M.; Ma, M. A combined catalyst and oxygen carrier system for the processing

of tar containing gases

10th International Conference on Catalysis in Membrane Reactors – ICCMR10, St. Petersburg, Russia (20.-24.6.2011), poster

Richter, J.; Kriegel, R.; Kahn, R.; Glüsing, J.; Ruhe, N.; Beckmann, M.; Böhning, D.; Müller, M.; Ma, M.

A combined catalyst and oxygen carrier system for the processing of tar containing gases

8th European Congress of Chemical Engineering/1st European Congress of Applied Biotechnology – ECCE/ECAB, Berlin (25.-29.9.2011), poster

Rödel, C.; Potthoff, A. Dispersion analysis in ceramic processing

2nd workshop dispersion analysis, Berlin (17.3.2011), presentation

Rödel, C.; Michaelis, A.; Fries, M.; Potthoff, A.

Einfluss von Rohstoffmodifizierungen auf die Wirkung von organischen Additiven in Al₃O₃-Suspensionen

5. Symposium Produktgestaltung in der Partikeltechnologie, Pfinztal (19./20.5.2011), presentation

Rödig, T.

Innovative Keramiken für piezoelektrische Generatoren Schulungsprogramm des

Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Rödig, T. Piezoelectric generator module for wireless sensor nodes in aerospace structures International Symposium on Piezocomposite Applications – ISPA

2011, Dresden (22./23.9.2011),

presentation

Luthardt, R.G.

Rost, A.; Schilm, J.; Kusnezoff, M.; Michaelis A Separatoren aus Li-Ionen leitender Keramik

Kraftwerk Batterie, Aachen

(28.2.-2.3.2011), presentation

Rudolph, H.; Johannes, M.; Ehrt, R.;

Analyse des Verbundes zwischen Lithiumdisilikat-Verblendkeramik und dichtgesintertem Zirkoniumdioxid

60. Jahrestagung der DGPro e.V. -Deutsche Gesellschaft für Prothetische Zahnmedizin und Biomaterialien, Hamburg (12.-14.5.2011), presentation

Rutkowski, B.; Baumann, S.; Beck, T.; Huang, B.; Malzbender, J.; Kriegel, R.; Steinbrech, R.W. Microstructural investigations of the hexagonal phase in BSCF membrane material after high

temperature exposure DKG-Jahrestagung, Saarbrücken (28. 30.3.2011), presentation

Sauchuk, V.; Megel, S.; Schilm, J. High temperature steels and interconnection for SOFC 1st Joint European Summer School for Fuel Cell and Hydrogen Technology, Viterbo, Italy (22.8.-2.9.2011), presentation

Scheithauer, U.; Haderk, K.; Richter, H.-J.; Petasch, U.; Zins, M.; Michaelis A Laminated multilayer for thermal shock resistant refractories based on the material system calcium-aluminate

54. Internationales Feuerfest-Kolloquium 2011, Aachen (19./20.10.2011), presentation

Scheithauer, U.; Haderk, K.;

Richter, H.-J.; Petasch, U.; Zins, M.; Michaelis, A. Lamination techniques for new multilayer for thermal shock resistant refractories based on the material system calciumaluminate

17th International Conference on Refractories, Praha, Czech Republic (10./11.5.2011), presentation

Schilm, J.; Rost, A.; Pönicke, A.; Kusnezoff, M. Fügetechnologien für SOFC

8. Löttechnisches Kolloquium des DVS 2011, Hanau (7.6.2011), presentation

Schilm, J.; Rost, A.; Pönicke, A. Sealing materials and joining techniques for SOFC

1st Joint European Summer School for Fuel Cell and Hydrogen Technology, Viterbo, Italy (22.8.-2.9.2011), presentation

Schmidt, J.; Kinski, I.; Michaelis, A.; Uhlig, S.

Plasma-enhanced CVD of ZnO with varying doping levels on different substrates

26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), presentation

Schmidt, J.; Kinski, I.; Michaelis, A.; Uhlig, S.

Plasma-Enhanced CVD of ZnO with varying doping levels on different substrates

4. Verbundtreffen des Dresdner Innovationszentrums Energieeffizienz, Dresden (8.11.2011), presentation

Schmidt, R.; Kretzschmar, C.; Eberstein, M. Influence of film thicknesses on the electrical properties of RuO₃thick film resistors on aluminium nitride ceramics (AIN)

44th International Symposium on Microelectronics, International Microelectronics And Packaging Society – IMAPS, Long Beach, USA (9.-13.10.2011), presentation

Schmidt, R.; Kretzschmar, C.; Eberstein, M.

Schichtdickenabhängigkeit einer 100 Ohm/Sq Widerstandspaste auf Aluminiumnitrid-Keramik

DKG-Jahrestagung 2011, Saarbrücken (28.-30.3.2011), presentation

Schneider, J.; Johannes, M.
Use of stirred media mills in the production of nanostrucutured ceramics

5th International Seminar »Nanotechnology, energy, plasma, lasers«, Hermsdorf/Jena (1.-3.11.2011), presentation

Schneider, M.; Schroth, S.; Richter, S.; Schubert, N.; Michaelis, A.

Choline chloride based ionic liquid – an alternative electrolyte for ECM?

7th International Symposium on Electrochemical Machining Technology – INSECT, Vienna, Austria (3./4.11.2011), presentation

Schneider, M.; Schroth, S.; Schubert, N.; Michaelis, A. Untersuchungen zum Elektrochemischen Bearbeiten (ECM) von Hartmetallen

33. Ulmer Gespräch, Ulm (12./13.05.2011), presentation

Schönecker, A.; Nicolai, M.; Schlenkrich, F.; Henschke, T.; Uhlig, S.

Investigation of domain switching of PZT and KNN-based ceramics

20th IEEE International Symposium on Applications of Ferroelectrics jointly held with the International Symposium on Piezoresponse Force Microscopy – ISAF PFM 2011, Vancouver, Canada (24.-27.7.2011), presentation

Schönecker, A.

Preparation and charakterization of acoustic transducers
based on KNN

International Symposium on Piezocomposite Applications – ISPA 2011, Dresden (22./23.9.2011), presentation

Schubert, N.; Schneider, M.; Michaelis, A. Investigation of anodic dissolution of cobalt in alkaline solution 7th International Symposium on Electrochemical Machining Techno-

logy - INSECT, Vienna, Austria

(3./4.11.2011), presentation

Funktionell modifizierte anorganisch-organische Kompositwerk-

stoffe

Schubert, R.

DKG-Jahrestagung, Saarbrücken (28.-30.3.2011), presentation 18. Symposium Verbundwerkstoffe und Werkstoffverbunde, Chemnitz (30.3.-1.4.2011), presentation

Schubert, R.

High performance electro-technical components with polymerceramic casting

5th International Seminar »Nanotechnology, energy, plasma, lasers«, Hermsdorf/Jena (1.-3.11.2011), presentation

Schubert, R.

Polymer-ceramic composites for technical applications with thermal load

Frontiers in Silicon chemistry 2011 – 1st Munich Forum on Functional Materials, München (14./15.4.2011), poster

Schwarz, B.

Möglichkeiten der Substratvor-

behandlung – Stand und neue Entwicklungen

Biogas-Schwerpunkt: Optimierung, Bernburg (23.3.2011), presentation

Schwarz, B.

Stand und neueste Entwicklungen auf dem Gebiet der

Substratvorbehandlung für den Biomasseeinsatz in Biogasanlagen

Sächsische Biogastagung, Groitzsch (6.10.2011), presentation

Schwarz, B.

Verfahrenstechnische Untersuchungen zur Substratbehandlung mittels separater Hydrolysestufe

Fachtagung Regenerative Energien als Zukunftstechnologie, Köthen (13./14.10.2011), presentation

Schwarz, B.

Stand und neueste Entwicklung auf dem Gebiet der Substratvorbehandlung für den Biomasseeinsatz in Biogasanlagen Biogas-Fachtagung Thüringen, Dermbach (8.11.2011), present.

Seuthe, T.; Grehn, M.; Eichler, H.J.; Mermillod-Blondin, A.; Rosenfeld, A.; Bonse, J.; Eberstein, M.

Strukturierung von Silikatgläsern mit unterschiedlicher Komposition durch ultrakurze Lichtpulse

85. Glastechnische Tagung der Deutschen Glastechnischen Gesellschaft (DGG), Saarbrücken (30.5.-1.6.2011), presentation

Standke, G.; Petasch, U.; Mammitzsch, L.; Adler, J.; Michaelis, A.

Katalytische Funktionsschichten
auf zellularen keramischen
Strukturen

Workshop »Funktionelle Materialien für die chemische Technik«, Dresden (6.10.2011), poster

Stein, J.; Potthoff, A.

Aufbereitung und Charakterisierung von Suspensionen

DKG-Fortbildungsseminar »Sprüh-

trocknung«, Dresden (08./09.11.2011), presentation

Steinbrech, R.W.; Rutkowski, B.; Malzbender, J.; Huang, B.;

Kriegel, R.; Beck, T.

Creep behaviour of BSCF oxygen
transport membranes

35th International Conference and Exposition on Advanced Ceramics and Composites – ICACC 2011, Daytona Beach, Florida, USA (23.-28.1.2011), presentation

Stelter, M.; Schneider, M.; Pfeifer, T. Highly efficient planar micro-SOFC

Small fuel cells conference, Boston, USA (8.-10.6.2011), presentation

Stockmann, J.

Trockenpressen – Technologische Aspekte

DKG-Fortbildungsseminar »Technologische Grundlagen der Granulierung und Granulatverarbeitung«,

Dresden (14./15.4.2011), presentation

Stockmann, J.

Verbindungstechnik

Schulungsprogramm des

Fraunhofer-Demonstrationszentrums AdvanCer, Freiburg

(10./11.11.2011), presentation

Svoboda, H.

Charakterisierung des

Pressverhaltens

DKG-Fortbildungsseminar »Sprühtrocknung«, Dresden (8./9.11.2011), presentation

Sydow, U.; Herrmann, M.; Schneider, M.; Kleebe, H.-J.; Michaelis, A. Electrochemical corrosion of SSiC and LPS-SiC ceramic materials

European Corrosion Congress -EUROCORR 2011, Stockholm, Sweden (4.-8.9.2011), poster

Thiele, J.; Kaltenborn, N.; Richter, H.; Voigt, I. Polymerabgeleitete SiBCN Keramik-Membranen für die Hochtemperatur-Gastrennung DKG-Jahrestagung, Saarbrücken (28.-30.3.2011), poster

Thiele, M.; Sempf, K.; Berger, L.-M.; Spatzier, J. Thermophysical and microstructural studies on thermallly sprayed chromium carbide coatings

International Thermal Spray

Conference – ITSC 2011, Hamburg
(27.-29.9.2011), presentation

Toma, L.-F.; Langner, S.;
Barbosa, M.M.; Berger, L.-M.;
Rödel, C.; Potthoff, A.
Influence of the suspension characteristics and spraying parameters on the properties of dense suspension-HVOF sprayed Al₂O₃ coatings

International Thermal Spray Conference – ITSC 2011, Hamburg (27.-29.9.2011), poster

Tröber, O.; Richter, H.; Voigt, I.

Organophilic zeolite filled
membranes for pervaporation
International Scientific Conference
on Pervaporation and Vapor
Permeation, Torun, Poland
(8.-11.9.2011), presentation

Tröber, O.; Richter, H.; Voigt, I.

Tailor made zeolites for different applications in composite materials

23. Deutsche Zeolithtagung,

Erlangen (2.-4.3.2011), poster

Tröber, O.; Richter, H.; Voigt, I.; Nagel, M.; Grimm, T.; Liebert, T.; Homuth, M.; Heft, A.; Schimanski, A.; Grünler, B. Verfahren zur Herstellung nanopartikulärer Zeolithe für die Anwendung in Kompositen DKG-Jahrestagung, Saarbrücken

(28.-30.3.2011), poster

Tröber, O.; Richter, H.; Stachel, D.; Voigt, I.

Zeolite nano particle preparation for highly permeable mixed matrix membranes

Network of Young Membrains 13, Enschede (21.-23.7.2011), presentation

Trofimenko, N.; Kusnezoff, M.; Michaelis, A. Recent development of electrolyte supported cells with high power density

219th Electrochemical Society Meeting, Montréal, Canada (1.-6.5.2011), presentation

Trofimenko, N.; Kusnezoff, M.; Michaelis, A.

Recent development of electrolyte supported cells with high power density

12th International Symposium on Solid Oxide Fuel Cells – SOFC-XII, Montreal, Canada (1.-6.5.2011), p.315-325, presentation

Uhlig, S.

Domain related topography formation during CMP of lead-free and lead containing

PRESENTATIONS AND POSTERS, TEACHING ACTIVITIES OF IKTS EMPLOYEES

ferroelectric ceramics

20th IEEE International Symposium on Applications of Ferroelectrics jointly held with the International Symposium on Piezoresponse Force Microscopy – ISAF PFM 2011, Vancouver, Canada (24.-27.7.2011), poster

van Gestel, T.; Bram, M.; Meulenberg, W.A.; Puhlfürß, P.; Richter, H.; Voigt, I.; Wolf, M.J.; Bouwmeester, H.J.M.

Microporous membranes for hydrogen separation: State of the art and future prospects 12. Jülicher Werkstoffsymposium,

Vashishta, L.; Voigt, I.; Richter, H.; Kühnert, J-T.; Weyd, M.

Jülich (5./6.10.2011), presentation

Ceramic membranes for the separation of glucose and the enrichment and dewatering of ethanol

International Conference on Membranes – ICM-2011, Kottayam, India (16.-19.9.2011), presentation

Voigt, I.; Hoyer, T.; Fischer, G.; Kämnitz, S.; Köhler, B.; Sikora, R.; Tupaika, F.; Niemz, F.-G.; Schulze, T. Ceramic hollow fiber contactors for membrane extraction International Congress on Membranes and Membrane

Processes - ICOM, Amsterdam,

the Netherlands (23.-29.7.2011), poster

Voigt, I.

Development of ceramic NF membranes with a cut-off below 450 D

International Workshop on Implementation of Nanomembrane
Technology in the Pharmaceutical
Industry, Sofia, Bulgaria
(9./10.9.2011), presentation

Voigt, I.

Innovations in ceramic membranes

International Workshop on Recent Development on Membrane Technology for Industrial Applications, Chennai, India (10./11.2.2011), presentation

Voigt, I.; Richter, H.; Kriegel, R.; Weyd, M.

Innovations in ceramic membranes

8th European Congress on
Chemical Engineering – ECCE,
Berlin (25.-29.9.2011), presentation

Voigt, I.; Richter, H.; Kriegel, R.; Kaltenborn, N.

Neue anorganische Membranen für Anwendungen in der Energie- und Umwelttechnik Thüringer Werkstofftag 2011, Jena (30.03.2011), presentation Voigt, I.; Richter, H.; Kühnert, J-T.; Weyd, M.; Tusel, E.; Brüschke, H.E.A. Sustainable, energy efficient and economic biorefineries by membrane enhanced processes International Congress on Membranes and Membrane Processes, Amsterdam, the Netherlands (23.-29.7.2011), presentation

Voigtsberger, B.

Micro- and nanostructured functional ceramics for future applications

5th International Seminar Nanotechnolgy, Energy, Plasma, Lasers – NEPL-201, Hermsdorf/Jena (1.-3.11.2011), presentation

Wätzig, K.; Krell, A.; Michaelis, A. Highly transparent Al-rich MgO n Al_20_3 spinel (1<n<2.5) by reaction sintering of MgO and Al_20_3 Glass and optical materials division annual meeting, Savannah, USA

Wätzig, K.; Grimm, M.; Scholz, S.; Michaelis, A.; Kinski, I.

(15.-19.5.2011), presentation

Polycrystalline silicon thin films using PE CVD and high order silanes

26th European Photovoltaic Solar Energy Conference and Exhibition – EU PVSEC, Hamburg (5.-9.9.2011), 3AV.1.33, poster Weidmann, S.K.; Kremmer, K.; Schneider, M.; Fürbeth, W. Nanochemical impregnation of Modified Phosphoric Acid Anodised (MPAA) layers – a promising replacement for Chromic Acid Anodising (CAA) European Corrosion Congress -EUROCORR 2011, Stockholm, Sweden (4.9.-8.9.2011),

Weiser, M.; Dörfler, S.; Schneider, M.; Althues, H.; Michaelis, A.; Kaskel, S. Elektrochemische Kupferabscheidung auf ausgerichteten MWCNTs

presentation

YoungNanoProfessionals-Workshop, Frankfurt am Main (8.11.2011), poster

Weiser, M.; Lämmel, C.; Schneider, M.; Michaelis, A. Kapazitätsbestimmung an EDLC-Materialien – ein Methodenvergleich

Zukunft Energie, Dresden (11.-13.5.2011), poster

Weiser, M.; Dörfler, S.; Schneider, M.; Althues, H.; Michaelis, A.; Kaskel, S. Platin Pulse Plating auf ausgerichteten MWCNTs YoungNanoProfessionals-Workshop, Frankfurt am Main

(8.11.2011), presentation

Weiser, M.; Fritsch, M.; Kusnezoff, M.; Schneider, M.; Michaelis, A.; Leonhardt, A.; Khavrus, V.; Malcher, P.; Pfannmöller, E.; Kramer, D.; Kohrs, K. Superkondensatoren auf Basis von Verbundwerkstoffen nanostrukturierter Kohlenstoffmodifikationen Kraftwerk Batterie, Aachen (28.2.-2.3.2011), presentation Weyd, M.; Richter, H.; Voigt, I.; Herrmann, K.; Kühnert, J-T. Bioethanolgewinnung unter Verwendung keramischer Membranen Weyd, M. presentation Wufka, A.

enertec/TerraTec 2011, Leipzig (25.-27.1.2011), presentation Verfahrenskonzepte zum Einsatz keramischer Membranen Arbeitskreis »Keramische Membranen«, Frankfurt/M. (5.5.2011), Improving the efficiency of biogas plants by the introduction of

innovative processes Biogaz Europe 2011, Nantes, Frankreich (25./26.10.2011), presentation Wufka, A.; Friedrich, E.

Leistungssteigerung in der

Biogasproduktion enerTec – Forum enertec

dezentral - Internationale Fachmesse für Energie, Leipzig (25.-27.1.2011), presentation

Ziesche, S. Ceramic interface and multilayer technology for micro fuel cells IMAPS/ACerS – 7th International Conference and Exhibition on Ceramic Interconnect and Ceramic Microsystems Technologies -

CICMT 2011, San Diego, USA

(5.-7.4.2011), presentation

Zins, M. Anwendungen und Lieferanten keramischer Hochleistungskomponenten Schulungsprogramm des

Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Zins, M. Einkauf von technischer Keramik: Richtig anfragen leicht gemacht BME-Forum »Einkauf von Technischer Keramik«, Nürnberg (12.5.2011), presentation

Zins, M. Eigenschaften keramischer Hochleistungswerkstoffe Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer, Dresden (9./10.3.2011), presentation

Zins. M. Keramische Hochleistungswerkstoffe: Einsatzbereiche, Entwicklungstrends

DKG-Fortbildungsseminar »Entbinderung keramischer Formteile«, Dresden (6./7.10.2011), present.

Zins, M. Keramische Werkstoffe und Anwendungen - Entwicklungstrends und -angebote DKG-Fortbildungsseminar »Thermoplastische Formgebung von Technischer Keramik« Dresden

(5./6.10.2011), presentation

Zschippang, E.; Klemm, H.; Herrmann, M.; Sempf, K.; Guth, U.; Michaelis, A. Ternary electro-conductive composites based on silicon nitride-silicon carbide

12th Conference of the European Ceramic Society - ECerS XII, Stockholm, Schweden (19.-23.6.2011), presentation

Teaching activities of IKTS employees

Dr. Barth, S. Vorlesung »Keramische Verfahrenstechnik«

Fachhochschule Jena, Fachbereich Scitec (WS11/12)

Dr. Fries, M. Vorlesung »Produktgestaltung keramische Sprühgranulate« Georg-Simon-Ohm-Hochschule Nürnberg (13.12.2011)

Dr. habil. Herrmann, M. Vorlesung und Studentenbetreuung »Technische Keramische Werkstoffe« University of Witwatersrand, Johannesburg, Südafrika (03/2011 und 09/2011)

Vorlesung »Keramografie« Im Rahmen der Lehrveranstaltung »Metallografie« TU Dresden, Institut für Werkstoffwissenschaft (10.01.2011)

Dipl.-Ing. Höhn, S.

Dr. Jahn, M. Vorlesung »Chemische Verfahrenstechnik/ Reaktionstechnik« HTW Dresden, Chemieingenieurwesen (SS11)

Dr. Kriegel, R. Vorlesung »Keramische Verfahrenstechnik«

TEACHING ACTIVITIES OF IKTS EMPLOYEES, PARTICIPATION IN BODIES AND TECHNICAL COMMITTEES

Fachhochschule Jena, Fachbereich Scitec (WS11/12)

Dr. Kusnezoff, M.;
Dr. Stelter, M.; Dr. Partsch, U.;
Dr. Jahn, M.; Heddrich, M.
Vorlesung

»Keramische Funktionswerkstoffe« TU Dresden, Institut für Werkstoffwissenschaft (SS11)

Prof. Dr. Michaelis, A.Vorlesung und Praktikum

»Keramische Werkstoffe«
TU Dresden, Institut für
Werkstoffwissenschaft
(WS10/11; WS11/12)

Prof. Dr. Michaelis, A.; Dr. Rebenklau, L.;

Dr. Schönecker, A.

Kapitel: »Technologien der Dickschichttechnik« in der Vorlesungsreihe »Hybridtechnik« TU Dresden, Fakultät Elektrotechnik und Informationstechnik

(WS11/12)

Möhring-Lotsch, N.

Lehrtätigkeit »Personalführung« Verwaltungs- und Wirtschaftsakademie Magdeburg VWA gemeinnützige GmbH (2011)

Dr. Rebenklau, L.

Vorlesung
»Dickschichttechnik« und »Multi-

layerkeramik« in der Vorlesung von Prof. Michaelis »Funktionskeramik«

TU Dresden, Institut für Werkstoffwissenschaft (SS11)

Dipl.-Ing. Svoboda, H.;

Dr. Fries, M.

Vorlesung

»Pulveraufbereitung und
-konfektionierung« im Rahmen
der Lehrveranstaltung
»Keramische Werkstoffe«
(25.11.2011)

Dr. Voigt, I.

Vorlesung »Keramische Verfahrenstechnik« Fachhochschule Jena, Fachbereich

Dr. Zins, M.

Scitec (WS11/12)

Vorlesung

»Metalle, Kunststoffe, Keramiken –
Technische Keramik als Leichtbaustoff«

TU Dresden, Institut für Werkstoffwissenschaft (WS10/11, WS11/12)

Participation In bodies and technical committees

Dipl.-Krist. Adler, J.

- DGM Fachausschuss »Zellulare Werkstoffe«
- FAD Förderkreis Abgasnachbe-

handlungstechnologien für Dieselmotoren e.V.

Dr. Beckert, W.

 Fraunhofer-Allianz »Numerische Simulation von Produkten und Prozessen« NUSIM

Dr. Faßauer, B.

- Fraunhofer-Allianz SysWasser
- Wasserwirtschaftliches
 Energiezentrum Dresden –
 e.qua impuls e.V.

Freund, Susanne

 Fraunhofer-Allianz AdvanCer, Geschäftsstelle

Dr. Friedrich, E.

- Fachverband »Biogas«

Dr. Fries, M.

- DGM/DKG-Arbeitskreis »Verarbeitungseigenschaften synthetischer keramischer Rohstoffe«, Leiter
- DKG-Fachausschuss »Verfahrenstechnik«
- ProcessNet-Fachgruppe
 »Agglomerations- und
 Schüttguttechnik«
- DKG-Fachausschusses FA III »Verfahrenstechnik«

Dr. Gestrich, T.

Gemeinschaftsausschuss
 »Pulvermetallurgie«, Expertenkreis »Sintern«

GEFTA-Arbeitskreis»Thermophysik«

Dipl.-Ing. Gronde, B.

- Gemeinschaft »Thermisches Spritzen e.V.«
- DVS-Arbeitsgruppe »Thermisches Spritzen«

Dr. Herrmann, M.

 DGM-Fachausschuss »Thermodynamik, Kinetik und Konstruktion der Werkstoffe«

Dipl.-Ing. Jaenicke-Rößler, K.

- GEFTA-Arbeitskreis »Thermophysik«
- GEFTA-Arbeitskreis »Messunsicherheit von Thermodilatometern«

Dr. Kaltenborn, N.

- DKG-Arbeitskreis »Kohlenstoff«

Dr. Klemm, H.

- DKG-Arbeitskreis »Verstärkung keramischer Stoffe«
- DIN Normenausschuss »Materialprüfung NMP 291«
- Carbon Composites e.V., Arbeitskreis »Ceramic Composites«

Dr. Krell, A.

 Associate Editor des »Journal of the American Ceramic Society«

Kunath, R.

- Arbeitskreis »Dresdner Informa-

- tionsvermittler e.V.«
- Arbeitskreis »Spezialbibliotheken«

Dr. Kusnezoff, M.

- DIN/VDE, Referat K 141, DKE Deutsche Kommission, »Elektrotechnik Elektronik Informationstechnik «
- Arbeitskreis »Aufbau- und Verbindungstechnik für Hochtemperatursensoren«

Dipl.-Ing. Ludwig, H.

DGM-Fachausschuss
 »Biomaterialien«

Prof. Dr. Michaelis, A.

- »World Academy of Ceramics«
 WAC
- WAC Forum Committee (2010-2014), Mitarbeit
- DKG-Vorstandsmitglied
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«, Arbeitskreis »Koordinierung«
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«,
 Arbeitskreis »Funktionskeramik«,
 Leitung
- DECHEMA-Arbeitsausschuss »Angewandte Anorganische Chemie«
- AGEF-Arbeitsgemeinschaft Elektrochemischer Forschungsinstitutionen e.V.
- DPG-Deutsche Physikalische Gesellschaft

- Institutsrat des IfWW,
 TU Dresden
- FZ Rossendorf, Vereinsmitglied
- Fa. Roth & Rau, Aufsichtsratsmitglied
- AiF Wissenschaftlicher Rat
- Solarvalley Mitteldeutschland e.V., Vorstand
- Beirat Arbeitskreis »Photovoltaik Silicon Saxony«
- Hochschulrat der Westsächsischen Hochschule Zwickau
- Dresdner Gesprächskreis
- NanoChem, BMBF, Gutachter
- Gutachterausschuss
 »Interne Programme« der
 Fraunhofer Gesellschaft
- Lenkungsgremium Innovationszentrum Energieeffizienz TUD
- Beirat eZelleron GmbH
- Vorstand Materialforschungsverbund Dresden e.V. MFD, Mitglied
- Energiebeirat des Wirtschaftsministeriums Sachsen
- Beirat Industrielles Netzwerk Erneuerbare Energien Sachsen EESA
- Dresden concept
- Clean Tech Media Award,
 Jurymitglied
- Gutachterausschuss »Märkte von Übermorgen« der Fraunhofer-Gesellschaft
- Editorial Board des »Journal of Ceramic Science and Technology«
- Editorial Board des »International Journal of Materials Research«

Dr. Moritz, T.

- ENMAT »European Network of Materials Research Centres«,
 Vice President
- Management Committee of COST action MP0701
 »Nanocomposite Materials«
- DECHEMA-Fachausschuss »Nanotechnologie«
- DKG-Expertenkreis »Keramikspritzguss«, Vorstandsvorsitzender

Dipl.-Phys. Mürbe, J.

VDI-Bezirksverein Dresden,
 Arbeitskreis »Granulometrie«

Nake, K.

 DGM-Arbeitskreis »Härteprüfung und AWT«, Fachausschuss »FA-12«

Dr. Nebelung, M.

- ProcessNet-Fachgruppe
 »Agglomerations- und
 Schüttguttechnik«
- ProcessNet-Fachgruppe»Trocknungstechnik«

Dr. Petasch, U.

 FAD Förderkreis Abgasnachbehandlungstechnologien für Dieselmotoren e.V.

Dipl.-Ing. Pönicke, A.

 DVS-Ausschuss für Technik, Arbeitsgruppe W3 »Fügen von Metall, Keramik und Glas«

Dr. Potthoff, A.

- DGM/DKG-Arbeitskreis »Prozessbegleitende Prüfverfahren«
- DECHEMAVCI-Arbeitskreis »Responsible Production and Use of Nanomaterials«
- Fraunhofer-Allianz »Nanotechnologie«

Dr. Rebenklau, L.

- VDIVDE-GMM Fachausschuss
 5.5 »Aufbau- und Verbindungstechnik«
- VDE/VDI-Gesellschaft für Mikroelektronik, Mikro- und Feinwerktechnik
- Arbeitskreis »Aufbau- und Verbindungstechnik für Hochtemperatursensoren«

Dr. Reichel, U.

- DKG-Fachausschuss 6 »Werkstoffanwendungen«
- DKG-Arbeitskreis »Verarbeitungseigenschaften synthetischer keramischer Rohstoffe«

Dr. Richter, H.

- International Zeolite Association

Dr. Richter, H.-J.

- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«, Arbeitskreis »Keramische Membranen«
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«,
 Arbeitskreis »Biokeramik«

PARTICIPATION IN BODIES AND TECHNICAL COMMITTEES

 DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«, Arbeitskreis »Generative Fertigung keramischer Komponenten«

Dr. Richter, V.

- DECHEMAVCI-Arbeitskreis »Responsible Production and Use of Nanomaterials«
- Fraunhofer-Allianz »Nanotechnologie«
- EPMA-Arbeitskreis »European Hard Materials Group«
- VDI-Fachausschuss »Schneidstoffanwendung«
- DIN-Normenausschuss »Werkstofftechnologie«, AA »Hartmetalle«
- DIN-Normenausschuss »Materialprüfung«, AA »Sintern«
- DGM/DKG-Gemeinschaftsausschuss »Pulvermetallurgie«, Expertenkreis »Sintern«

Dr. Schilm, J.

- DGG-Fachausschuss 1 »Physik und Chemie des Glases«
- DKG/DGG-Arbeitskreis »Glasigkristalline Multifunktionswerkstoffe«
- DVS-Ausschuss für Technik,
 Arbeitsgruppe W3 »Fügen von
 Metall, Keramik und Glas«

Dr. Schönecker, A.

- Beirat der Smart Material GmbH Dresden

Dipl.-Chem. Schubert, R.

 DKG-Expertenkreis »Keramikspritzguss«

Standke, Gisela

 DGM Fachausschuss »Zellulare Werkstoffe«

Dipl.-Ing. Stahn, M.

- VDI-Entwicklung, Konstruktion, Vertrieb

Dr. Stelter, M.

- Brennstoffzellen Initiative Sachsen e.V., Vorstand
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«,
 Arbeitskreis »Energie«

Dipl.-Min. Thiele, S.

- GTS-Gemeinschaft Thermisches Spritzen e.V.

Dr. Voigt, I.

- GVC-Fachausschuss »Produktionsintegrierte Wasser- und Abwassertechnik«
- ProcessNet-Arbeitsausschuss»Membrantechnik«
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«, Arbeitskreis »Keramische Membranen«, Leiter
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«, Arbeitskreis »Koordinierung«

Dr. Voigtsberger, B.

- DKG-Mitglied des Präsidiums und Vorstandes
- DGM/DKG-Gemeinschaftsausschuss »Hochleistungskeramik«, Arbeitskreis »Koordinierung«, Vorsitz
- Hochschulrat Fachhochschule
- MNT Mikro-Nano-Technologie
 Thüringen e.V., Mitglied des Vorstandes
- Wirtschaftsbeirat der Ministerpräsidentin Thüringens
- IHK Ostthüringen zu Gera, Ausschuss für Industrie und Forschung

Dr. Wunderlich, C.

- Brennstoffzellen Initiative Sachsen e.V., Vorstand
- VDI-Fachausschuss »Brennstoffzellen«

Dr. Zins, M.

- Fraunhofer-Allianz AdvanCer,
 Sprecher
- DKG-Koordinierungsgruppe »Strukturwerkstoffe Fachausschüsse«
- Fachausschuss »Pulvermetallurgie«
- DKG-Fachausschuss »Keramikanwendungen«
- Deutsche Messe AG, Fachmessebeirat »Industrial Supply«
- Messe München, Fachbeirat
 »Ceramitec«

Institut für Prozess- und Anwendungstechnik Keramik, RWTH
 Aachen, Vorstand

Advisory boards for symposia and conferences

Freund, S.

- Schulungsprogramm des Fraunhofer-Demonstrationszentrums AdvanCer »Keramische Hochleistungswerkstoffe – Block I: Werkstoffe und Verfahren«, Dresden (9./10.3.2011), Organisation

Dr. Fries, M.

- DKG-Fortbildungsseminar »Technologische Grundlagen der Granulierung und Granulatverarbeitung«, IKTS Dresden/TU Dresden (14./15.4.2011), Organisation
- DKG-Fortbildungsseminar
 »Sprühtrocknung«, IKTS Dresden/TU Dresden (9./10.11.2011),
 Organisation
- DKG-Symposium »Charakterisierungsverfahren in der keramischen Aufbereitung«, Erlangen (29./30.11.2011), Programmausschuss

Dr. Gestrich, T.

 30. Hagener Symposium Pulvermetallurgie »Sintern – der zentrale Prozess der Pulvermetallurgie«, Hagen (24./25.11.2011), Programmausschuss

Dr. Herrmann, M.

DKG-Fortbildungsseminar
 »Entbinderung keramischer
 Formteile«, IKTS Dresden
 (6./7.10.2011), Organisation

Dr. Jahn, M.

4. Sächsischer Brennstoffzellentag, Leipzig (10.11.2011),
 Organisation

Prof. Dr. Michaelis, A.

- Workshop »Technologien für dezentrale Energiespeicherung auf Basis innovativer Akkumulatoren«, Dresden (24.3.2011)
- DKG-Jahrestagung 2011, Saarbrücken (28.-30.3.2011)
- ISPA 2011 International Symposium on Piezocomposite Applications, Dresden (22./23.9.2011)
- Symposium Hochleistungskeramik DKG/DGM 2012, Karlsruhe (25./26.10.2011)
- ProcessNet DECHEMA-Diskussionstagung »Anorganisch-Technische Chemie«, Frankfurt/Main (2011), Vorbereitungskomitee
- 2. Dresdner Werkstoffsymposium »Werkstoffe für die Mobilität«, Dresden, TUD IfWW (8./9.12.2011)
- DKG-Jahrestagung 2012/Symposium Hochleistungskeramik
 DKG/DGM 2012, Nürnberg
 (5.-7.3.2012)
- 10th CMCEE International Symposium on Ceramic Materials

- and Components for Energy and Environmental Applications, Dresden (20.-23.5.2012), Organisationskomitee
- ProcessNet DECHEMA-Diskussionstagung »Anorganisch-Technische Chemie«, Frankfurt/Main (2012), Vorbereitungskomitee
- MSE 2012 Materials Science and Engineering, Darmstadt (25.-27.09.2012)
- Materialforschungstournee des MFD, Dresden (2011/2012)
- Vision Keramik 2013+

Dr. Moritz, T.

- DKG-Fortbildungsseminar »Plastische und Thermoplastische Formgebung«, Dresden (5./6.10.2011), Organisation

Dr. Reichel, U.

- III. International Research and Practice Conference and Specialized Exhibition on Modern Ceramic Materials, Properties, Technology, Applications, Novosibirsk, Russland (14.-19.9.2011)
- 5th International Seminar »Nanotechnology, Energy, Plasma,
 Lasers – NEPL-2011«, Hermsdorf,
 Jena (1.-3.11.2011)

Dr. Schneider, M.

 International Workshop on Impedance Spectroscopy, Chemnitz (28.-30.9.2011), Program Committee 7th International Symposium on ElectroChemical Machining Technology – INSECT 2011, Wien (3./4.11.2011), Advisory Board

Dr. Schönecker, A.

- PT-PIESA-Workshop »Hochleistungswerkstoffe« (21.9.2011)
- ISPA 2011 International Symposium on Piezocomposite Applications, Dresden (22./23.9.2011)

Dr. Stelter, M.

4. Sächsischer Brennstoffzellentag, Leipzig (10.11.2011), Moderation

Dr. Voigt, I.

- DGM-Symposium Hochleistungskeramik 2011, Karlsruhe (25./26.10.2011)

Dr. Voigtsberger, B.

- DGM-Symposium Hochleistungskeramik 2011, Karlsruhe (25.-26.10.2011)
- 5th International Seminar
 »Nanotechnology, Energy,
 Plasma, Lasers NEPL-2011«,
 Hermsdorf, Jena (1.-3.11.2011)

Dr. Wunderlich, C.

15th European Fuel Cell Forum
 2011, Lucerne, Switzerland
 (28.6.-1.7.2011), Advisory Board

Dr. Zins, M.

- BME-Forum »Einkauf von

Technischer Keramik«, Nürnberg (11./12.5.2011), Fachliche Leitung

Dissertations

Klein, Cornelia

Sol-Gel-Verfahren für die Herstellung von ZrO₂-Schichten Dissertation 2011 IKTS Dresden – TU Freiberg, Fakultät für Chemie und Physik

Wätzig, Katja

Transparente $\mathrm{MgAl_2O_4}$ -Keramik aus Precursor-abgeleiteten Spinell-Pulvern oder per Reaktionssintern von MgO -/ $\mathrm{Al_2O_3}$ -Gemischen Dissertation 2011 IKTS Dresden – TU Freiberg, Fakultät für Chemie und Physik

Diploma theses

Arnold, Sébastien

Bruchmechanische Untersuchung gelöteter Metall-Keramik-Verbunde Diplomarbeit 2011 IKTS Dresden – TU Dresden, Fakultät Maschinenwesen, Institut für Oberflächen- und Fertigungstechnik

Bachmann, Elisa

Herstellung und Charakterisierung von Katalysatoren zur Reformie-

PARTICIPATION IN BODIES AND TECHNICAL COMMITTEES, DISSERTATIONS, DIPLOMA THESES

rung von Ethanol für den Betrieb in einer Hochtemperaturbrennstoffzelle Bachelorarbeit 2011 IKTS Dresden – HTW Dresden, Fakultät Maschinenbau/Verfahrenstechnik

Gierth, Paul

Untersuchungen zu Lötverfahren für Photovoltaik-Dickschichtpasten Diplomarbeit 2011 IKTS Dresden – TU Dresden, Fakultät Elektrotechnik, Institut für Aufbau- und Verbindungstechnik

Görlitz, Henrik

Entwicklung und Charakterisierung von Titanoxid-Kompositen als Material für den Einsatz als Thermoelektrikum Diplomarbeit 2011 IKTS Dresden – TU Dresden, Fakultät Maschinenwesen, Institut für Werkstoffwissenschaft

Hagemann, Ralf

Modifikation von hydrophoben
Zeolithmembranen und deren Charakterisierung durch Pervaporation
und alternative Verfahren
Diplomarbeit 2011
IKTS Hermsdorf – Fachhochschule
Jena, Fachbereich SciTec

Korneli, Marcel

Untersuchungen zum Einfluss der Fließ- und Presseigenschaften von

Granulaten auf Eigenschaftsschwankungen trockengepresster Grünkörper Diplomarbeit 2011 IKTS Dresden – TU Dresden, Fakultät Maschinenwesen

Krause, Robert

Partielle Oxidation von LPG für Brennstoffzellanwendungen Bachelorarbeit 2011 IKTS Dresden – HTW Dresden, Fakultät Maschinenbau/Verfahrenstechnik

Lenz, Christian

Miniaturkraftsensor in LTC-Technologie
Diplomarbeit 2011
IKTS Dresden – TU Dresden,
Fakultät Elektrotechnik und Informationstechnik, Institut für Feinwerktechnik und Elektronik-Design

Matthey, Björn

Rolle der Grenzflächen in gradierten Siliciumcarbid-Diamant-Kompositwerkstoffen Diplomarbeit 2011 IKTS Dresden – TU Bergakademie Freiberg, Fakultät für Werkstoffwissenschaft und Werkstofftechnologie

Neumann, Josephine

2D Modell eines auf dem Prinzip der partiellen Oxidation arbeitenden monolithischen Reformers für den Einsatz in einem SOFC-System Diplomarbeit 2011 IKTS Dresden – TU Dresden, Fakultät Maschinenwesen

Nousch, Laura

Systemkonzeption und Prozessauslegung für eine SOFC-Anlage mit reduzierter Betriebstemperatur Diplomarbeit 2011 IKTS Dresden – TU Dresden, Fakultät für Maschinenwesen, Institut für Energietechnik

Schalomon, Jens

Experimentelle Untersuchungen zum Betriebsverhalten des Reformers im Hinblick auf die Systemintegration in ein Brennstoffzellensystem Bachelorarbeit 2011 IKTS Dresden – Hochschule Lausitz Senftenberg, Institut für Chemieingenieurwesen/Verfahrenstechnik

Schliephake, Angelika

Deaktivierungsverhalten von Oxidationskatalysatoren beim Einsatz zur Nachbehandlung von SOFC-Abgas Bachelorarbeit 2011

IKTS Dresden – HTW Dresden,
Fakultät Maschinenbau/Verfahrenstechnik

Schubert, Nora

Untersuchungen zum Electrochemical Machining (ECM) von Cobalt Masterarbeit 2011 IKTS Dresden – TU Dresden, Fakultät Mathematik und Naturwissenschaften, Institut für Physikalische Chemie

Schütz, Matthias

Labortechnische Untersuchungen zur Bewertung und Auslegung einer separaten Hydrolysestufe für landwirtschaftliche Biogasanlagen Masterarbeit 2011 IKTS Dresden – TU Dresden, Fakultät für Forst-, Geo- und Hydrowissenschaften, Institut für Abfallwirtschaft und Altlasten

Semisch, Jan

Entwässerung kommunaler Klärschlämme unter Einsatz natürlicher Flockungshilfsmittel
Diplomarbeit 2011
IKTS Dresden – TU Dresden,
Fakultät Forst-, Geo- und Hydrowissenschaften, Fachrichtung Wasserwesen, Institut für Siedlungs- und Industriewasserwirtschaft

Wagner, Sebastian

Theoretische und experimentelle Untersuchungen zur heterogenen Katalyse von CO und H₂ aus SOFC-Abgas Bachelorarbeit 2011 IKTS Dresden – HTW Dresden, Fakultät Maschinenbau/Verfahrenstechnik

Wanke, Andreas

Applikationsuntersuchungen zum
Aerosoldruck von polymeren Leitpasten/-tinten
Diplomarbeit 2011
IKTS Dresden – TU Dresden,
Fakultät Elektrotechnik, Institut für
Aufbau- und Verbindungstechnik

Wieden, Stefanie

Labortechnische Untersuchungen zum chemischen und biologischen Aufschluss von lignozellulosehaltigen Reststoffen am Beispiel von Weizenstroh zur Effektivierung der Biogaserzeugung Masterarbeit 2011
IKTS Dresden – TU Dresden, Fakultät für Forst-, Geo- und Hydrowissenschaften, Institut für Abfallwirtschaft und Altlasten



ART AT FRAUNHOFER IKTS 2010-2011

Continuity and creative genius have been characterizing the creative research atmosphere at Fraunhofer IKTS for 20 years. So, the artist Jochen Rohde is an integral part of the exhibitions. In the past two years, he organized two exhibitions with Manara Grund showing acrylic paintings and botanic subjects. This was a wonderful symbiosis harmonizing the abstract art of Jochen Rohde and the representationalism of Manara Grund's natural objects.

The graphic artist Mechthild Mansel and the art student Judith Michael organized the exhibition "Light and Motion". Mechthild Mansel says about her work: "It is my central concern to uncover the variety of human state, the basic patterns of inner feelings as well as their adequate expression in order to bring it into a general and personal interpretation. Color is an important carrier of emotion. The vibrations of colors seeing with our eyes subconsciously address us like music which is also strongly influencing my work."

Light is a central topic for Judith Michael. "I take pictures of light. I use natural and artificial light as motive, e.g. sunlight, spectral colors in refractions, but also self-made LEDs as light source on the animation board. I study the change of natural and artificial light. It is the aim to create an artistic symbiosis of own motions, the motion of light sources as well as their change. The term "light painting" is characterizing my experimental photography."


At the end of this exhibition year, Fraunhofer IKTS staff presented photographs showing "structures". The exhibition lives on the viewer's feel for details and combines the various possibilities of seeing one object with the photographic styles.

Grit Kaiser

- **1** Mechthild Mansel Acrylic painting (cut-out).
- 2 Jochen Rohde Acrylic painting (cut-out).
- 3 Manara Grund Photography (cut-out).

 Picture on the right

Judith Michael – Photography (cut-out).



EVENTS / TRADE FAIRS 2011

Conferences 10th International Symposium on Ceramic Materials and Components for Energy and Environmental Applications – CMCEE Dresden/Munich, May 20–24, 2012 Electrochemical Collo-	Thermoplastic shape-forming of advanced ceramics – technology and training Dresden, October 10–11, 2012 Debinding of ceramic bodies Dresden, October 11–12, 2012	Please find further information at www.advancer.fraunhofer.de Participation in trade fairs Biogas Convention and Trade Fair Bremen, January 10–12, 2012	ACHEMA Frankfurt, June 18–22, 2012 European Fuel Cell Forum Lucerne, June 26–29, 2012 ICIM (International Conference on Inorganic Membranes) Twente, July 10–13, 2012
quium Dresden, November 29–30, 2012	Spray drying of ceramic suspensions Dresden, November 7–8, 2012	nano tech Tokyo, February 15–17, 2012 FuelCell Expo Tokyo, February 29 – March 2,	IMPAS 2012 San Diego, September 9–13, 2012 EU PVSEC
Events Girls' Day	Please find further information at www.dkg.de	2012 Jenaer Industry Days	Frankfurt, September 24–28, 2012
Dresden, April 26, 2012	Seminars of the Fraun- hofer Demonstration Cen-	Jena, March 28–29, 2012	Materialica Munich, October 23–25,
Long Night of Sciences Dresden, July 6, 2012	ter AdvanCer	Hannover Messe Hanover, April 23–27, 2012	2012
Fraunhofer Talent School Dresden, November 2012 www.talent-school-	Introduction into Advanced Ceramics Part I: Materials, technol-	IFAT Munich, May 7–11 2012	Innovation Day Thuringia Erfurt, November 2, 2012 Electronica
dresden.de	ogy Dresden, March 14–15, 2012	SMT/HYBRID/PACKAGING Nuremberg, May 8–10, 2012	Munich, November 13–16, 2012
Seminars / Workshops DKG seminars	Part II: Machining Berlin, May 9–10, 2012	Sensor & Test Nuremberg, May 22–24, 2012	Hybridica Munich, November 13–16, 2012
Technological fundamentals of granulation and granule processing Dresden, April 18–19, 2012	Part III: Construction, testing Freiburg, November 8–9, 2012	CERAMITEC Munich, May 22–25, 2012	

HOW TO REACH US

How to reach us in Dresden

by car

- At the three-way highway intersection "Dresden West" exit Autobahn A4 onto Autobahn A17 in direction "Prag" (Praque)
- Exit at "Dresden Prohlis" (Exit 4)
- Continue 2 km along the secondary road in direction "Zentrum" (City Center)
- At the end of the secondary road (Kaufmarkt store will be on the right side), go through light and continue straight ahead along Langer Weg in direction "Prohlis" (IHK)
- After 1 km, turn left onto Mügelner Strasse
- Turn right at the next traffic light onto Moränenende
- Continue under the train tracks and turn left at next traffic light onto Breitscheidstrasse
- Continue 3 km (the road name will change to An der Rennbahn and then to Winterbergstrasse)
- Fraunhofer IKTS is on the left side of the road (Winterbergstrasse 28)

by train

- From Dresden main railway station take train S1 (direction Bad Schandau) or train S2 (direction Pirna) to stop "Haltepunkt Strehlen"
- Change to bus line 61 (direction Weißig/Fernsehturm) or 85 (direction Striesen) and exit at "Grunaer Weg"

by plane

- From Airport Dresden-Klotzsche take a taxi to Winterbergstrasse 28 (distance is approximately 7 miles or 10 km)
- Or use suburban train S2 (underground train station) to stop "Haltepunkt Strehlen"

How to reach us in Hermsdorf

by car

- From exit Bad Klosterlausnitz/Hermsdorf (A9, exit 23) follow the road to Hermsdorf, go straight ahead up to the roundabout
- Turn right to Robert-Friese-Strasse
- The 4th turning to the right after the roundabout is Michael-Faraday-Strasse
- Fraunhofer IKTS is on the left side
- From exit Hermsdorf-Ost (A4, exit 56a) follow the road to Hermsdorf
- At Regensburger Strasse turn left and go straight ahead up to the roundabout
- Turn off to right at the roundabout and follow Am Globus
- After about 1km turn off left to Michael-Faraday-Strasse
- Fraunhofer IKTS is on the left side

by train

- From Hermsdorf-Klosterlausnitz main station turn right and walk in the direction of the railway bridge
- Walk straight into Keramikerstrasse (do not cross the bridge)
- Pass the porcelain factory and the Hermsdorf town house
- Turn right, pass the roundabout and walk straight into Robert-Friese-Strasse
- After 600 m turn right into Michael-Faraday-Strasse
- Find Fraunhofer IKTS after 20 m

Editorial team/layout	Institute address
Katrin Schwarz	Fraunhofer Institute for
Peter Peuker	Ceramic Technologies and Systems IKTS
Andrea Gaal	
Susanne Freund	Dresden branch of the institute
Rita Kunath	Winterbergstrasse 28, 01277 Dresden, Germany
	Phone +49 351 2553-7700
Dutation	Fax +49 351 2553-7600
Printing	Hermsdorf branch of the institute
ELBTAL Druckerei & Kartonagen Kahle GmbH	Michael-Faraday-Strasse 1, 07629 Hermsdorf, Germany
ELDIAL Druckerer & Kartonageri Kanie Gilibir	Phone +49 36601 9301-0
	Fax +49 36601 9301-3921
Photo acknowledgments	
	info@ikts.fraunhofer.de
Atelier »Mein Foto« Dresden	www.ikts.fraunhofer.de
Foto Wachs Dresden	
Photographer Christian Hüller, Leipzig	
Photographer Jürgen Lösel, Dresden	Press and public relations
Photographer Sebastian Reuter, Jena	
Fraunhofer FEP	DiplChem. Katrin Schwarz
Fraunhofer IKTS	Phone +49 351 2553-7720
	katrin.schwarz@ikts.fraunhofer.de
	katiii.scriwarz@ikts.irauririorer.de
	Reprints permitted only upon express authorization by
	editorial team.
	© Fraunhofer IKTS, Dresden 04/2012